

DD CEN ISO/TS 16181:2011



BSI Standards Publication

Footwear — Critical substances potentially present in footwear and footwear components — Determination of phthalates in footwear materials (ISO/TS 16181:2011)

bsi.

...making excellence a habit.™

National foreword

This Draft for Development is the UK implementation of CEN ISO/TS 16181:2011.

This publication is not to be regarded as a British Standard.

It is being issued in the Draft for Development series of publications and is of a provisional nature. It should be applied on this provisional basis, so that information and experience of its practical application can be obtained.

Comments arising from the use of this Draft for Development are requested so that UK experience can be reported to the international organization responsible for its conversion to an international standard. A review of this publication will be initiated not later than 3 years after its publication by the international organization so that a decision can be taken on its status. Notification of the start of the review period will be made in an announcement in the appropriate issue of Update Standards.

According to the replies received by the end of the review period, the responsible BSI Committee will decide whether to support the

conversion into an international Standard, to extend the life of the Technical Specification or to withdraw it. Comments should be sent to the Secretary of the responsible BSI Technical Committee at British Standards House, 389 Chiswick High Road, London W4 4AL.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear, leather and coated fabrics.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© BSI 2011

ISBN 978 0 580 74887 5

ICS 61.060

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 August 2011.

Amendments issued since publication

Date	Text affected
------	---------------

ICS 61.060

English Version

**Footwear - Critical substances potentially present in footwear
and footwear components - Determination of phthalates in
footwear materials (ISO/TS 16181:2011)**

Chaussures - Substances critiques potentiellement
présentes dans les chaussures et les composants des
chaussures - Détermination des phtalates dans les
matériaux des chaussures (ISO/TS 16181:2011)

Schuhe - Möglicherweise in Schuhen und
Schuhbestandteilen vorhandene kritische Substanzen -
Bestimmung von Phthalaten in Schuhwerkstoffen (ISO/TS
16181:2011)

This Technical Specification (CEN/TS) was approved by CEN on 21 May 2011 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (CEN ISO/TS 16181:2011) has been prepared by Technical Committee CEN/TC 309 "Footwear", the secretariat of which is held by AENOR, in collaboration with Technical Committee ISO/TC 216 "Footwear".

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

In other circumstances, particularly when there is an urgent market requirement for such documents, a technical committee may decide to publish other types of document:

- an ISO Publicly Available Specification (ISO/PAS) represents an agreement between technical experts in an ISO working group and is accepted for publication if it is approved by more than 50 % of the members of the parent committee casting a vote;
- an ISO Technical Specification (ISO/TS) represents an agreement between the members of a technical committee and is accepted for publication if it is approved by 2/3 of the members of the committee casting a vote.

An ISO/PAS or ISO/TS is reviewed after three years in order to decide whether it will be confirmed for a further three years, revised to become an International Standard, or withdrawn. If the ISO/PAS or ISO/TS is confirmed, it is reviewed again after a further three years, at which time it must either be transformed into an International Standard or be withdrawn.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO/TS 16181 was prepared by the European Committee for Standardization (CEN) Technical Committee CEN/TC 309, *Footwear*, in collaboration with Technical Committee ISO/TC 216, *Footwear*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Introduction

Phthalates are commonly used as plasticizers in polymers. Toxicological concern has arisen due to their potential effect as endocrine disruptors and some of the listed phthalates are toxic in reproduction. The level of media publicity will ensure that their use continues to be of concern to consumers.

Phthalates are controversial because high doses of many phthalates have shown hormonal activity in rodent studies. Studies on rodents involving large amounts of phthalates have shown damage to the liver, the kidneys, the lungs, and the developing testes.

This Technical Specification calls for the use of substances and/or procedures that can be injurious to health if appropriate precautions are not observed. It refers only to technical suitability and does not absolve the user from legal obligations relating to health and safety at any stage.

Footwear — Critical substances potentially present in footwear and footwear components — Determination of phthalates in footwear materials

SAFETY PRECAUTIONS — Persons using this Technical Specification should be familiar with normal laboratory practice. This Technical Specification does not claim to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

IMPORTANT — It is absolutely essential that tests conducted according to this Technical Specification be carried out by suitably trained staff.

1 Scope

This Technical Specification specifies a test method to determine the presence of phthalate compounds. This test method is applicable to all types of footwear materials.

NOTE 1 This test method can also be used to determine plasticizers other than those listed in 3.2, subject to validation.

NOTE 2 ISO/TR 16178 defines which materials are concerned by this determination.

2 Principle

The aim of the method is to extract phthalates in footwear materials such as leather, textile, polymer, coated materials or others. This method uses extraction apparatus with *n*-hexane/acetone as solvent.

The total *n*-hexane/acetone extractable phthalate plasticizer content is calculated by weight with gas chromatography-mass spectrometry (GC-MS) detection to identify and quantify individual phthalates.

3 Apparatus and reagents

3.1 Apparatus

- 3.1.1 Scales, resolution of 1 mg.
- 3.1.2 Flask, 50 ml.
- 3.1.3 Water-cooled condenser.
- 3.1.4 Spark-proof heating mantle/water bath.
- 3.1.5 Ultrasonic bath.
- 3.1.6 Microwave extractor.
- 3.1.7 Steam bath or rotary evaporator.

3.1.8 Calibrated volumetric flasks of suitable volume.

Avoid direct contact between the samples and glassware and/or equipment used in order to minimize cross-contamination. Glassware, after washing, should be given an extra rinse with 0,1 N nitric acid and finally with acetone, acetone/methanol and/or cyclohexane. Dry at 110 °C for 1 h.

WARNING — The vapour of the organic solvents are highly flammable, especially at high temperature. Allow glassware to cool down before use.

3.1.9 Gas chromatograph with mass-selective detector (GC-MS).

3.2 Reagents

Unless otherwise specified, use only reagents of recognized analytical grade.

3.2.1 Water, distilled or of equivalent purity.

3.2.2 *n*-Hexane, CAS¹⁾ number: 110-54-3.

3.2.3 Di-iso-nonyl phthalate (DINP), CAS number: 28553-12-0 or 68515-48-0.

3.2.4 Di-(2-ethylhexyl) phthalate (DEHP), CAS number: 117-81-7.

3.2.5 Di-*n*-octyl phthalate (DNOP), CAS number: 117-84-0.

3.2.6 Di-iso-decyl phthalate (DIDP), CAS number: 26761-40-0 or 68515-49-1.

3.2.7 Butyl benzyl phthalate (BBP), CAS number: 85-68-7.

3.2.8 Di-butyl phthalate (DBP), CAS number: 84-74-2.

3.2.9 Di-cyclohexyl phthalate (DCHP), CAS number: 84-61 -7, internal standard.

3.2.10 Acetone, CAS number: 67-64-1.

3.2.11 Mixture of *n*-hexane/acetone, 80 %/20 % volume fraction.

3.2.12 Di-isobutyl phthalate (DIBP), CAS number: 84-69-5.

4 Sampling

The test piece consists of a single material taken from the footwear, such as leather, textile, polymer, coated material or others. The preparation of the sample should involve removal of the individual materials from the footwear, and preparation of a test piece made of particles as small as possible (but of at least 4 mm).

NOTE It is possible to grind the sample.

1) CAS: Chemical Abstract Service.

5 Test procedure

5.1 Preparation of solutions

5.1.1 Preparation of the internal standard solution

Prepare a 500 µg/ml stock solution of the internal standard in *n*-hexane.

5.1.2 Standard solution

Prepare a series of individual stock standard solutions of the individual phthalate in *n*-hexane, as shown in Table 1.

Table 1 — Stock solutions

Phthalate	DIDP	DINP	DBP	BBP	DNOP	DEHP	DIBP
Concentration, µg/ml	1 000	1 000	200	200	200	200	200

From the stock standard solutions, prepare appropriate phthalate calibration solutions in *n*-hexane.

Use at least five appropriate dilutions of the calibration sets to create calibration graphs, add to each an appropriate amount of internal standard and perform GC-MS analysis.

NOTE DIDP and DINP overlap in the chromatogram; the target ions to be chosen are indicated in Annex A.

5.2 Extraction procedures

5.2.1 General

Prepare the appropriate amount of internal standard solution.

5.2.2 Blank

For each series of tests, a blank shall be prepared. For the preparation of the blank, the complete procedure (extraction either 5.2.3 or 5.2.4 and GC-MS analysis) shall be done in a 50 ml glass flask (3.1.2) without the sample.

5.2.3 Ultrasonic extraction

Weigh accurately ($2,0 \pm 0,1$) g of the pieces of a representative specimen into a 50 ml glass flask (3.1.2) fitted with teflon stopcock. Add 40 ml of *n*-hexane/acetone (3.2.11) to wet the entire specimen.

Extract the phthalate in the ultrasonic bath (3.1.5) for 1 h at 50 °C and transfer the extract to a 50 ml volumetric flask (3.1.8) after filtration or centrifugation.

Fill to the mark with *n*-hexane.

Transfer a known volume of organic phase into a suitable GC sampling vial, add an appropriate volume of internal standard solution and perform GC-MS analysis. If necessary, prepare further diluted solutions using the original solution and repeat the analysis after adding the appropriate volume of internal standard solution.

5.2.4 Microwave extractor

Weigh accurately ($2,0 \pm 0,1$) g of the pieces of a representative specimen into a polytetrafluoroethylene (PTFE) vessel. Add a sufficient quantity of the *n*-hexane/acetone mixture (3.2.11) to wet the whole specimen.

Extract the phthalate in the microwave extractor. The following parameters could be used as a basis for optimizing the extraction:

- power: 600 W;
- time: 15 min;
- temperature: 100 °C;
- pressure: 10 bars (1 MPa).

Transfer the extract into a 50 ml volumetric flask. Fill to the mark with *n*-hexane.

Transfer a known volume into a suitable GC sampling vial, add an appropriate volume of internal standard solution and perform GC-MS analysis. If necessary, prepare further diluted solutions using the original solution and repeat the analysis after adding the appropriate volume of internal standard solution.

5.3 Calculation of results

From the calibration graph, determine the content of each phthalate, *P*, expressed as a percentage, corrected for the internal standard peak area, and interpolate the concentration of the phthalate in microgrammes per millilitre, correcting for any dilutions. Subtract the blank concentration (see 5.2.2) from the specimen concentration, according to Equation (1).

$$P = \frac{V \times (c_s \times c_b)}{m \times 1000} \quad (1)$$

where

- V* is the volume of the volumetric flask, in millilitres;
- m* is the corrected mass of the specimen, in grammes;
- c_b* is the concentration of the individual phthalate of blank solution, in microgrammes per millilitre;
- c_s* is the concentration of the individual phthalate of the specimen solution, corrected for any dilutions, in microgrammes per millilitre.

6 Test report

The test report shall include at least the following:

- a) a reference to this Technical Specification, i.e. ISO/TS 16181:2011;
- b) all details necessary for complete identification of the sample tested;
- c) a description of the extraction apparatus;
- d) the percentage by mass of each listed phthalate in the plasticized material or tested material;
- e) any deviation by agreement or otherwise from the procedure specified.

Annex A (informative)

Suitable gas chromatography-mass spectrometry (GC-MS) apparatus, method and precision data for determination of phthalate plasticizers

A.1 General

The following equipment, column and operating conditions have been found suitable:

Equipment: 6890 gas chromatograph (GC) mass-selective device (MS), quadrupole.

Column: 5 % phenyl methyl siloxane for MS; length 30 m; 0,32 mm interior diameter and 0,25 µm film thickness.

Carrier gas: helium.

Flow rate: 2,0 ml/min.

Injector temperature: 250 °C, mode splitless or split.

Injection volume: 1,0 µl.

Temperature programme: 150 °C for 1 min.
up to 250 °C at 8 °C/min.
up to 290 °C at 3 °C/min.
isothermal 5,00 min.
Total programme time: 34 min.

Transfer line temperature: 290 °C.

MS mode: Electron impact.

Typical quantification ions for phthalate plasticizers are shown in Table A.1.

Table A.1 — Typical quantification ions for phthalate plasticizers

Phthalate plasticizers	Target ion	Q1	Q2
Di-butyl phthalate (DBP)	149	223	205
Butyl benzyl phthalate (BBP)	149	206	238
Di-(2-ethylhexyl) phthalate (DEHP)	149	167	279
Di- <i>n</i> -octyl phthalate (DNOP)	149	279	261
Di-iso-nonyl phthalate (DINP)	293	149	127
Di-iso-decyl phthalate (DIDP)	307	149	141
Di-cyclohexyl phthalate (DCHP) (internal standard)	149	167	249
Di-isobutyl phthalate (DIBP)	149	223	205

Depending on the type of equipment used, the appropriate operating conditions may need to be established.

A.2 Detection limits and precision data

The detection limits for GC-MS analysis for the phthalate esters are shown in Table A.2.

Table A.2 — Detection limits for GC-MS analysis for phthalate esters

Phthalate ester	DIDP	DINP	DBP	BBP	DNOP	DEHP	DCHP
Detection limit, µg/ml	3,0	2,5	0,05	0,05	0,05	0,05	0,05

The repeatability data, r , on six analyses of a polyvinylchloride (PVC) reference material is $(38,62 \pm 0,83)$ % for a relative coefficient $C_{V,rel} = \pm 2$ %.

The repeatability data, r , on six analyses of an article gave a mean value of $(20,5 \pm 0,71)$ % for a relative coefficient $C_{V,rel} = \pm 3$ % for similar articles.

NOTE The coefficient of variation, C_V , is the ratio of the standard deviation to the average (see ISO 3534-1).

Bibliography

- [1] ISO 3534-1, *Statistics — Vocabulary and symbols — Part 1: General statistical terms and terms used in probability*
- [2] ISO/TR 16178, *Footwear — Critical substances potentially present in footwear and footwear components*
- [3] EN 14372:2004, *Child use and care articles — Cutlery and feeding utensils — Safety requirements and tests*
- [4] Commission Directive 2005/84/EC of the European Parliament and of the Council of 14 December 2005 on phthalates in toys and child care articles
- [5] Commission Directive 2001/95/EC of the European Parliament and of the Council of 3 December 2001 on general product safety

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™