



BSI Standards Publication

**Steels and cast irons —  
Determination of lead,  
cadmium, mercury, hexavalent  
chromium, polybrominated  
biphenyls (PBB) and  
polybrominated diphenylethers  
(PBDE) with regard to  
directives 2011/65/EU (RoHS)  
and 2000/53/EC (ELV) —  
Limitations**

**National foreword**

This Published Document is the UK implementation of CEN/TR 10364:2016.

The UK participation in its preparation was entrusted to Technical Committee ISE/102, Methods of Chemical Analysis for Iron and Steel.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2016. Published by BSI Standards Limited 2016

ISBN 978 0 580 90484 4

ICS 77.040.30; 77.080.01

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 30 April 2016.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

TECHNICAL REPORT

**CEN/TR 10364**

RAPPORT TECHNIQUE

TECHNISCHER BERICHT

March 2016

ICS 77.040.30; 77.080.01

English Version

**Steels and cast irons - Determination of lead, cadmium, mercury, hexavalent chromium, polybrominated biphenyls (PBB) and polybrominated diphenylethers (PBDE) with regard to directives 2011/65/EU (RoHS) and 2000/53/EC (ELV) - Limitations**

Aciers et fontes - Déterminations du plomb, du cadmium, du mercure, du chrome hexavalent, des diphenyles polybromés (PBB) et des diphenyléthers polybromés (PBDE) en relation avec les directives 2011/65/EU (RoHS) et 2000/53/EC (ELV) - Limites

Stahl und Gusseisen - Bestimmung von Blei, Cadmium, Quecksilber, sechswertigem Chrom, polybromierten Biphenylen (PBB) und polybromierten Diphenylethern im Hinblick auf EU-Direktiven 2011/65/EU (RoHS) und 2000/53/EC (ELV) - Beschränkungen

This Technical Report was approved by CEN on 29 September 2015. It has been drawn up by the Technical Committee ECISS/TC 102.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

<b>Contents</b>	<b>Page</b>
<b>European foreword</b> .....	<b>3</b>
<b>1 Scope</b> .....	<b>4</b>
<b>2 Requirements and applicability</b> .....	<b>4</b>
<b>2.1 General</b> .....	<b>4</b>
<b>2.2 Bulk materials</b> .....	<b>4</b>
<b>2.2.1 Lead (Pb)</b> .....	<b>4</b>
<b>2.2.2 Cadmium (Cd) and mercury (Hg)</b> .....	<b>5</b>
<b>2.2.3 Hexavalent chromium [Cr (VI)]</b> .....	<b>5</b>
<b>2.2.4 Polybrominated biphenyls (PBB) and polybrominated diphenylethers (PBDE)</b> .....	<b>5</b>
<b>2.3 Surface</b> .....	<b>5</b>
<b>2.3.1 General</b> .....	<b>5</b>
<b>2.3.2 Hexavalent chromium [Cr (VI)]</b> .....	<b>5</b>
<b>3 Recommendation</b> .....	<b>6</b>
<b>Bibliography</b> .....	<b>7</b>

## **European foreword**

This document (CEN/TR 10364:2016) has been prepared by Technical Committee ECISS/TC 102 “Methods of chemical analysis for iron and steel”, the secretariat of which is held by SIS.

This project was submitted to the vote with document reference FprCEN/TR 16895.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

## 1 Scope

The present Technical Report gives guidance regarding the chemical composition controls of steels (except chrome plated products) and cast irons in respect of the European legislation, namely Directives 2011/65/EU (RoHS) [1], repealing 2002/95/EU and 2000/53/EC (ELV) [2].

These directives require the characterization of these materials for Cadmium (Cd), hexavalent chromium (Cr (VI)), mercury (Hg), Lead (Pb), polybrominated biphenyls (PBB) and polybrominated diphenylethers (PBDE). Nevertheless, the directives do not reflect the correspondence between these elements/compounds and the normal composition of each material concerned. In other words, for every material there is an obligation to determine all the compounds listed, independently of the relevance of such controls.

## 2 Requirements and applicability

### 2.1 General

Directive 2011/65/EU, article 4, restricts the following substances to the maximum concentration values to the following concentrations:

- Lead: 0,1 %;
- Mercury: 0,1 %;
- Cadmium: 0,01 %;
- Hexavalent chromium: 0,1 %;
- Polybrominated biphenyls (PBB): 0,1 %;
- Polybrominated diphenyl ethers (PBDE): 0,1 %.

Steel and cast iron manufacturers are often required to state/provide compliance with the directives above and submit analytical results for each of those elements/compounds. However, due to the manufacturing processes and the inherent properties of the steels and cast irons, the determination of most of the compounds listed is not applicable or relevant.

Subclauses 2.2 and 2.3 details the relevance of these requirements.

### 2.2 Bulk materials

#### 2.2.1 Lead (Pb)

Due to a 1 755 °C boiling point, lead is the single element among the six compounds specified in the directives which can be present in the steels and cast irons.

NOTE For stainless steel production using the Argon Oxygen Decarburization (AOD) converter process or equivalent, the lead content in the alloy will be considerably decreased to orders of magnitude below the directives requirements levels.

In contrast to cadmium and mercury, lead is also possible to detect and quantify on a reproducible base by using standardized methods as EN 10181 [3], EN 62321 [4], EN 62321-1 [5] or ISO 16918-1 [6].

### 2.2.2 Cadmium (Cd) and mercury (Hg)

With high temperature required during the melting processes and because of their physico-chemical properties, cadmium (Cd) and mercury (Hg) are normally absent in steels and cast irons.

The temperature required for melting iron based alloys is at least 1 400 °C, whereas the boiling temperatures of Cadmium (Cd) and mercury (Hg) are 767 °C and 357 °C respectively. In other words, these elements will evaporate during the melting process and cannot be present in an easily quantifiable amount in the steels and cast irons.

There are analytical techniques available and appropriate for the determination of both these elements below

1 µg/g as, for example, inductively coupled plasma mass spectrometry (ICP-MS), cold vapour atomic absorption spectrometry or electrothermal atomic absorption spectrometry (ETAAS). However for the physical reasons above, i.e. the “absence of content”, it remains impossible to verify the robustness of the procedures for such aims: this includes selecting the most appropriate dissolution procedures and also the unavailability of appropriate reference materials.

### 2.2.3 Hexavalent chromium [Cr (VI)]

According to the document “hexavalent chromium in steels, cobalt, nickel and zirconium based alloys” [7] the occurrence of hexavalent chromium (Cr (VI)) in steel is purely hypothetical. This is due to the physical nature of metallic bonding where ions cannot exist.

### 2.2.4 Polybrominated biphenyls (PBB) and polybrominated diphenylethers (PBDE)

The most common types of polybrominated biphenyls (PBB) and polybrominated diphenylethers (PBDE) homologues are penta-, octo- and deca- bromodiphenyl ethers and hexa-, octo- and deca- bromobiphenyl ethers. They are extremely stable compounds with boiling points in the range of about 300 to 500 °C. Investigations [8] have shown that polybrominated biphenyls (PBB) decompose by pyrohydrolysis at temperatures ranging from 600 to 900 °C, i.e. significantly lower than in the steel making process and that the main part of polybrominated diphenylethers (PBDE) in fly ash from electric arc furnaces are destroyed or removed by thermal treatment at

1 450 °C [9].

Thus it shall be concluded that these compounds cannot be present in the steel (or cast iron) itself.

## 2.3 Surface

### 2.3.1 General

The as-delivered products from the steel plants or foundries are controlled and protected.

However, as for any material, the surface of steel and cast iron products may get contaminated or may undergo surface reactions. In some circumstances, due to further processing or treatments, this may result in presence of un-wanted substances on the surface.

### 2.3.2 Hexavalent chromium [Cr (VI)]

Due to some surface treatment, hexavalent chromium (Cr (VI)) is the single substance among the six elements/compounds specified in the directives which may be found on the surface of the steels and cast irons.

However a positive detection of this ion on the surface of any steel or cast iron shall not be put in correspondence with the bulk material composition. For the control of this ion, standardized methods are available as, for example, EN 62321.

### 3 Recommendation

When receiving requirements related with Directives 2011/65/EU (RoHS), 2002/95/EU and 2000/53/EC, it is recommended to take the information given in the present Technical Report into account.

In other words, the single compounds relevant to be determined are:

- lead in the bulk materials (see NOTE in 2.2.1);
- hexavalent chromium (Cr (VI)) on the surface of some products (see 2.3.2).



## Bibliography

- [1] Directive 2011/65/EU of the European Parliament and of the Council of 8 June 2011 on the restriction of the use of certain hazardous substances in electrical and electronic equipment (RoHS)
- [2] Directive 2000/53/EC of the European Parliament and of the Council of 18 September 2000 on end-of life vehicles (ELV)
- [3] EN 10181, *Chemical analysis of ferrous materials - Determination of lead in steels - Flame atomic absorption spectrometric method*
- [4] EN 62321, *Electrotechnical products — Determination of levels of six regulated substances (lead, mercury, cadmium, hexavalent chromium, polybrominated biphenyls, polybrominated diphenyl ethers) (IEC 62321)*
- [5] EN 62321-1, *Determination of certain substances in electrotechnical products — Part 1: Introduction and overview (IEC 62321-1)*
- [6] ISO 16918-1, *Steel and iron — Determination of nine elements by the inductively coupled plasma mass spectrometric method — Part 1: Determination of tin, antimony, cerium, lead and bismuth*
- [7] Hexavalent Chromium in steels, cobalt, nickel and zirconium based alloys, issued by Swerea KIMAB
- [8] IPCS/INCHEM, International Programme on Chemical Safety, Health and Safety Guide No. 83
- [9] MING LIN YI, ZHOU S.-Q. et al. Emissions of polybrominated diphenyl ethers during the thermal treatment for electric arc furnace fly ash. *Aerosol Air Qual. Res.* 2012, **12** pp. 237–250





# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK