

PD CEN/TS 14541:2013



BSI Standards Publication

# Plastics pipes and fittings — Characteristics for utilisation of non-virgin PVC-U, PP and PE materials

**bsi.**

...making excellence a habit.™

**National foreword**

This Published Document is the UK implementation of CEN/TS 14541:2013. It supersedes DD CEN/TS 14541:2007 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee PRI/88/1, Plastics piping for non-pressure applications.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013

ISBN 978 0 580 80005 4

ICS 23.040.20; 23.040.45

**Compliance with a British Standard cannot confer immunity from legal obligations.**

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 31 May 2013.

**Amendments issued since publication**

Date	Text affected
------	---------------

---

TECHNICAL SPECIFICATION  
SPÉCIFICATION TECHNIQUE  
TECHNISCHE SPEZIFIKATION

# CEN/TS 14541

May 2013

ICS 23.040.20; 23.040.45

Supersedes CEN/TS 14541:2007

English Version

## Plastics pipes and fittings - Characteristics for utilisation of non-virgin PVC-U, PP and PE materials

Tubes et raccords en plastique - Caractéristiques pour l'utilisation de matières non vierges en PVC-U, PP et PE

Kunststoffrohrlösungen und Formstücke - Eigenschaften für die Verwendung von Rücklaufmaterial und Recyclat aus PVC-U-, PP- und PE-Materialien

This Technical Specification (CEN/TS) was approved by CEN on 6 November 2012 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

## Contents

Page

Foreword.....	3
1 Scope .....	4
2 Normative references .....	4
3 Terms, definitions and abbreviations .....	5
3.1 Terms and definitions .....	5
3.2 Abbreviations .....	5
4 Utilisation of non-virgin material for non-pressure application .....	5
4.1 Own reprocessed material .....	5
4.2 External reprocessed and recycled materials with agreed specification .....	5
4.3 External reprocessed and recycled materials without agreed specification .....	6
5 Utilisation of non-virgin material for pressure application .....	8
5.1 Own reprocessed material .....	8
5.2 External reprocessed and recycled materials with agreed specification .....	8
5.3 External reprocessed and recycled materials without agreed specification .....	8
6 General guidance for utilisation of non-virgin material.....	9
Bibliography .....	10

## Foreword

This document (CEN/TS 14541:2013) has been prepared by Technical Committee CEN/TC 155 “Plastics piping systems and ducting systems”, the secretariat of which is held by NEN.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TS 14541:2007.

The main changes are:

- definitions brought in line with common practice;
- application “Pressure piping systems” is introduced;
- a general guidance has been added for utilisation of non-virgin materials;
- Annex A “Processing and performance of pipes and characteristics of recyclable material” is deleted.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This Technical Specification specifies definitions and recommended characteristics and test methods for the utilisation of PVC-U, PP and PE non-virgin materials in pipes, fittings and ancillaries for both pressure and non-pressure piping systems.

This Technical Specification specifies the conditions for utilisation of non-virgin material with and without agreed specification

Non-virgin materials may be reformulated by the use of additives and processing techniques to meet an agreed specification. Typically the additives used would be stabilisers and pigments etc.

The WG responsible for the product standard should consider the content of this document and only permit dosage levels which give compliance with the requirements of the product standard. Further, the WG should consider whether extra or more frequent product testing is relevant when using such material in the production of pipes and fittings in accordance with the relevant product standard.

NOTE For the purpose of this specification the term pipes means extruded pipes, gutters and any parts of a fabricated fitting which is made from an extruded pipe. The term fitting means injection- and rotomoulded fittings and injection moulded parts of a fabricated fitting.

For the recycling process, the testing and the use of the non-virgin material National and/or European regulations may apply.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12099, *Plastics piping systems — Polyethylene piping materials and components — Determination of volatile content*

EN 10204:2004, *Metallic products — Types of inspection documents*

EN 15346:2007, *Plastics — Recycled Plastics — Characterisation of poly(vinyl chloride) (PVC) recyclates*

EN ISO 306, *Plastics — Thermoplastic materials — Determination of Vicat softening temperature (VST) (ISO 306)*

EN ISO 13229, *Thermoplastics piping systems for non-pressure applications — Unplasticized poly(vinyl chloride) (PVC-U) pipes and fittings — Determination of the viscosity number and K-value (ISO 13229)*

EN ISO 1133-1, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method (ISO 1133-1)*

EN ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method (ISO 1183-2)*

EN ISO 3451-1:2008, *Plastics — Determination of ash — Part 1: General method (ISO 3451-1:2008)*

EN ISO 3451-5, *Plastics — Determination of ash — Part 5: Poly(vinyl chloride) (ISO 3451-5)*

EN ISO 11357-6, *Plastics — Differential scanning calorimetry (DSC) — Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT) (ISO 11357-6)*

### 3 Terms, definitions and abbreviations

#### 3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

##### 3.1.1

##### **virgin material**

material in the form such as granules or powder that have not been subjected to use or processing other than that required for their manufacture and to which no reprocessed or recycled material have been added

##### 3.1.2

##### **own reprocessed material**

material prepared from rejected unused pipes, gutters, fittings and ancillaries, including trimmings from the production, that will be reprocessed in a manufacturer's plant after having been previously processed by the same manufacturer by a process such as moulding or extrusion and for which the complete formulation is known

##### 3.1.3

##### **external reprocessed material**

material from the production of unused thermoplastic products, regardless of where they are manufactured

##### 3.1.4

##### **recycled material**

material from used thermoplastic products which have been cleaned and crushed or ground

##### 3.1.5

##### **agreed specification**

specification of the relevant material characteristics agreed between the supplier of the non-virgin material and the pipe, fitting and/or ancillary manufacturer

#### 3.2 Abbreviations

PE : polyethylene

PP : polypropylene

PP-MD : polypropylene modified by minerals

PVC-U : unplasticized poly(vinyl chloride)

MFR : melt mass-flow rate

OIT : oxidation induction time

### 4 Utilisation of non-virgin material for non-pressure application

#### 4.1 Own reprocessed material

The use of clean, own reprocessed material for the production of pipes, gutters, fittings and ancillaries shall be permitted without limitations unless otherwise specified in the referring standard.

#### 4.2 External reprocessed and recycled materials with agreed specification

External reprocessed and recycled material with an agreed specification shall be permitted for the production of pipes, gutters, fittings and ancillaries provided that all the following conditions are met:

- it shall at least cover the characteristics given in Tables 1, 2 and 3 for PVC-U, PP/PP-MD and PE, respectively.
- when determined in accordance with the test methods given in Tables 1, 2 and 3 for PVC-U, PP/PP-MD and PE, the actual values from these characteristics shall conform to the values given in the agreed specification.
- each delivery shall be covered by a declaration according to 4.1 of EN 10204:2004, showing conformity to the agreed specification by Inspection certificate 3.1, "type3.1". This declaration can be made by either the material supplier or the product manufacturer as agreed between the parties.
- The quality plan of the supplier of external reprocessed or recycled material should conform to EN ISO 9001 [1].

### 4.3 External reprocessed and recycled materials without agreed specification

The use of clean external reprocessed and recycled materials without agreed specification for the production of pipes, gutters, fittings and ancillaries shall not be permitted unless otherwise specified in the referring standard.

**Table 1 — Characteristics of external reprocessed and recycled PVC-U that should be included in the agreed specification**

Characteristic	Unit	Test method <sup>a, b</sup>	Remark
Density	kg/m <sup>3</sup>	EN ISO 1183-2	
Filler content by ash rest	% by mass	EN ISO 3451-5	Linked to PVC content
K-value		EN ISO 13229	
Vicat softening temperature	°C	EN ISO 306	
Particle size	mm	Sieve analysis	
Type of pigments and stabiliser		By analysis	
Impurities		Annex C of EN 15346:2007 or evaluation of sheets or evaluation of micronized material	
Extraneous polymers		IR analyses or DSC	Presence

<sup>a</sup> Samples shall be taken from the compounded and pelletised or from each individual material batch source. The frequency of sampling shall be agreed between supplier and product manufacturer and where relevant, the certification body.

<sup>b</sup> If the source of the material is consistent, e.g. pipes and fittings or other products produced under a quality mark. It is not required to test those material characteristics covered by the quality mark.

When deciding the amount of characteristics to be tested, the frequency with which they have to be tested and the related requirements at least the following should be considered:

- 1) the recycling process and sources of the material because of risk of impurities;
- 2) the processing of the material into the end product;
- 3) the wanted characteristics of the end product;
- 4) possible limitations of sources for the recyclable material;
- 5) the intended dosage level of the material.



**Table 2 — Characteristics of external reprocessed and recycled PP and PP-MD that should be included in the agreed specification**

<b>Characteristic</b>	<b>Unit</b>	<b>Test method <sup>a, b</sup></b>	<b>Remark</b>
Density	kg/m <sup>3</sup>	EN ISO 1183-2	
Thermal Stability OIT	min	EN ISO 11357-6 Temperature 200 °C	
MFR	g/10 min	EN ISO 1133-1	
Ash residue	%	EN ISO 3451-1:2008	
Extraneous polymers		IR analyses or DSC	Presence
Impurities		Mesh filtering	Use agreed mesh size
Type of pigments and/or additives		By analysis	Optional; to be agreed between purchaser and supplier
Volatile matter	mg/kg	EN 12099	
<p><sup>a</sup> Samples shall be taken from the compounded and pelletised or from each individual material batch source. The frequency of sampling shall be agreed between supplier and product manufacturer and where relevant, the certification body.</p> <p><sup>b</sup> If the source of the material is consistent, e.g. pipes and fittings or other products produced under a quality mark. It is not required to test those material characteristics covered by the quality mark.</p> <p>When deciding the amount of characteristics to be tested, the frequency with which they have to be tested and the related requirements at least the following should be considered:</p> <ol style="list-style-type: none"> <li>1) the recycling process and sources of the material because of risk of extraneous polymers and impurities;</li> <li>2) the processing of the material into the end product;</li> <li>3) the wanted characteristics of the end product;</li> <li>4) possible limitations of sources for the recyclable material;</li> <li>5) the intended dosage level of the material.</li> </ol>			

**Table 3 – Characteristics of external reprocessed and recycled PE that should be included in the agreed specification**

Characteristic	Unit	Test method <sup>a,b</sup>	Remarks
Density	kg/m <sup>3</sup>	EN ISO 1183-2	
Thermal stability OIT	min	EN ISO 11357-6 Temperature 200 °C	
MFR	g/10 min	EN ISO 1133-1	
Ash residue	%	EN ISO 3451-1:2008	
Extraneous polymers		IR analysis or DSC	Presence
Impurities		Mesh filtering	Use agreed mesh size
Type of pigments and/or additives		By analysis	Optional; to be agreed between purchaser and supplier
Volatile matter	mg/kg	EN 12099	
<p><sup>a</sup> Samples shall be taken from the compounded and pelletised or from each individual material batch source. The frequency of sampling shall be agreed between supplier and product manufacturer and where relevant, the certification body.</p> <p><sup>b</sup> If the source of the material is consistent, e.g. pipes and fittings or other products produced under a quality mark. It is not required to test those material characteristics covered by the quality mark.</p> <p>When deciding the amount of characteristics to be tested, the frequency with which they have to be tested and the related requirements at least the following should be considered:</p> <ol style="list-style-type: none"> <li>1) the recycling process and sources of the material because of risk of extraneous polymers and impurities;</li> <li>2) the processing of the material into the end product;</li> <li>3) the wanted characteristics of the end product;</li> <li>4) possible limitations of sources for the recyclable material;</li> <li>5) the intended dosage level of the material.</li> </ol>			

## 5 Utilisation of non-virgin material for pressure application

### 5.1 Own reprocessed material

The use of clean, own reprocessed material for the production of pipes, fittings and ancillaries shall be specified in the referring product standard.

### 5.2 External reprocessed and recycled materials with agreed specification

The use of clean external reprocessed and recycled materials with agreed specification for the production of pipes, fittings and ancillaries shall not be permitted.

### 5.3 External reprocessed and recycled materials without agreed specification

The use of clean external reprocessed and recycled materials without agreed specification for the production of pipes, fittings and ancillaries shall not be permitted.

## **6 General guidance for utilisation of non-virgin material**

In case of utilisation of non-virgin material, with or without an agreed specification, the following should be considered:

- the maximum quantity of external reprocessed and recycled material that is intended to be added shall be specified by the product manufacturer or in accordance with the applicable product standard;
- the quantity of external reprocessed and recycled material that is actually added in each production series shall be recorded by the product manufacturer;
- the performance of the end product shall conform to all the requirements specified in the relevant product standard;
- type testing shall be carried out on the end product with the maximum specified percentage by weight and with each form [e.g. granules or powder] of external reprocessed or recycled material with an agreed specification. Approved results shall be taken as proving conformity also of components containing lower levels of external reprocessed or recycled material.

## Bibliography

- [1] EN ISO 9001, *Quality management systems — Requirements (ISO 9001)*
- [2] EN 15344, *Plastics — Recycled Plastics — Characterisation of Polyethylene (PE) recyclates*
- [3] EN 15345, *Plastics — Recycled Plastics — Characterisation of Polypropylene (PP) recyclates*
- [4] EN ISO 1133-2, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 2: Method for materials sensitive to time-temperature history and/or moisture (ISO 1133-2)*



# British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

## About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

## Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at [bsigroup.com/standards](http://bsigroup.com/standards) or contacting our Customer Services team or Knowledge Centre.

## Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at [bsigroup.com/shop](http://bsigroup.com/shop), where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

## Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to [bsigroup.com/subscriptions](http://bsigroup.com/subscriptions).

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

**PLUS** is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit [bsigroup.com/shop](http://bsigroup.com/shop).

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email [bsmusales@bsigroup.com](mailto:bsmusales@bsigroup.com).

## BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

## Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

## Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

## Useful Contacts:

### Customer Services

**Tel:** +44 845 086 9001

**Email (orders):** [orders@bsigroup.com](mailto:orders@bsigroup.com)

**Email (enquiries):** [cservices@bsigroup.com](mailto:cservices@bsigroup.com)

### Subscriptions

**Tel:** +44 845 086 9001

**Email:** [subscriptions@bsigroup.com](mailto:subscriptions@bsigroup.com)

### Knowledge Centre

**Tel:** +44 20 8996 7004

**Email:** [knowledgecentre@bsigroup.com](mailto:knowledgecentre@bsigroup.com)

### Copyright & Licensing

**Tel:** +44 20 8996 7070

**Email:** [copyright@bsigroup.com](mailto:copyright@bsigroup.com)



...making excellence a habit.™