

PD ISO/TS 11619:2014



BSI Standards Publication

Polyurethane tubing for use primarily in pneumatic installations — Dimensions and specification

bsi.

...making excellence a habit.™

National foreword

This Published Document is the UK implementation of ISO/TS 11619:2014.

The UK participation in its preparation was entrusted to Technical Committee PRI/66, Rubber and plastics tubing, hoses and hose assemblies.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2014. Published by BSI Standards Limited 2014

ISBN 978 0 580 85118 6

ICS 23.040.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 28 February 2014.

Amendments issued since publication

Date	Text affected
------	---------------

TECHNICAL
SPECIFICATION

ISO/TS
11619

First edition
2014-02-15

**Polyurethane tubing for use primarily
in pneumatic installations —
Dimensions and specification**

*Tubes en polyuréthane utilisés principalement dans les installations
pneumatiques — Dimensions et spécifications*



Reference number
ISO/TS 11619:2014(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2014

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Materials and construction	1
5 Dimensions and tolerances	1
5.1 Outside diameters, wall thickness and tolerances.....	1
5.2 Length tolerances.....	2
6 Performance requirements	2
6.1 Hydrostatic testing at 23 °C ± 2 °C.....	2
6.2 Hydrostatic testing at 60 °C ± 2 °C.....	3
6.3 Maximum working pressure.....	3
6.4 Minimum bend radius.....	3
7 Type, routine and production testing	4
8 Marking	4
9 Recommendations for packing and storage	4
Annex A (normative) Test frequency	5
Annex B (informative) Recommended tests for production testing	6
Bibliography	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: Foreword - Supplementary information

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Rubber and plastics hoses and hose assemblies*.

Introduction

This Technical Specification has been prepared to provide minimum acceptable requirements for the satisfactory performance of thermoplastic polyurethane tubing used mainly in pneumatic applications.

The tubing conveys compressed air which controls and powers pneumatic systems.

This Technical Specification will be revised to an International Standard when ISO 14743 has been revised and published in ISO/TC 131.

Polyurethane tubing for use primarily in pneumatic installations — Dimensions and specification

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate health and safety practices and to ensure compliance with any national regulatory conditions.

1 Scope

This Technical Specification specifies the requirements for flexible thermoplastic polyurethane tubing conveying compressed air, for use in the ambient temperature range from 23 °C to 60 °C, in sizes from 3 mm to 12 mm outside diameter. Working pressure depends on the tube size and the service temperature (see [Table 4](#)). Tubing may be used with push on connectors which are specified in ISO 14743.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1307, *Rubber and plastics hoses — Hose sizes, minimum and maximum inside diameters, and tolerances on cut-to-length hoses*

ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing*

ISO 10619-1:2011, *Rubber and plastics hoses and tubing — Measurement of flexibility and stiffness — Part 1: Bending tests at ambient temperature*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 8331, *Rubber and plastics hoses and hose assemblies — Guidelines for selection, storage, use and maintenance*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

4 Materials and construction

The tubing shall be manufactured from polyester or polyether based polyurethane and shall be homogenous, and free from surface imperfections. The tubing is extruded and can be coloured to user requirements. For applications where there is moisture or water present above 40 °C, polyurethane materials with good hydrolysis resistance would be required. This must be specified by the user to the supplier of the tubing.

5 Dimensions and tolerances

5.1 Outside diameters, wall thickness and tolerances

The outside diameters and tolerances of tubing shall meet the requirements given in [Table 1](#).

Table 1 — Outside diameters, wall thickness and tolerances

Outside diameter		Wall thickness	
Diameter mm	Tolerance mm	Thickness mm	Tolerance mm
3	±0,10	0,50	+ 0,10 - 0,05
4	±0,10	0,75	+ 0,10 - 0,05
5	±0,10	1,00	+ 0,10 - 0,05
6	±0,10	1,00	+ 0,10 - 0,05
8	±0,10	1,25	+ 0,10 - 0,05
8	±0,10	1,00	+ 0,10 - 0,05
10	±0,15	1,50	+ 0,15 - 0,07
10	±0,15	1,00	+ 0,15 - 0,05
12	±0,15	2,00	+ 0,15 - 0,07

5.2 Length tolerances

The tolerances on cut lengths shall be in accordance with ISO 1307.

6 Performance requirements

6.1 Hydrostatic testing at 23 °C ± 2 °C

When subjected to the burst pressure test specified in ISO 1402 at 23 °C ± 2 °C, tubing shall meet the requirements specified in [Table 2](#).

Table 2 — Burst testing at 23 °C ± 2 °C

Outside diameter mm	Wall thickness mm	Minimum burst pressure MPa	Minimum burst pressure bar
3	0,5	5,40	54,0
4	0,75	6,23	62,3
5	1,0	6,75	67,5
6	1,0	5,40	54,0
8	1,25	5,00	50,0
8	1,0	3,84	38,4
10	1,5	4,76	47,6
10	1,0	3,00	30,0
12	2,0	5,40	54,0

6.2 Hydrostatic testing at 60 °C ± 2 °C

When subjected to the burst pressure test specified in ISO 1402 at 60 °C ± 2 °C, tubing shall meet the requirements given in [Table 3](#). Tests shall be conducted at 60 °C in a proper temperature controlled cabinet, and compressed gas (either air or nitrogen) can be used as a burst test media.

Table 3 — Burst testing at 60 °C ± 2 °C

Outside diameter mm	Wall thickness mm	Minimum burst pressure MPa	Minimum burst pressure bar
3	0,5	3,46	34,6
4	0,75	3,98	39,8
5	1,0	4,32	43,2
6	1,0	3,45	34,5
8	1,25	3,20	32,0
8	1,0	2,47	24,7
10	1,5	3,04	30,4
10	1,0	1,92	19,2
12	2,0	3,45	34,5

6.3 Maximum working pressure

The maximum working pressure shall be as specified in [Table 4](#).

Table 4 — Maximum working pressures at 23 °C and 60 °C

Outside diameter mm	Wall thick- ness mm	Maximum work- ing pressure at 23 °C MPa	Maximum work- ing pressure at 23 °C bar	Maximum work- ing pressure at 60 °C MPa	Maximum work- ing pressure at 60 °C bar
3	0,5	1,35	13,5	0,86	8,6
4	0,75	1,55	15,5	0,99	9,9
5	1,0	1,68	16,8	1,08	10,8
6	1,0	1,35	13,5	0,86	8,6
8	1,25	1,25	12,5	0,80	8,0
8	1,0	0,96	9,6	0,61	6,1
10	1,5	1,19	11,9	0,76	7,6
10	1,0	0,75	7,5	0,48	4,8
12	2,0	1,35	13,5	0,86	8,6

NOTE Maximum working pressures are based on a factor of safety of 4:1 on minimum burst pressures because the main use of this tubing is for conveying compressed air.

6.4 Minimum bend radius

When tested in accordance with ISO 10619-1:2011 method A1, the minimum bend radius shall be as specified in [Table 5](#), and the value of T/D shall be greater than 0,9.

Table 5 — Minimum bending radius at 23 °C

Outside diameter mm	Wall thickness mm	Minimum bend radius at 23 °C mm
3	0,5	13
4	0,75	13
5	1,0	15
6	1,0	20
8	1,25	25
8	1,0	35
10	1,5	40
10	1,0	60
12	2,0	40

7 Type, routine and production testing

For type testing and routine testing, the tests specified in [Annex A](#) shall be carried out.

For production testing, the tests given in [Annex B](#) are recommended.

NOTE

- Type tests are those tests required to obtain product approval;
- Routine tests are those carried out on each length of tubing; and
- Production tests are those carried out on each production batch.

8 Marking

Tubing shall be marked in characters which can be easily seen with the naked eye, either using a contrasting indelible ink or as otherwise agreed between the supplier and the purchaser, with at least the following information:

- a) the manufacturer's name or trade mark, e.g. XXX;
- b) the reference of this Technical Specification, i.e. ISO/TS 11619:2014;
- c) the outside diameter and wall thickness, e.g. 6 mm × 1 mm;
- d) the maximum working pressure at 23 °C in MPa and bar, e.g. 1,35 MPa (13,5 bar) at 23 °C; and
- e) the quarter and the last two digits of the year of manufacture, e.g. 1Q14.

EXAMPLE XXX/ISO/TS 11619:2014/6 mm × 1 mm/MWP1,35 MPa (13,5 bar) at 23 °C/1Q14

9 Recommendations for packing and storage

The recommendations for packing and storage are given in ISO 8331.

Annex A (normative)

Test frequency

A.1 [Table A.1](#) gives the frequency of testing for routine tests and type tests.

A.2 Type tests are those carried out to verify that the tube meets all the requirements of this Technical Specification.

A.3 Routine tests are those tests to be carried out on every manufactured length of tube.

NOTE This type of tubing is normally produced with continuous outside diameter measurement and also wall thickness gauging.

Table A.1 — Frequency of testing for routine tests and type tests

Test	Routine test	Type test
5.1 Outside diameter	X	X
5.1 Wall thickness	X	X
6.1 Hydrostatic testing at 23 °C	N.A.	X
6.2 Hydrostatic testing at 60 °C	N.A.	X
6.4 Bend radius test	N.A.	X
NOTE N.A. = Not applicable		

Annex B (informative)

Recommended tests for production testing

B.1 [Table B.1](#) gives the recommended tests for production acceptance testing.

B.2 Production tests are those tests to be carried out on a manufactured batch of tubing or sample of tube from a manufactured batch.

B.3 A manufacturing batch is defined as a maximum of 6 000 m of tubing.

Table B.1 — Recommended tests for production acceptance testing

Test	Production test
5.1 Outside diameter	X
5.1 Wall thickness	X
6.1 Hydrostatic testing at 23 °C	X
6.2 Hydrostatic testing at 60 °C	N.A.
6.4 Bend radius test	N.A.
NOTE N.A. = Not applicable	

Bibliography

ISO 14743:2004, *Pneumatic fluid power — Push-in connectors for thermoplastic tubes*¹⁾

1) Under revision.

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™