

PD ISO/TS 16097:2013



BSI Standards Publication

Vulcanized crumb rubber — Evaluation procedures

bsi.

...making excellence a habit.™

National foreword

This Published Document is the UK implementation of ISO/TS 16097:2013.

The UK participation in its preparation was entrusted to Technical Committee PRI/50, Rubber - Raw, natural and synthetic, including latex and carbon black.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2013. Published by BSI Standards Limited 2013

ISBN 978 0 580 80170 9

ICS 83.040.10

Compliance with a British Standard cannot confer immunity from legal obligations.

This Published Document was published under the authority of the Standards Policy and Strategy Committee on 30 September 2013.

Amendments issued since publication

Date	Text affected
------	---------------

TECHNICAL
SPECIFICATION

PD ISO/TS 16097:2013

ISO/TS
16097

First edition
2013-10-01

**Vulcanized crumb rubber —
Evaluation procedures**

Poudrettes de caoutchouc vulcanisées — Méthodes d'évaluation



Reference number
ISO/TS 16097:2013(E)

© ISO 2013



COPYRIGHT PROTECTED DOCUMENT

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Sampling and sample preparation	1
4 Physical and chemical tests on raw vulcanized crumb rubber	1
4.1 Classification	1
4.2 Determination of particle size distribution	2
4.3 Determination of free steel content	2
4.4 Determination of free textile content	2
4.5 Acetone extract	2
4.6 Ash	2
4.7 Carbon black	2
4.8 Rubber content	2
5 Preparation of test mixes for evaluation	2
5.1 Standard test formulation	2
5.2 Procedure	3
6 Evaluation of vulcanization characteristics by a curemeter test	5
6.1 Using an oscillating-disc curemeter	5
6.2 Using a rotorless curemeter	6
7 Evaluation of Mooney viscosity of test mixes	6
8 Evaluation of tensile stress-strain properties of vulcanized test mixes	6
9 Evaluation of Shore hardness of vulcanized test mixes	6
10 Evaluation of tear strength of vulcanized test mixes	6
11 Test report	6
Bibliography	8

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

Vulcanized crumb rubber — Evaluation procedures

1 Scope

This Technical Specification specifies physical and chemical tests, standard test formulations, equipment and processing methods for the vulcanization-characteristics evaluation and the mechanical properties of vulcanized crumb rubber.

It is not aimed to provide specifications or limitations, or whether these vulcanized crumb rubbers may be used.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 34-1:2010, *Rubber, vulcanized or thermoplastic — Determination of tear strength — Part 1: Trouser, angle and crescent test pieces*

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 247:2006, *Rubber — Determination of ash*

ISO 289-1, *Rubber, unvulcanized — Determinations using a shearing-disc viscometer — Part 1: Determination of Mooney viscosity*

ISO 1407:2011, *Rubber — Determination of solvent extract*

ISO 1408, *Rubber — Determination of carbon black content — Pyrolytic and chemical degradation methods*

ISO 2393, *Rubber test mixes — Preparation, mixing and vulcanization — Equipment and procedures*

ISO 3417, *Rubber — Measurement of vulcanization characteristics with the oscillating disc curemeter*

ISO 6502, *Rubber — Guide to the use of curemeters*

ISO 7619-1, *Rubber, vulcanized or thermoplastic — Determination of indentation hardness — Part 1: Durometer method (Shore hardness)*

CEN/TS 14243:2010, *Materials produced from end of life tyres — Specification of categories based on their dimension(s) and impurities and methods for determining their dimension(s) and impurities*

3 Sampling and sample preparation

Take a laboratory sample of approximately 1,5 kg.

4 Physical and chemical tests on raw vulcanized crumb rubber

4.1 Classification

Classify raw vulcanized crumb rubber, based mainly on their dimensions, in accordance with CEN/TS 14243:2010, Clause 4.

4.2 Determination of particle size distribution

Determine the particle size distribution in accordance with CEN/TS 14243:2010, Clauses 5 and 6.

4.3 Determination of free steel content

Determine the free steel content in accordance with CEN/TS 14243:2010, Annex B.

4.4 Determination of free textile content

Determine the free textile content in accordance with CEN/TS 14243:2010, Annex C.

4.5 Acetone extract

Determine the acetone extract in accordance with ISO 1407:2011, methods A or B.

4.6 Ash

Determine the ash in accordance with ISO 247:2006, method A.

4.7 Carbon black

Determine the carbon black content in accordance with ISO 1408.

4.8 Rubber content

Determine the rubber content, R , in percent (%), with the following equation:

$$R = 100 - (a + b + c)$$

where

a is the acetone extract, in percent (%);

b is the ash content, in percent (%);

c is the carbon black content, in percent (%).

5 Preparation of test mixes for evaluation

5.1 Standard test formulation

The standard test formulation is given in [Table 1](#).

The materials used shall be national or international standard reference materials. If no standard reference material is available, the materials to be used shall be agreed between the interested parties.

Table 1 — Standard test formulation

Material	Parts by mass
Natural rubber STR 20 ^a	100,00
Vulcanized crumb rubber	30,00 ^e
Industry reference black ^b	5,00
Stearic acid ^c	2,00
Zinc oxide ^c	3,00
Sulfur ^c	2,25
TBBS ^d	1,00
Total	143,25

^a Standard Thai Rubber 20 was used in the formula standard test for the drafting of this Technical Specification. This information is given for the convenience of users of this document and does not constitute an endorsement by ISO of this product.

^b The current industry reference black shall be used.

^c Powder materials shall be used (standard curing ingredients used in the industry).

^d N-tert-butyl-benzothiazole-2-sulfenamide. This is supplied in powder form having an initial insoluble-matter content, determined in accordance with ISO 11235, of less than 0,3 %. The material shall be stored at room temperature in a closed container and the insoluble matter checked every 6 months. If this is found to exceed 0,75 % the TBBS shall be discarded or recrystallized.

^e 30 parts by mass of vulcanized crumb rubber is the suitable ratio to show the result of crumb rubber, while the short duration for mixing procedure is acquired. And it allows stabilizing the particle size distribution of the crumb.

5.2 Procedure

5.2.1 Equipment and procedure

Equipment and procedure for the preparation, mixing and vulcanization shall be in accordance with ISO 2393.

5.2.2 Mixing procedure - Two stage mixing using an internal mixer for initial mixing and a mill for final mixing

5.2.2.1 Stage 1 - Initial mixing procedure

	Duration min	Cumulative time min
a) Adjust the temperature of the internal mixer to a starting temperature of 50 °C ± 3 °C. Close the discharge door, start the rotor and raise the ram.	0	0
b) Load the rubber, lower the ram and allow the rubber to be masticated.	1,0	1,0
c) Raise the ram and add the zinc oxide and the stearic acid. Lower the ram and allow the batch to be masticated.	0,5	1,5
d) Raise the ram and add the carbon black and the crumb rubber. Lower the ram and allow the batch to be mixed.	0,75	2,25
e) Raise the ram, sweep the mouth of the mixing chamber and lower the ram. Allow the batch to be mixed.	0,5	2,75
Total time (max.)	2,75	
f) Turn off the rotor, raise the ram, remove the mixing chamber and discharge the batch. Record the maximum batch temperature.		
g) Immediately pass the batch four times through a laboratory mill with its mill opening set at 2,5 mm and at a temperature of 50 °C ± 5 °C. Check-weigh the batch (see ISO 2393). If the mass of the batch differs from the theoretical value by more than + 0,5 % or - 1,5 %, discard the batch and re-mix.		
h) Leave the batch for 30 min to 24 h after mixing.		

NOTE Only one mixing procedure is used during initial mixing to get similar result in particle size distribution in various mixes.

5.2.2.2 Stage 2 - Final mill mixing procedure

The standard laboratory-mill batch mass, in grams, shall be based on the recorded batch mass.

Set the mill temperature at 50 °C ± 5 °C and the mill opening to 1,5 mm.

A good rolling bank at the nip of the rolls shall be maintained during mixing. If this is not obtained with the nip settings specified hereunder, small adjustments to the mill openings may be necessary.

	Duration min	Cumulative time min
a) Band the master-batch on the slow roll.	1,0	1,0
b) Add the TBBS. Do not cut the band until the accelerator is completely dispersed.	0,5	1,5
c) Make a 3/4 cut from each side, allowing 15 s between each cut.	0,5	2,0
d) Add the sulfur. Do not cut the band until the powder is completely dispersed.	0,5	2,5
e) Make a 3/4 cut from each side, allowing 15 s between each cut.	0,5	3,0
f) Make three alternating 3/4 cuts from each side, allowing 15 s between each cut.	2,0	5,0
g) Cut the batch from the mill. Set the mill opening at 0,8 mm and pass the rolled batch endwise through the rolls six times, introducing it from each end alternately.	2,0	7,0
Total time (max.)	7,0	
h) Sheet the batch to an approximate thickness of 6 mm and check-weigh the batch (see ISO 2393). If the mass of the batch differs from the theoretical value by more than + 0,5 % or - 1,5 %, discard the batch and re-mix. Remove sufficient material for curemeter testing.		
i) Sheet the batch to approximately 2,2 mm in order to prepare test sheets or to the appropriate thickness in order to prepare ISO rings or dumbbell test pieces in accordance with ISO 37.		
j) After mixing and prior to vulcanization, condition the batch for at least 2 h at room temperature, but not more than 24 h.		

6 Evaluation of vulcanization characteristics by a curemeter test

6.1 Using an oscillating-disc curemeter

Measure the following standard test parameters:

M_L , M_H at defined time, t_{s1} , $t'_c(50)$, $t'_c(90)$, $t'_c(95)$ and $t'_c(99)$

in accordance with ISO 3417, using the following test conditions:

- oscillation frequency: 1,7 Hz (100 cycles per minute);
- amplitude of oscillation: 1° of arc;

An amplitude of oscillation of 3° of arc is permitted as an alternative. If such an amplitude is chosen, measure t_{s2} instead of t_{s1} ;

- selectivity: to be chosen to give at least 75 % of full-scale deflection at M_H ;
- die temperature: 150 °C ± 0,3 °C;
- pre-heat time: none.

6.2 Using a rotorless curemeter

Measure the following standard test parameters:

F_L , F_{max} at defined time, t_{s1} , $t'_c(50)$, $t'_c(90)$, $t'_c(95)$ and $t'_c(99)$

in accordance with ISO 6502, using the following test conditions:

- oscillation frequency: 1,7 Hz (100 cycles per minute);
- amplitude of oscillation: 0,5° of arc;

An amplitude of oscillation of 1° of arc is permitted as an alternative. If such an amplitude is chosen, measure t_{s2} instead of t_{s1} ;

- selectivity: to be chosen to give at least 75 % of full-scale deflection at F_{max} ;
- die temperature: 150 °C ± 0,3 °C;
- pre-heat time: None.

The two types of curemeter may not give identical results.

7 Evaluation of Mooney viscosity of test mixes

Determine the Mooney viscosity in accordance with ISO 289-1.

Record the result as $ML(1'+4')$ at 100 °C.

8 Evaluation of tensile stress-strain properties of vulcanized test mixes

Vulcanize sheets at 150 °C for a period chosen from $t'_c(95)$.

Condition vulcanized sheets for 16 h to 96 h and measure the stress-strain properties in accordance with ISO 37.

9 Evaluation of Shore hardness of vulcanized test mixes

Use vulcanized sheets for the evaluation of tensile stress-strain properties.

Measure the Shore hardness using durometers with the A scale for rubbers in the normal hardness range in accordance with ISO 7619-1.

10 Evaluation of tear strength of vulcanized test mixes

Use vulcanized sheets for the evaluation of tear strength.

Measure the tear strength using an angle test piece without a nick according to method B of ISO 34-1:2010.

11 Test report

The test report shall include the following:

- a) a reference to this Technical Specification;
- b) all details necessary for the identification of the sample;
- c) the reference materials used to prepare the test mix;

- d) the ambient conditions in the laboratory during preparation of the test mix;
- e) the type of curemeter used, the defined time at which was M_H was measured and the amplitude of oscillation used for the curemeter test, as defined in Clause 6;
- f) any unusual features noted during the determination;
- g) details of any operations not included in this International Standard or in the International Standards to which reference is made, as well as of any operation regarded as optional;
- h) the results and the units in which they have been expressed;
- i) the date of the test.

Bibliography

- [1] ISO 11235, *Rubber compounding ingredients — Sulfenamide accelerators — Test methods*
- [2] ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email bsmusales@bsigroup.com.

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Copyright

All the data, software and documentation set out in all British Standards and other BSI publications are the property of and copyrighted by BSI, or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI. Details and advice can be obtained from the Copyright & Licensing Department.

Useful Contacts:

Customer Services

Tel: +44 845 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 845 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com



...making excellence a habit.™