

629-82

4851903 0023412 8

G-26-80

International Standard



629

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

## Steel and cast iron — Determination of manganese content — Spectrophotometric method

*Aciers et fontes — Dosage du manganèse — Méthode spectrophotométrique*

First edition — 1982-11-15

UDC 669.13/.14 : 543.42 : 546.711

Ref. No. ISO 629-1982 (E)

Descriptors : steels, cast iron, chemical analysis, determination of content, spectrophotometric analysis.

Price based on 4 pages

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 629 was developed by Technical Committee ISO/TC 17, *Steel*.

It was submitted directly to the ISO Council, in accordance with clause 5.10.1 of part 1 of the Directives for the technical work of ISO. It cancels and replaces ISO Recommendation R 629-1967, which had been approved by the member bodies of the following countries :

Australia	Hungary	South Africa, Rep. of
Austria	India	Spain
Belgium	Israel	Sweden
Brazil	Italy	Switzerland
Canada	Japan	Turkey
Chile	Korea, Rep. of	United Kingdom
Czechoslovakia	Netherlands	USA
Denmark	New Zealand	USSR
Egypt, Arab Rep. of	Norway	Yugoslavia
France	Poland	
Germany, F. R.	Romania	

The member body of the following country had expressed disapproval of the document on technical grounds :

Portugal

# Steel and cast iron — Determination of manganese content — Spectrophotometric method

## 1 Scope and field of application

This International Standard specifies a spectrophotometric method for the determination of manganese in steel and cast iron.

The method is applicable to products having manganese contents between 0,001 and 4 % (*m/m*).

## 2 Reference

ISO 377/2, *Selection and preparation of samples and test pieces of wrought steels — Part 2 : Samples and test pieces intended for the determination of the chemical composition.*<sup>1)</sup>

## 3 Principle

Dissolution of a test portion in sulphuric-phosphoric acid mixture and nitric acid. Treatment of the test solution with perchloric acid. Formation of the permanganate ion by sodium periodate.

Spectrophotometric measurement of the test solution at wavelength of about 545 nm.

## 4 Reagents

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

NOTE — Verify by blank tests that relevant reagents are free from manganese. Wherever necessary, the results should be corrected accordingly.

### 4.1 Water, free from organic matter.

Bring to the boil water acidified with 10 ml/l of sulphuric acid ( $\rho$  about 1,83 g/ml), add several crystals of sodium periodate ( $\text{NaIO}_4$ ) and keep boiling for 10 min.

### 4.2 Pure iron, free from manganese.

### 4.3 Hydrochloric acid, $\rho$ about 1,19 g/ml.

### 4.4 Nitric acid, $\rho$ about 1,40 g/ml.

### 4.5 Perchloric acid, $\rho$ about 1,67 g/ml.

NOTE — It is also possible to use perchloric acid,  $\rho$  about 1,54 g/ml. 127 ml of perchloric acid,  $\rho$  about 1,54 g/ml is equivalent to 100 ml of perchloric acid, about 1,67 g/ml.

### 4.6 Perchloric acid, diluted 1 + 499.

### 4.7 Sulphuric/phosphoric acid mixture.

To 600 ml of water add in the following order, carefully and stirring at the same time, 100 ml of sulphuric acid ( $\rho$  about 1,83 g/ml) and 150 ml of phosphoric acid ( $\rho$  about 1,71 g/ml). Cool and dilute to 1 000 ml with water.

### 4.8 Sodium periodate, 50 g/l solution.

### 4.9 Manganese, standard solution

#### 4.9.1 Stock solution

Weigh, to the nearest 0,001 g, 2,877 g of potassium permanganate, dissolve in 500 ml of water and add 10 ml sulphuric acid ( $\rho$  about 1,83 g/ml). Decolorize the solution with hydrogen peroxide [about 30 % (*m/m*)] or with a stream of sulphur dioxide. In the latter case, eliminate the excess of reagent by boiling.

After cooling, transfer the solution to a 1 000 ml one-mark volumetric flask, dilute to the mark with water and mix.

1 ml of this stock solution contains 1,00 mg of Mn.

#### 4.9.2 Standard solution A.

Transfer 100 ml of the stock solution (4.9.1) to a 1 000 ml one-mark volumetric flask and dilute to the mark with water and mix.

1 ml of standard solution A contains 0,1 mg of Mn.

#### 4.9.3 Standard solution B.

Transfer 250 ml of the standard solution A (4.9.2) to a 1 000 ml one-mark volumetric flask, dilute to the mark with water and mix.

1 ml of standard solution B contains 0,025 mg of Mn.

1) At present at the stage of draft. (Partial revision of ISO/R 377-1964.)

## 5 Apparatus

Ordinary laboratory apparatus and

### 5.1 Spectrophotometer.

## 6 Sampling

Sampling shall be carried out in accordance with ISO 377/2 or appropriate national standards for cast iron.

## 7 Procedure

**WARNING:** Perchloric acid vapour may cause explosions in the presence of ammonia, nitrous fumes or organic material in general.

### 7.1 Test portion

According to the presumed manganese content, weigh, to the nearest 0,001 g, the following mass (*m*) of the test portion:

- a) for Mn contents less than 0,05 % (*m/m*): *m* approximately 2 g;
- b) for Mn contents between 0,05 and 2 % (*m/m*): *m* approximately 1 g;
- c) for Mn contents greater than 2 % (*m/m*): *m* approximately 0,5 g.

### 7.2 Determination

#### 7.2.1 Preparation of test solution

Place the test portion (7.1) in a 250 ml conical flask, add 50 ml of the sulphuric/phosphoric acid mixture (4.7) and heat gently until effervescence ceases. When the attack is complete, oxidize with a few drops of the nitric acid (4.4) and add 20 ml of the perchloric acid (4.5). Evaporate until white perchloric acid fumes are given off and keep at this temperature for 10 min.

After cooling, take up with water, dilute to 70 to 80 ml and boil. If necessary, filter and wash with the hot perchloric acid (4.6).

Collect the filtrate in a 100 ml one-mark volumetric flask. Dilute to the mark with water and mix. This gives solution S<sub>1</sub>.

NOTE — For samples that do not dissolve readily in the sulphuric/phosphoric acid mixture (4.7), add also 10 ml of the hydrochloric acid (4.3) and 10 ml of the nitric acid (4.4) to facilitate the dissolution.

#### 7.2.2 Formation of coloured compound for test portion

Introduce into a 250 ml conical flask the following quantities of solution S<sub>1</sub>, and reagents specified in table 1, depending on the presumed manganese content.

Bring to the boil, add 10 ml of the sodium periodate solution (4.8), boil for 2 min and maintain at 90 °C for 10 min. Cool to

ambient temperature. Transfer into a 100 ml volumetric flask, dilute to the mark with water (4.1) and mix.

#### 7.2.3 Preparation of the compensation solution

Take the same volumes of solution S<sub>1</sub>, water and sulphuric/phosphoric acid mixture (4.7) as for the formation of the coloured compound for the test portion (7.2.2). Add 2 or 3 drops of the hydrochloric acid (4.3) and boil for several minutes.

After cooling, transfer into a 100 ml one-mark volumetric flask, dilute to the mark with water and mix.

#### 7.2.4 Spectrophotometric measurement

Carry out the spectrophotometric measurements on the test solution (7.2.2), using the spectrophotometer (5.1) at a wavelength about 545 nm, after having adjusted the instrument to zero absorbance against the compensation solution (7.2.3).

#### 7.2.5 Establishment of calibration curve

##### 7.2.5.1 Preparation of reference solutions

###### 7.2.5.1.1 For manganese contents less than 0,05 % (*m/m*)

Weigh, to the nearest 0,001 g, 2,000 g of the pure iron (4.2). Transfer into a series of six 250 ml conical flasks, add 50 ml of the sulphuric/phosphoric acid mixture (4.7) and heat gently until effervescence ceases. When the attack is complete, oxidize with a few drops of the nitric acid (4.4) and add 20 ml of the perchloric acid (4.5). Evaporate until white perchloric acid fumes are given off and keep at this temperature for 10 min.

After cooling, take up with water, dilute to 70 to 80 ml and boil. If necessary, filter and wash with the hot perchloric acid (4.6).

Collect the filtrate in a 100 ml one-mark volumetric flask. After cooling, dilute to the mark with water and mix. This gives solution S<sub>2</sub>.

Introduce into a series of six 250 ml conical flasks the quantities of manganese standard solution B (4.9.3) specified in table 2.

Dilute the above volumes to 25 ml with water, add 40,0 ml of solution S<sub>2</sub> and 5 ml of the sulphuric/phosphoric acid mixture (4.7). Continue in accordance with sub-clause 7.2.2, beginning at "Bring to the boil...".

###### 7.2.5.1.2 For manganese contents between 0,05 and 4 % (*m/m*)

Weigh, to the nearest 0,001 g, approximately 1 g of the pure iron (4.2). Transfer into a 250 ml conical flask, add 50 ml of the sulphuric/phosphoric acid mixture (4.7) and heat gently until effervescence ceases. When the attack is complete, oxidize with a few drops of the nitric acid (4.4) and add 20 ml of the perchloric acid (4.5). Evaporate until white perchloric acid fumes are given off and keep at this temperature for 10 min.

After cooling, take up with water, dilute to 70 to 80 ml and boil. If necessary, filter and wash with the hot perchloric acid (4.6).

Collect the filtrate in a 100 ml conical flask. After cooling, dilute to the mark with water and mix. This gives solution S<sub>3</sub>.

Introduce into a series of six 250 ml conical flasks the quantities of manganese standard solution A (4.9.2) specified in table 3.

Dilute the above volumes to 25 ml with water, add 10 ml of solution S<sub>3</sub> and 20 ml of the sulphuric/phosphoric acid mixture (4.7). Continue in accordance with sub-clause 7.2.2, beginning at "Bring to the boil...".

#### 7.2.5.2 Spectrophotometric measurements

Carry out the spectrophotometric measurements on the

reference solutions (7.2.5.1.1 and 7.2.5.1.2), using the spectrophotometer (5.1) at a wavelength about 545 nm, after having adjusted the instrument to zero absorbance against the reference solution "0".

#### 7.2.5.3 Plotting of calibration curve or calculating of angular coefficient of the straight line

Plot the absorbance against the known mass of manganese, in milligrams, in 100 ml of reference solution.

Calculate the angular coefficient (*a*), the mass, in milligrams, of manganese in 100 ml by absorbance per optical pathlength of 1 cm, from the slope of the calibration curve if it is a straight line.

Table 1 — Dilution guide for test solution

Presumed Mn content % (m/m)	Mass of original test portion g	Volume of solution S <sub>1</sub> ml	Mass of the equivalent test portion g	Volume of water added ml	Volume of sulphuric/ phosphoric acid mixture (4.7) added ml
Less than 0,05	2	40,0	0,80	10	5
0,05 to 0,50	1	40,0	0,40	10	5
0,10 to 1,00	1	20,0	0,20	20	15
0,20 to 2,00	1	10,0	0,10	25	20
0,40 to 4,00	0,5	10,0	0,05	25	20

Table 2 — Preparation guide for reference solution of manganese less than 0,05 % (m/m)

		1	2	3	4	5	6	Flask
Introduce		0	2,0	5,0	10,0	15,0	20,0	ml of standard solution B (4.9.3)
containing		0	0,050	0,125	0,250	0,375	0,500	mg of manganese
corresponding to								
for a test portion of	a test volume of							
2 g	40 ml	0	0,006	0,016	0,031	0,047	0,063	% (m/m) of manganese

Table 3 — Preparation guide for reference solution of manganese between 0,050 and 4 % (m/m)

		1	2	3	4	5	6	Flask
Introduce		0	2,0	5,0	10,0	15,0	20,0	ml of standard solution A (4.9.2)
containing		0	0,20	0,50	1,00	1,50	2,00	mg of manganese
corresponding to								
for a test portion of	a test volume of							
1 g	40 ml	0	0,050	0,125	0,250	0,375	0,500	% (m/m) of manganese
	20 ml	0	0,100	0,250	0,500	0,750	1,000	
	10 ml	0	0,200	0,500	1,000	1,500	2,000	
0,5 g	10 ml	0	0,400	1,000	2,000	3,000	4,000	

## 8 Expression of results

The manganese (Mn) content, as a percentage by mass, is obtained in accordance with the calibration curve or calculated from the formula

$$\begin{aligned} \text{Mn \% (m/m)} &= a \times \frac{D}{d} \times \frac{100}{V} \times \frac{1}{m} \times \frac{1}{10^3} \times 100 \\ &= \frac{a \times D \times 10}{d \times V \times m} \end{aligned}$$

where

$a$  is the angular coefficient, in

$$\frac{\text{mg Mn/100 ml}}{\text{absorbance/cm}}$$

$D$  is the absorbance of the test solution corrected with the absorbance of its compensating solution (7.2.5.3);

$d$  is the optical pathlength, in centimetres, used for the measurement (7.2.4 or 7.2.5.2);

$V$  is the volume, in millilitre, of the test solution used for the determination (7.2.2);

$m$  is the mass, in grams, of the test portion (7.1).

## 9 Test report

The test report shall include the following particulars :

- a) the method used by reference to this International Standard;
- b) the results, and the form in which they are expressed;
- c) any unusual features noted during the determination;
- d) any operation not specified in this International Standard, or any optional operations which may have influenced the result.