
**Heat-treatable steels, alloy steels and
free-cutting steels —**

Part 4:
Free-cutting steels

*Aciers pour traitement thermique, aciers alliés et aciers pour
décolletage —*

Partie 4: Aciers pour décolletage



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification and designation	2
4.1 Classification.....	2
4.2 Designation.....	2
5 Information to be supplied by the purchaser	2
5.1 Mandatory information.....	2
5.2 Options/supplementary or special requirements.....	3
5.3 Ordering example.....	3
6 Manufacturing process	3
6.1 General.....	3
6.2 Heat treatment and surface condition at delivery.....	3
6.2.1 Normal condition at delivery.....	3
6.2.2 Particular heat-treatment condition.....	3
6.3 Traceability of the cast.....	3
7 Requirements	4
7.1 Chemical composition, hardness, and mechanical properties.....	4
7.1.1 General.....	4
7.1.2 Chemical composition.....	4
7.1.3 Mechanical properties.....	4
7.2 Machinability.....	4
7.3 Weldability.....	4
7.4 Grain size.....	4
7.5 Internal soundness.....	4
7.6 Surface quality.....	5
7.7 Shape, dimensions, and tolerances.....	5
8 Inspection	5
8.1 Testing procedures and types of documents.....	5
8.2 Frequency of testing.....	6
8.3 Specific inspection and testing.....	6
8.3.1 Verification of the hardness and mechanical properties.....	6
8.3.2 Visual and dimensional inspection.....	6
9 Test methods	6
9.1 Chemical analysis.....	6
9.2 Hardness and mechanical tests.....	6
9.2.1 Hardness.....	6
9.2.2 Mechanical tests.....	6
9.3 Retests.....	6
10 Marking	7
Annex A (normative) Ruling sections for mechanical properties	14
Annex B (normative) Supplementary or special requirements	17
Annex C (informative) Designation of steels given in this part of ISO 683 and of comparable grades covered in various designation systems	19
Annex D (informative) Dimensional standards applicable to products complying with this part of ISO 683	20
Bibliography	21

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

The committee responsible for this document is ISO/TC 17, *Steel*, Subcommittee SC 4, *Heat treatable and alloy steels*.

This second edition cancels and replaces the first edition (ISO 683-4:2014), of which it constitutes a minor revision.

ISO 683 consists of the following parts, under the general title *Heat-treatable steels, alloy steels and free-cutting steels*:

- *Part 1: Non-alloy steels for quenching and tempering*
- *Part 2: Alloy steels for quenching and tempering*
- *Part 3: Case-hardening steels*
- *Part 4: Free-cutting steels*
- *Part 5: Nitriding steels*
- *Part 14: Hot-rolled steels for quenched and tempered springs*
- *Part 15: Valve steels for internal combustion engines*
- *Part 17: Ball and roller bearing steels*
- *Part 18: Bright steel products*

Heat-treatable steels, alloy steels and free-cutting steels —

Part 4: Free-cutting steels

1 Scope

This part of ISO 683 gives the technical delivery requirements for semi-finished products (e.g. blooms, billets, slabs), bars and wire rod, manufactured from the free-cutting steels listed in [Table 2](#) and supplied in one of the treatment conditions given for the different types of products in [Table 1](#), rows 2 to 4.

This part of ISO 683 covers three groups of free-cutting steels for mechanical purposes as listed in [Table 2](#), namely

- a) not intended for heat treatment,
- b) suitable for case-hardening, and
- c) suitable for quenching and tempering.

Free-cutting steels are often used as bright bars. For these products, refer to ISO 683-18.

In special cases, variations in these technical delivery requirements or additions to them can form the subject of an agreement at the time of enquiry and order (see [5.2](#) and [Annex B](#)).

In addition to this part of ISO 683, the general technical delivery requirements of ISO 404 are applicable.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing*

ISO 404, *Steel and steel products — General technical delivery requirements*

ISO 643, *Steels — Micrographic determination of the apparent grain size*

ISO 4885, *Ferrous products — Heat treatments — Vocabulary*

ISO 4948-1, *Steels — Classification — Part 1: Classification of steels into unalloyed and alloy steels based on chemical composition*

ISO 4948-2, *Steels — Classification — Part 2: Classification of unalloyed and alloy steels according to main quality classes and main property or application characteristics*

ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 6929, *Steel products — Vocabulary*

ISO 9443, *Heat-treatable and alloy steels — Surface quality classes for hot-rolled round bars and wire rods — Technical delivery conditions*

ISO 10474, *Steel and steel products — Inspection documents*

ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition*

ISO/TR 9769, *Steel and iron — Review of available methods of analysis*

ISO/TS 4949, *Steel names based on letter symbols*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 377, ISO 4885, ISO 4948-1, ISO 4948-2, ISO 6929, ISO 14284 and the following apply.

3.1 ruling section

section for which the specified mechanical properties shall apply

Note 1 to entry: Independent of the actual shape and dimensions of the cross-section of the product, the size of its ruling section is always given by a diameter. This corresponds to the diameter of an “equivalent round bar”. That is a round bar which will show the same cooling rate as the actual ruling section of the product concerned at its position for taking the test pieces, when being cooled from austenitizing temperature.

3.2 free-cutting steels

steels characterized by good machinability with high metal removal rate, mostly obtained by higher than normal contents of sulphur

Note 1 to entry: Other elements besides sulfur can be added for further improving the machinability.

4 Classification and designation

4.1 Classification

The classification of the relevant steel grades is allocated in accordance with ISO 4948-1 and ISO 4948-2. All steels covered by this part of ISO 683 are classified as non-alloy quality steels.

4.2 Designation

For the steel grades covered by this part of ISO 683, the steel names given in the relevant tables are allocated in accordance with ISO/TS 4949.

5 Information to be supplied by the purchaser

5.1 Mandatory information

The manufacturer shall obtain the following information from the purchaser at the time of enquiry and order:

- a) the quantity to be delivered;
- b) the designation of the product form (e.g. slab, bloom, billet, round bar, wire rod);
- c) either the designation of the dimensional standard and the dimensions and tolerances selected from this (see [7.7](#)) or the designation of the drawing or any other document, covering the dimensions and tolerances required for the product;
- d) a reference to this part of ISO 683, i.e. ISO 683-4;

- e) the designation of the steel grade given in [Table 2](#);
- f) standard designation for a test report 2.2 or, if required, any other type of inspection document in accordance with ISO 10474.

5.2 Options/supplementary or special requirements

A number of options are specified in this part of ISO 683 and listed below. If the purchaser does not indicate the wish to implement any of these options, the products will be supplied in accordance with the basic specification of this part of ISO 683 (see [5.1](#)).

- a) If a heat-treatment condition other than the untreated condition is required, the symbol for this other condition (see [Table 1](#), column 2).
- b) Any supplementary requirement that shall comply with the symbol and, where necessary, the details of this supplementary requirement (see [Annex B](#)).
- c) Suitability of bars and rod for bright drawing (see [7.6.4](#)).
- d) Any requirement relating to removal of surface defects (see [7.6.5](#)).

5.3 Ordering example

EXAMPLE 50 hot-rolled round bars according to ISO 1035-1, with a nominal diameter of 40 mm and a nominal length of 8 000 mm, with diameter tolerance according to class S and with length tolerance according to ISO 1035-4, class L2, made of steel grade ISO 683-4, 35S20 (see [Table 2](#)) in the heat-treatment condition +U (see [Table 1](#)), product analysis/option (see [B.5](#)) with a test report 2.2 in accordance with ISO 10474.

**50 round bars ISO 1035 – 40,0S × 8 000L2
steel grade ISO 683-4 – 35S20 option B.5
Inspection document ISO 10474 – 2.2**

6 Manufacturing process

6.1 General

The manufacturing process of the steel and of the products is, with the restrictions given by the requirements in [6.2](#) and [6.3](#), left to the discretion of the manufacturer.

For minimum reduction ratio or minimum thickness deformation ratio of rolled and forged products, see [B.6](#).

6.2 Heat treatment and surface condition at delivery

6.2.1 Normal condition at delivery

Unless otherwise agreed at the time of enquiry and order, the products shall be delivered in the untreated condition that means “as hot-worked”.

6.2.2 Particular heat-treatment condition

If so agreed at the time of enquiry and order, the products shall be delivered in one of the particular heat-treatment conditions given in [Table 1](#), rows 3 and 4.

6.3 Traceability of the cast

Each product shall be traceable to the cast (see [Clause 10](#)).

7 Requirements

7.1 Chemical composition, hardness, and mechanical properties

7.1.1 General

[Table 1](#) gives a survey of combinations of usual treatment conditions at delivery, product forms, and requirements according to [Tables 2](#) to [6](#) (chemical composition, maximum hardness, mechanical properties).

7.1.2 Chemical composition

The chemical composition determined by cast analysis shall comply with the values in [Table 2](#).

Permissible deviations between the limiting values for cast analysis and the values for product analysis are given in [Table 3](#).

The product analysis shall be carried out when specified at the time of the enquiry and order (see [B.5](#)).

WARNING — Due to hazardous effects to health and environmental problems of Pb, it is recommended to instead use steels only with sulfur and other innocuous free-cutting element additions.

7.1.3 Mechanical properties

Mechanical properties for free-cutting steels are given in [Tables 4](#) to [6](#).

7.2 Machinability

The steels covered by this part of ISO 683 have good machinability and chip-breaking characteristics. However, the machinability decreases with increasing carbon, silicon and manganese contents, while cold reduction improves the machinability of the steels not intended for heat treatment and steel 10S20.

NOTE Non-leaded steels with comparable chemical composition generally have identical mechanical properties, but often lower machinability than leaded steels.

7.3 Weldability

Because of their high sulfur and phosphorus content, free-cutting steels are normally not recommended for welding.

7.4 Grain size

Unless otherwise agreed at the time of enquiry and order, the grain size shall be left to the discretion of the manufacturer. If a fine grain structure is required for case-hardening steels or steels for quenching and tempering, the special requirement in [B.3](#) shall be ordered.

If direct hardening treatment is used for case-hardening steels, a fine grain structure should be ordered.

7.5 Internal soundness

Where appropriate, requirements relating to the internal soundness of the products shall be agreed at the time of enquiry and order (see [B.4](#)).

7.6 Surface quality

7.6.1 All products shall have a smooth surface finish appropriate to the manufacturing processes applied.

7.6.2 Minor surface imperfections, which can occur under normal manufacturing conditions, such as prints originating from rolled-in scale, are not to be regarded as defects.

7.6.3 Bars and wire rod are delivered with surface class 1za2 according to ISO 9443, unless otherwise agreed at the time of enquiry and order.

It is more difficult to detect and eliminate surface discontinuities in coiled products than in cut lengths. This should be taken into account when agreements on surface quality are made.

7.6.4 If suitability of bars and rod for bright drawing is required, this shall be agreed at the time of enquiry and order.

7.6.5 The removal of surface defects by welding is not permitted.

If surface discontinuities are repaired, the method and maximum depth of removal shall be agreed at the time of enquiry and order.

7.7 Shape, dimensions, and tolerances

The shape, dimensions, and tolerances of the products shall comply with the requirements agreed at the time of enquiry and order. The agreements shall, as much as possible, be based on corresponding International Standards (see [Annex D](#)), or otherwise on suitable national standards.

8 Inspection

8.1 Testing procedures and types of documents

8.1.1 Products complying with this part of ISO 683 shall be ordered and delivered with one of the inspection documents specified in ISO 10474. The type of document shall be agreed upon at the time of enquiry and order. If the order does not contain any specification of this type, a test report 2.2 shall be issued.

8.1.2 If, in accordance with the agreements made at the time of enquiry and order, a test report 2.2 is to be provided, this shall cover the following information:

- a) confirmation that the material complies with the requirements of the order;
- b) results of the cast analysis of the concerned cast for all elements specified in [Table 2](#) for the steel grade.

8.1.3 If in accordance with the agreements in the order an inspection certificate [3.1](#) or [3.2](#) is to be provided, the specific inspections and tests described in [8.2](#), [8.3](#), and [Clause 9](#) shall be carried out and the results shall be confirmed in the inspection certificate.

In addition, the inspection certificate shall cover the following:

- a) confirmation that the material complies with the requirements of the order;
- b) results of the cast analysis of the concerned cast for all elements specified in [Table 2](#) for the steel grade;

- c) the result of all inspections and tests ordered by supplementary requirements (see [Annex B](#));
- d) the symbol letters or numbers relating the inspection certificate, test pieces and products to each other.

8.2 Frequency of testing

The amount of testing, the sampling conditions, and the test methods to be applied for the verification of compliance with the requirements shall be in accordance with the prescriptions of [Table 7](#).

8.3 Specific inspection and testing

8.3.1 Verification of the hardness and mechanical properties

The hardness requirements and/or mechanical properties given for the relevant treatment condition in [Table 1](#), column 6, sub-column 6.2, shall be verified, with the following exception. The requirements given in [Table 1](#), footnote a (mechanical properties of reference test pieces), shall only be verified if the supplementary requirement given in [B.2](#), is ordered.

8.3.2 Visual and dimensional inspection

A sufficient number of products shall be inspected to ensure compliance with the specification.

9 Test methods

9.1 Chemical analysis

The choice of a suitable physical or chemical analytical method for the analysis shall be at the discretion of the manufacturer. In cases of dispute, the method for product analysis used shall be agreed taking into account the relevant existing International Standards.

The list of available International Standards on chemical analysis is given in ISO/TR 9769.

9.2 Hardness and mechanical tests

9.2.1 Hardness

For products in the untreated condition, the hardness shall be measured in accordance with ISO 6506-1.

9.2.2 Mechanical tests

The tensile test shall be carried out in accordance with ISO 6892-1.

For the specified yield strength in the tables of mechanical properties in this part of ISO 683, the upper yield strength (R_{eH}) shall be determined.

If a yield phenomenon is not present, the 0,2 % proof strength ($R_{p0,2}$) shall be determined.

9.3 Retests

Retests for steels for quenching and tempering and criteria are specified in ISO 404.

10 Marking

The manufacturer shall mark the products or the bundles or boxes containing the products in a suitable way, so that the identification of the cast, the steel name, and the origin of the delivery is possible (see [B.7](#)).

Table 1 — Combinations of usual heat-treatment conditions at delivery, product forms, and requirements according to [Tables 2 to 6](#)

	1	2	3	4	5	6		
1	Heat-treatment condition at delivery	Symbol	x = applicable for Semi-finished products Bars Wire rod			6.1	6.2	Applicable requirements
2	Untreated	None or +U	x	x	x	Chemical composition according to Tables 2 and 3	Maximum Brinell hardness or (in the case of dispute) the tensile strength according to Table 4 in the case of steels not intended for heat treatment or Table 5 in the case of case-hardening steels or Table 6 in the case of steels for quenching and tempering ^a	
3	Quenched and tempered	+QT	—	x	—			Mechanical properties according to Table 6 in the case of steels for quenching and tempering
4	Others	Other treatment conditions, for example, the stress relieved condition, can be agreed at the time of enquiry and order.						

^a The mechanical properties specified in [Table 6](#) for the quenched + tempered condition shall be achievable after appropriate heat treatment if so agreed at the time of enquiry and order (see [B.2](#)).

Table 2 — Steel grades and chemical composition (cast analysis)

Steel name	% mass fraction ^a					
	C	Si	Mn	P	S	Pb
Steels not intended for heat treatment						
9S20	0,13	0,05 ^b	0,60 to 1,20	0,11 ^d	0,15 to 0,25	—
11SMn30	0,14	0,05 ^b	0,90 to 1,30	0,11 ^c	0,27 to 0,33	—
11SMnPb30						0,20 to 0,35
11SMn37	0,14	0,05 ^b	1,00 to 1,50	0,11 ^c	0,34 to 0,40	—
11SMnPb37						0,20 to 0,35
Case-hardening steels						
10S20	0,07 to 0,13	0,40	0,70 to 1,10	0,060	0,15 to 0,25	—
10SPb20						0,20 to 0,35

NOTE Elements not quoted shall not be intentionally added to the steel without the agreement of the purchaser, other than for the purpose of finishing the heat. All reasonable precautions shall be taken to prevent the addition of such elements from scrap or other materials used in manufacture which affect the mechanical properties and applicability. However, if agreed, the manufacturer can add elements such as Ca, Se, Te, etc. for the purpose of improving the machinability. These elements have to be reported in the inspection document.

^a Maximum values unless otherwise indicated.

^b Since silicon has an adverse effect on machinability, it is not intentionally added to specified limits, but if the formation of special oxides is guaranteed, a Si-content of 0,10 % to 0,40 % can be agreed.

^c At the time of enquiry and order, it can be agreed that either a grade with 0,06 % to 0,11 % P or a grade with max, 0,05 % P shall be delivered.

Table 2 (continued)

Steel name	% mass fraction ^a					
	C	Si	Mn	P	S	Pb
15SMn13	0,12 to 0,18	0,40	0,90 to 1,30	0,060	0,08 to 0,18	—
17SMn20	0,14 to 0,20	0,40	1,20 to 1,60	0,060	0,15 to 0,25	—
Steels for quenching and tempering						
35S20	0,32 to 0,39	0,40	0,70 to 1,10	0,060	0,15 to 0,25	—
35SPb20						0,15 to 0,35
36SMn14	0,32 to 0,39	0,40	1,30 to 1,70	0,060	0,10 to 0,18	—
36SMnPb14						0,15 to 0,35
35SMn20	0,32 to 0,39	0,40	0,90 to 1,40	0,060	0,15 to 0,25	—
35SMnPb20						0,15 to 0,35
38SMn28	0,35 to 0,40	0,40	1,20 to 1,50	0,060	0,24 to 0,33	—
38SMnPb28						0,15 to 0,35
44SMn28	0,40 to 0,48	0,40	1,30 to 1,70	0,060	0,24 to 0,33	—
44SMnPb28						0,15 to 0,35
46S20	0,42 to 0,50	0,40	0,70 to 1,10	0,060	0,15 to 0,25	—
46SPb20						0,15 to 0,35
<p>NOTE Elements not quoted shall not be intentionally added to the steel without the agreement of the purchaser, other than for the purpose of finishing the heat. All reasonable precautions shall be taken to prevent the addition of such elements from scrap or other materials used in manufacture which affect the mechanical properties and applicability. However, if agreed, the manufacturer can add elements such as Ca, Se, Te, etc. for the purpose of improving the machinability. These elements have to be reported in the inspection document.</p> <p>^a Maximum values unless otherwise indicated.</p> <p>^b Since silicon has an adverse effect on machinability, it is not intentionally added to specified limits, but if the formation of special oxides is guaranteed, a Si-content of 0,10 % to 0,40 % can be agreed.</p> <p>^c At the time of enquiry and order, it can be agreed that either a grade with 0,06 % to 0,11 % P or a grade with max, 0,05 % P shall be delivered.</p>						

Table 3 — Permissible deviations between the product analysis and the limiting values for the cast analysis

Element	Permissible maximum content according to cast analysis	Permissible deviations ^a
	% mass fraction	% mass fraction
C	≤0,30	±0,02
	0,30 < C ≤ 0,50	±0,03
Si	≤0,05	±0,01
	0,05 < Si ≤ 0,40	±0,03
Mn	≤1,00	±0,04
	1,00 < Mn ≤ 1,70	±0,06
P	≤0,06	±0,008
	0,06 < P ≤ 0,11	±0,02
S	≤0,33	±0,03
	0,33 < S ≤ 0,40	±0,04
Pb	≤0,35	+0,03 -0,02
	<p>^a ± means that, in one cast, the deviation can occur over the upper value or under the lower value of the specified range in this table, but not both at the same time.</p>	

Table 4 — Mechanical properties of free-cutting steels not intended for heat treatment

Steel name ^b	Diameter mm	Hardness ^a HBW max.	Untreated
			Tensile strength R_m MPa
9S20	$d \leq 16$	154	330 to 520
	$16 < d \leq 40$	154	330 to 520
	$40 < d \leq 63$	154	320 to 520
	$63 < d \leq 100$	140	310 to 470
11SMn30	$5 \leq d \leq 10$	169	380 to 570
11SMnPb30	$10 < d \leq 16$	169	380 to 570
	$16 < d \leq 40$	169	380 to 570
11SMn37	$40 < d \leq 63$	169	370 to 570
11SMnPb37	$63 < d \leq 100$	154	360 to 520

^a In cases of dispute, the tensile strength values are the decisive factor.

^b In this table, grades alloyed with further elements for better machinability are not explicitly mentioned, but the mechanical properties are also valid for them (see [Table 2](#)).

Table 5 — Mechanical properties of case-hardening free-cutting steels

Steel name ^b	Diameter mm	Hardness ^a HBW max	Untreated
			Tensile strength R_m MPa
10S20 10SPb20	$5 \leq d \leq 10$	156	360 to 530
	$10 < d \leq 16$	156	360 to 530
	$16 < d \leq 40$	156	360 to 530
	$40 < d \leq 63$	156	360 to 530
	$63 < d \leq 100$	146	350 to 490
15SMn13	$5 \leq d \leq 10$	181	430 to 610
	$10 < d \leq 16$	178	430 to 600
	$16 < d \leq 40$	178	430 to 600
	$40 < d \leq 63$	172	430 to 580
	$63 < d \leq 100$	160	420 to 540
17SMn20	$5 \leq d \leq 10$	181	430 to 610
	$10 < d \leq 16$	178	430 to 600
	$16 < d \leq 40$	178	430 to 600
	$40 < d \leq 63$	172	430 to 580
	$63 < d \leq 100$	160	420 to 540

^a In cases of dispute, the tensile strength values are the decisive factor.

^b In this table, grades alloyed with further elements for better machinability are not explicitly mentioned, but the mechanical properties are also valid for them (see [Table 2](#)).

Table 6 — Mechanical properties of free-cutting steels for quenching and tempering

Steel name ^b	Diameter mm	Untreated		Quenched and tempered		
		Hardness ^a HBW max.	Tensile strength R_m MPa	Tensile properties		
				R_e min MPa	R_m MPa	A min %
35S20 35SPb20	$5 \leq d \leq 10$	210	550 to 720	430	630 to 780	15
	$10 < d \leq 16$	204	550 to 700	430	630 to 780	15
	$16 < d \leq 40$	198	520 to 680	380	600 to 750	16
	$40 < d \leq 63$	196	520 to 670	320	550 to 700	17
	$63 < d \leq 100$	190	500 to 650	320	550 to 700	17
36SMn14 36SMnPb14	$5 \leq d \leq 10$	225	580 to 770	480	700 to 850	14
	$10 < d \leq 16$	225	580 to 770	460	700 to 850	14
	$16 < d \leq 40$	219	560 to 750	420	670 to 820	15
	$40 < d \leq 63$	216	560 to 740	400	640 to 790	16
	$63 < d \leq 100$	216	550 to 740	360	570 to 720	17
35SMn20 35SMnPb20	$5 \leq d \leq 10$	225	580 to 770	—	—	—
	$10 < d \leq 16$	225	580 to 770	420	620 to 820	14
	$16 < d \leq 40$	219	560 to 750	365	590 to 790	16
	$40 < d \leq 63$	216	560 to 740	335	540 to 740	17
	$63 < d \leq 100$	216	550 to 740	—	—	—
38SMn28 38SMnPb28	$5 \leq d \leq 10$	228	580 to 780	480	700 to 850	15
	$10 < d \leq 16$	219	580 to 750	460	700 to 850	15
	$16 < d \leq 40$	213	560 to 730	420	700 to 850	15
	$40 < d \leq 63$	213	560 to 730	400	700 to 850	16
	$63 < d \leq 100$	204	550 to 700	380	630 to 800	16
44SMn28 44SMnPb28	$5 \leq d \leq 10$	(266)	630 to 900	520	700 to 850	16
	$10 < d \leq 16$	(252)	630 to 850	480	700 to 850	16
	$16 < d \leq 40$	241	630 to 820	420	700 to 850	16
	$40 < d \leq 63$	231	620 to 790	410	700 to 850	16
	$63 < d \leq 100$	228	610 to 780	400	700 to 850	16
46S20 46SPb20	$5 \leq d \leq 10$	234	590 to 800	490	700 to 850	12
	$10 < d \leq 16$	228	590 to 780	490	700 to 850	12
	$16 < d \leq 40$	222	590 to 760	430	650 to 800	13
	$40 < d \leq 63$	213	580 to 730	370	630 to 780	14
	$63 < d \leq 100$	207	560 to 710	370	630 to 780	14

^a In cases of dispute, the tensile strength values are the decisive factor.

^b In this table, grades alloyed with further elements for better machinability are not explicitly mentioned, but the mechanical properties are also valid for them (see [Table 2](#)).

Table 7 — Test conditions for verification of compliance with the various requirements

	1		2	3	4	5	6
No.	Requirements		Amount of testing			Sampling ^b	Test method
		See tables	Test unit ^a	Sample products per test unit	Tests per sample product		
1	Chemical composition	Tables 2 and 3	C	(The cast analysis is given by the manufacturer; for product analysis, see B.5)			
2	Hardness in the untreated condition (as rolled)	Tables 4, 5, and 6	C + D	1	1	The hardness shall be measured, if possible, at the circumference of the product at a distance of 1 × diameter from one end and, in cases of products with square or rectangular cross-section, at a distance of 0,25 × w (width of the product) from one longitudinal edge. In cases of dispute, the tensile test is to be done.	According to ISO 6506-1
3	Mechanical properties of products in the untreated or quenched and tempered condition	Tables 4, 5, and 6	C + D + T	1 ^c	1	The test pieces for the tensile test shall be taken in accordance with Figure 1 .	The tensile test shall be carried out in accordance with ISO 6892-1 on proportional test pieces having a gauge length of $L_0 = 5,65 \sqrt{S_0}$ (S_0 = area of the cross-section of the test piece.)

NOTE Verification of the requirements is only necessary if an inspection certificate is ordered.

^a The tests shall be carried out separately for each cast as indicated by “C”, each dimension as indicated by “D”, and each heat-treatment batch as indicated by “T”.

Products with different thicknesses can be grouped if the thicknesses lie in the same dimensional range for mechanical properties and if the differences in thickness do not affect the properties. In case of doubt, the thinnest and the thickest product shall be tested.

^b The general conditions for selection and preparation of test samples and test pieces shall be in accordance with ISO 377 and ISO 14284.

^c If the products are continuously heat treated, one sample product shall be taken for each 25 t or part, thereof, but at least one sample product for each cast.


Table 8 — Conditions for heat treatment of case-hardening free-cutting steels^a

Steel name ^e	Carburizing temperature ^b °C	Direct and simple hardening temperature °C	Double hardening		Quenching agent	Tempering ^d °C
			Core-hardening temperature °C	Case-hardening temperature °C		
10S20 10SPb20 15SMn13 17SMn20	880 to 980	830 to 870	880 to 920	780 to 820	Water, oil, emulsion ^c	150 to 200
<p>^a The temperatures given for carburizing, direct and simple hardening, core hardening, case hardening, and tempering are for guidance; the actual temperatures chosen shall be those that will give the properties required.</p> <p>^b The carburizing temperature will depend on the chemical composition of the steel, the mass of the product, and the carburizing medium. If the steels are direct hardened, in general a temperature of 950 °C is not exceeded. For special procedures, for example under vacuum, higher temperatures, for example 1 020 °C to 1 050 °C, are not unusual.</p> <p>^c The kind of quenching agent depends, for example, on the shape of the products, the cooling conditions and the quantity of furnace filling.</p> <p>^d Time for tempering as a guide: 1 h minimum.</p> <p>^e In this table, grades alloyed with further elements for better machinability are not explicitly mentioned, but the heat-treatment conditions are also valid for them (see Table 2).</p>						


Table 9 — Conditions for heat treatment of free-cutting steels for quenching and tempering^a

Steel name ^d	Quenching ^b		Tempering ^c °C
	°C	Medium	
35S20 35SPb20	860 to 890	Water or oil	540 to 680
36SMn14 36SMnPb14 35SMn20 35SMnPb20 38SMn28 38SMnPb28	850 to 880	Water or oil	540 to 680
44SMn28 44SMnPb28 46S20 46SPb20	840 to 870	Water or oil	540 to 680
<p>^a The temperature are for guidance, but the actual temperatures chosen shall be those that will give the properties required.</p> <p>^b Time for austenitizing as a guide: 0,5 h minimum.</p> <p>^c Time for tempering as a guide: 1 h minimum.</p> <p>^d In this table, grades alloyed with further elements for better machinability are not explicitly mentioned, but the heat-treatment conditions are also valid for them (see Table 2).</p>			

Dimensions in millimetres



a) Round and similar shaped sections



b) Rectangular and square sections

Key

- 1 tensile test piece
- 2 sample
- 3 rough specimen
- 4 test piece
- a For small products (d or $w \leq 25$ mm), the test piece shall, if possible, consist of an un-machined part of the bar.

Figure 1 — Location of the test pieces in bars and rods

Annex A (normative)

Ruling sections for mechanical properties

A.1 Definition

See [3.1](#).

A.2 Determination of the diameter of the equivalent ruling section


A.2.1 If the test pieces are taken from products with simple cross-sections and from positions with quasi two-dimensional heat flow, [A.2.1.1](#) to [A.2.1.3](#) shall apply.

A.2.1.1 For rounds, the nominal diameter of the product (not comprising the machining allowance) shall be taken as the diameter of the ruling section.

A.2.1.2 For hexagons and octagons, the nominal distance between two opposite sides of the cross-section shall be taken as the diameter of the ruling section.

A.2.1.3 For square and rectangular bars, the diameter of the ruling section shall be determined in accordance with the example shown in [Figure A.1](#).

Dimensions in millimetres

**Key**

- X width
- Y thickness
- 1 diameter of the ruling cross-section


EXAMPLE For a rectangular bar with a section of 40 mm × 60 mm, the diameter of the ruling section is 50 mm.

Figure A.1 — Diameter of the equivalent ruling section for square and rectangular sections for quenching in oil or water

A.2.2 For other product forms, the ruling section shall be agreed at the time of enquiry and order.

NOTE For this purpose, the following procedure can serve as a guideline. The product is hardened in accordance with usual practice. It is then cut so that the hardness and structure at the position of the ruling section provided for taking test pieces can be determined. From another product of the type under consideration and of the same cast, an end-quench piece is taken from the prescribed position and tested in the usual way. Then, the distance is determined at which the end-quench test piece shows the same hardness and structure as the ruling section at the position provided for taking test pieces. On the basis of this distance, the diameter of the ruling section is then estimated using [Figures A.2](#) and [A.3](#).

Dimensions in millimetres




Key

- X distance from the quenched end
- Y bar diameter
- 1 surface
- 2 3/4 radius
- 3 centre

NOTE Source: Reference [10].

Figure A.2 — Relationship between the cooling rates in end-quench test pieces (Jominy test pieces) and in quenched round bars in mildly agitated water

Dimensions in millimetres



Key

- X distance from the quenched end
- Y bar diameter
- 1 surface
- 2 3/4 radius
- 3 centre

NOTE Source: Reference [10].

Figure A.3 — Relationship between the cooling rates in end-quench test pieces (Jominy test pieces) and in quenched round bars in mildly agitated oil

Annex B (normative)

Supplementary or special requirements

B.1 General

One or more of the following supplementary or special requirements shall be applied, but only when specified in the enquiry and order. Details of these requirements shall, where necessary, be agreed upon by the manufacturer and purchaser at the time of enquiry and order.

B.2 Mechanical properties of reference test pieces in the quenched and tempered condition

For deliveries of steels for quenching and tempering, in a condition other than quenched and tempered, the requirements for the mechanical properties in the quenched and tempered condition (see [Table 6](#)) shall be verified on a reference test piece.

In the case of bars and wire rods, the sample to be quenched and tempered shall, unless otherwise agreed, have the cross-section of the product. In all other cases, the dimensions and the manufacture of the sample shall be agreed at the time of enquiry and order, where appropriate, taking into consideration the indications for the determination of the ruling section given in [Annex A](#). The samples shall be quenched and tempered in accordance with the conditions given in [Table 9](#) or as agreed at the time of enquiry and order. The details of the heat treatment shall be given in the document. Unless otherwise agreed, the test pieces shall be taken in accordance with the relevant specifications of this part of ISO 683.

B.3 Fine grain steel

When tested in accordance with ISO 643, the steel shall have an austenite grain size of 5 or finer. If specific testing is ordered, the grain size requirement is to be verified by determining the aluminium content or micrographically. In the case of determining the grain size by the aluminium content for case hardening steels, Al min is 0,018 % and for steels for quenching and tempering, Al min is 0,007 %. The Al-content shall be given in the inspection document. For micrographical test according to ISO 643 for case hardening steels, see ISO 683-3, and for steels for quenching and tempering, see ISO 683-1.

B.4 Non-destructive tests

The products shall be non-destructively tested under conditions and according to an acceptance standard agreed at the time of enquiry and order.

B.5 Product analysis

One product analysis shall be carried out per cast for the determination of all elements for which values are specified for the cast analysis of the steel type concerned.

The conditions for sampling shall be in accordance with ISO 14284. In cases of dispute, the analysis shall be carried out, if possible, according to the appropriate internationally standardized method.

B.6 Reduction ratio and deformation ratio

If the central soundness of the hot-rolled or forged products is important, the purchaser must be aware that a minimum reduction ratio (referred to the cross-section) for long products, or a minimum thickness deformation ratio (referred to the thickness) for flat products, is necessary. In this case, a minimum reduction ratio or a minimum thickness deformation ratio of, for example, 4:1, can be agreed at the time of enquiry and order.

B.7 Special agreements for marking

The products shall be marked in a way that is specially agreed at the time of enquiry and order.

Annex C (informative)

Designation of steels given in this part of ISO 683 and of comparable grades covered in various designation systems

Table C.1 — Designation of steels given in this part of ISO 683 and of comparable grades covered in various designation systems

Steel designations according to ^a										
ISO name (ISO 683-4)	ISO number (ISO 683-4)	SAE ^b		EN 10087 number ^c			JIS ^d		GB/T 8731-2008 ^e	
			i/n/w ^f			i/n/w ^f		i/n/w ^f		i/n/w ^f
Steels not intended for heat treatment										
9S20	—	—	—	—	—	—	SUM21	n	Y08	w
11SMn30	—	SAE 1215	n	11SMn30	1,0715	I	SUM22	n	Y15	n
11SMnPb30	—	SAE 12L15	n	11SMnPb30	1,0718	I	SUM22L	n	Y15Pb	n
11SMn37	—	—	—	11SMn37	1,0736	I	—	—	—	—
11SMnPb37	—	—	—	11SMnPb37	1,0737	I	—	—	—	—
Case-hardening steels										
10S20	—	—	—	10S20	1,0721	I	—	—	Y12	n
10SPb20	—	—	—	10SPb20	1,0722	I	—	—	Y12Pb	w
15SMn13	—	—	—	15SMn13	1,0725	i	—	—	—	—
17SMn20	—	—	—	—	—	—	—	—	—	—
Steels for quenching and tempering										
35S20	—	—	—	35S20	1,0726	I	—	—	Y30	w
35SPb20	—	—	—	35SPb20	1,0756	I	—	—	—	—
36SMn14	—	SAE 1137	n	36SMn14	1,0764	I	SUM41	n	—	—
36SMnPb14	—	SAE 11L37	n	36SMnPb14	1,0765	i	—	—	—	—
35SMn20	—	—	—	—	—	—	—	—	Y40Mn	n
35SMnPb20	—	—	—	—	—	—	—	—	—	—
38SMn28	—	—	—	38SMn28	1,0760	I	—	—	—	—
38SMnPb28	—	—	—	38SMnPb28	1,0761	I	—	—	—	—
44SMn28	—	SAE 1144	n	44SMn28	1,0762	I	SUM43	n	Y45Mn	w
44SMnPb28	—	SAE 11L44	n	44SMnPb28	1,0763	I	—	—	Y45MnSPb	n
46S20	—	—	—	46S20	1,0727	I	—	—	Y45	i
46SPb20	—	—	—	46SPb20	1,0757	i	—	—	—	—
^a See sources in the Bibliography. ^b SAE steel listed in SAE standard. ^c European steel listed in EN 10087 and in the “Stahl-Eisen-Liste”. If the steel number is given in brackets, then the steel is only listed in the “Stahl-Eisen-Liste”. ^d Japanese Industrial Standard. ^e Chinese National Standard. ^f I = identical steel to ISO-steel grade, n = steel grade with closer match of composition, but not identical, w = wider match.										

Annex D
(informative)

**Dimensional standards applicable to products complying with this
part of ISO 683**

- a) ISO 1035-1, *Hot-rolled steel bars — Part 1: Dimensions of round bars*
- b) ISO 1035-2, *Hot-rolled steel bars — Part 2: Dimensions of square bars*
- c) ISO 1035-3, *Hot-rolled steel bars — Part 3: Dimensions of flat bars*
- d) ISO 1035-4, *Hot-rolled steel bars — Part 4: Tolerances*
- e) ISO 16124, *Steel wire rod — Dimensions and tolerances*

Bibliography

- [1] ISO 683-1, *Heat-treatable steels, alloy steels and free-cutting steels — Part 1: Non-alloy steels for quenching and tempering*
- [2] ISO 683-2, *Heat-treatable steels, alloy steels and free-cutting steels — Part 2: Alloy steels for quenching and tempering*
- [3] ISO 683-3, *Heat-treatable steels, alloy steels and free-cutting steels — Part 3: Case-hardening steels*
- [4] ISO 683-17, *Heat-treated steels, alloy steels and free-cutting steels — Part 17: Ball and roller bearing steels*
- [5] ISO 683-18, *Heat-treatable steels, alloy steels and free-cutting steels — Part 18: Bright steel products*
- [6] ISO 2938, *Hollow steel bars for machining*
- [7] ISO 4954, *Steels for cold heading and cold extruding*
- [8] EN 10087, *Free cutting steels. Technical delivery conditions for semi-finished products, hot rolled bars and rods*
- [9] GB/T 8731-2008, *Free-cutting steels — Technical requirements*
- [10] SAE J406c, *Methods of Determining Hardenability of Steels*

