

INTERNATIONAL STANDARD

ISO 1138

Second edition
2007-02-15

AMENDMENT 1
2012-04-15

Rubber compounding ingredients — Carbon black — Determination of sulfur content

Amendment 1: Clarification of digestion temperature in Subclause 3.4.5

*Ingrédients de mélange du caoutchouc — Noir de carbone — Dosage
du soufre total*

*Amendement 1: Clarification concernant la température de macération
au Paragraphe 3.4.5*



Reference number
ISO 1138:2007/Amd.1:2012(E)

© ISO 2012

ISO 1138:2007/Amd.1:2012(E)



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 1138:2007 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

Rubber compounding ingredients — Carbon black — Determination of sulfur content

Amendment 1: Clarification of digestion temperature in Subclause 3.4.5

Page 2, Subclause 3.4.5

In the fourth line of the subclause, replace “Digest the mixture on an electric hot-plate at low temperature” by “Digest the mixture on an electric hot-plate at moderate temperature, i.e. below the boiling point”, so that the subclause reads as follows:

3.4.5 Open the bomb and wash all the inner surfaces of the bomb with water, collecting all the washings in a 250 ml beaker. Filter the solution into a 400 ml beaker, washing the filter paper with three 5 ml portions of water. Add 5 ml of the hydrochloric acid (3.2.2), 5 ml of the saturated picric acid solution (3.2.3) and 10 ml of the barium chloride solution (3.2.1) to the filtrate. Digest the mixture on an electric hot-plate at moderate temperature, i.e. below the boiling point, for approximately 15 min. Filter through a low-ash paper and wash the precipitate in the paper with 10 ml portions of boiling water. Continue washing until a test with silver nitrate shows absence of chloride in the filtrate.

ISO 1138:2007/Amd.1:2012(E)

ICS 83.040.20

Price based on 1 page