

---

---

**Plastics — Polyamide (PA) moulding and  
extrusion materials —**

**Part 1:  
Designation system and basis for  
specification**

*Plastiques — Matériaux polyamides (PA) pour moulage et extrusion —  
Partie 1: Système de désignation et base de spécification*



Reference number  
ISO 1874-1:2010(E)

© ISO 2010

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Designation system</b> .....	<b>2</b>
<b>3.1 General</b> .....	<b>2</b>
<b>3.2 Data block 1</b> .....	<b>2</b>
<b>3.3 Data block 2</b> .....	<b>5</b>
<b>3.4 Data block 3</b> .....	<b>5</b>
<b>3.5 Data block 4</b> .....	<b>8</b>
<b>3.6 Data block 5</b> .....	<b>9</b>
<b>4 Examples of designations</b> .....	<b>9</b>
<b>4.1 Designation only</b> .....	<b>9</b>
<b>4.2 Designation transformed into a specification</b> .....	<b>11</b>
<b>Annex A (normative) Definition and designation of polyamides</b> .....	<b>13</b>
<b>Bibliography</b> .....	<b>15</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 1874-1 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This third edition cancels and replaces the second edition (ISO 1874-1:1992), which has been technically revised.

ISO 1874 consists of the following parts, under the general title *Plastics — Polyamide (PA) moulding and extrusion materials*:

- *Part 1: Designation system and basis for specifications*
- *Part 2: Preparation of test specimens and determination of properties*

# Plastics — Polyamide (PA) moulding and extrusion materials —

## Part 1: Designation system and basis for specification

### 1 Scope

This part of ISO 1874 establishes a system of designation for polyamide (PA) thermoplastic materials, which may be used as the basis for specifications.

It covers polyamide homopolymers for moulding and extrusion based on PA 6, PA 66, PA 69, PA 610, PA 612, PA 11, PA 12, PA MXD6, PA 46, PA 1212, PA 4T, PA 6T and PA 9T and copolyamides of various compositions for moulding and extrusion.

The types of polyamide plastic are differentiated from each other by a classification system based on appropriate levels of the designatory properties

- a) viscosity number,
- b) tensile modulus of elasticity and
- c) presence of nucleating agent,

and on information about chemical structure, intended application, method of processing, important properties, additives, colour, fillers and reinforcing materials.

The designation system is applicable to all polyamide homopolymers and copolymers. It applies to materials ready for normal use, unmodified and modified by colorants, additives, fillers, reinforcing materials, polymer modifiers, etc.

This part of ISO 1874 does not apply to monomer casting-type polyamides of PA 6 and PA 12.

It is not intended to imply that materials having the same designation give necessarily the same performance. This part of ISO 1874 does not provide engineering data, performance data or data on processing conditions which may be required to specify a material for a particular application and/or method of processing. If such additional properties are required, they shall be determined in accordance with the test methods specified in ISO 1874-2, if suitable.

In order to specify a thermoplastic material for a particular application or reproducible processing, additional requirements may be given in data block 5 (see 3.1 and 3.6).

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 307, *Plastics — Polyamides — Determination of viscosity number*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 1874-2, *Plastics — Polyamide (PA) moulding and extrusion materials — Part 2: Preparation of test specimens and determination of properties*

### 3 Designation system

#### 3.1 General

The designation system for thermoplastics is based on the following standardized pattern:

Designation						
Description block (optional)	Identity block					
	International Standard number block	Individual-item block				
		Data block 1	Data block 2	Data block 3	Data block 4	Data block 5

The designation consists of an optional description block, reading “Thermoplastics”, and an identity block comprising the International Standard number and an individual-item block. For unambiguous designation, the individual-item block is subdivided into five data blocks comprising the following information:

- Data block 1: Identification of the plastic by its abbreviated term (PA), and information about the chemical structure and composition (see 3.2).
- Data block 2: Position 1: Intended application and/or method of processing (see 3.3).  
Positions 2 to 8: Important properties, additives and supplementary information (see 3.3).
- Data block 3: Designatory properties (see 3.4).
- Data block 4: Fillers or reinforcing materials and their nominal content (see 3.5).
- Data block 5: For the purpose of specifications, a fifth data block containing additional information may be added (see 3.6). The kind of information and the code-letters used are not the subject of this part of ISO 1874.

The first character of the individual-item block shall be a hyphen.

The five data blocks shall be separated from each other by a comma.

If a data block is not used, this shall be indicated by doubling the separation sign, i.e. by two commas (,,).

#### 3.2 Data block 1

In this data block, after the hyphen, the polyamide (PA) is identified by using the symbols listed in Tables 1 and 2.

Polyamides containing a plasticizer may be designated by adding the letter P after the symbol, separated from it by a hyphen (e.g. PA 610-P).

Polyamides containing an impact modifier may be designated by adding the letters HI after the symbol, separated from it by a hyphen (e.g. PA 6-HI).

Table 1 — Symbols indicating the chemical structure of polyamide materials in data block 1

Symbol	Name and chemical structure
PA 4T	Polyamide 4T: homopolymer based on tetramethylenediamine and terephthalic acid
PA 6	Polyamide 6: homopolymer based on $\epsilon$ -caprolactam
PA 66	Polyamide 66: homopolymer based on hexamethylenediamine and adipic acid
PA 69	Polyamide 69: homopolymer based on hexamethylenediamine and azelaic acid
PA 610	Polyamide 610: homopolymer based on hexamethylenediamine and sebacic acid
PA 612	Polyamide 612: homopolymer based on hexamethylenediamine and dodecanedioic acid <sup>a</sup>
PA 6T	Polyamide 6T: homopolymer based on hexamethylenediamine and terephthalic acid
PA 9T	Polyamide 9T: homopolymer based on nonamethylenediamine and terephthalic acid
PA 11	Polyamide 11: homopolymer based on 11-aminoundecanoic acid
PA 12	Polyamide 12: homopolymer based on $\omega$ -aminododecanoic acid or on lauro lactam
PA MXD6	Polyamide MXD6: homopolymer based on <i>m</i> -xylylenediamine and adipic acid
PA 46	Polyamide 46: homopolymer based on tetramethylenediamine and adipic acid
PA 1212	Polyamide 1212: homopolymer based on dodecanediamine and dodecanedioic acid <sup>a</sup>
<sup>a</sup> 1,10-Decanedicarboxylic acid.	

**Table 2 — Symbols indicating the chemical structure of copolyamide materials in data block 1 (examples)**

Symbol	Chemical structure
<b>PA 66/610</b>	Polyamide copolymers based on hexamethylenediamine, adipic acid and sebacic acid
<b>PA 6/12</b>	Polyamide copolymers based on $\epsilon$ -caprolactam and lauro lactam
<b>PA 6/66/PACM 6</b>	Polyamide ternary copolymers based on $\epsilon$ -caprolactam, hexamethylenediamine, adipic acid, bis( <i>p</i> -aminocyclohexyl)methane and adipic acid
<b>PA 12/IPDI</b>	Polyamide copolymers based on lauro lactam, isophoronediamine and isophthalic acid
<b>PA 46/6</b>	Polyamide copolymers based on tetramethylenediamine, adipic acid and $\epsilon$ -caprolactam
<b>PA 4T/6T</b>	Polyamide copolymers based on tetramethylenediamine, terephthalic acid and hexamethylenediamine
<b>PA 6T/MPMDT<sup>a</sup></b>	Polyamide copolymers based on hexamethylenediamine, terephthalic acid and methylpentamethylenediamine
<b>PA 6T/66<sup>a</sup></b>	Polyamide copolymers based on hexamethylenediamine, terephthalic acid and adipic acid
<b>PA 6T/6I<sup>a</sup></b>	Polyamide copolymers based on hexamethylenediamine, terephthalic acid and isophthalic acid
<b>PA 6T/6I/66<sup>a</sup></b>	Polyamide copolymers based on hexamethylenediamine, terephthalic acid, isophthalic acid and adipic acid
<b>PA 66/6I</b>	Polyamide copolymers based on hexamethylenediamine, adipic acid and isophthalic acid
<b>PA NDT/INDT</b>	Polyamide copolymers based on 1,6-diamino-2,2,4-trimethylenehexane, 1,6-diamino-2,4,4-trimethylenehexane and terephthalic acid
<b>PA 12/IPDI</b>	Polyamide copolymers based on lauro lactam, isophoronediamine and isophthalic acid
The following three symbols include an indication of the mass content ratio (see Annex A).	
<b>PA 66/6 (90/10)</b>	Polyamide copolymers based on 90 % (by mass) of hexamethylenediamine and adipic acid and 10 % (by mass) of $\epsilon$ -caprolactam
<b>PA 6/66 (80/20)</b>	Polyamide copolymers based on 80 % (by mass) of $\epsilon$ -caprolactam and 20 % (by mass) of hexamethylenediamine and adipic acid
<b>PA 66/6 (20/80)</b>	Polyamide copolymers based on 20 % (by mass) of hexamethylenediamine and adipic acid and 80 % (by mass) of $\epsilon$ -caprolactam
<sup>a</sup> Polyamides designated PA 6T/XX/YY may also be called polyphthalamides (PPAs) provided the residues of terephthalic acid or isophthalic acid or the combination of the two make up at least 55 mole percent of the dicarboxylic acid portion of the repeating structural units of the polymer chain (ASTM D5336).	



### 3.3 Data block 2

In this data block, information about the intended application or method of processing is given in position 1 and information about important properties, additives and colorants in positions 2 to 8. The code-letters used are specified in Table 3.

If information is presented in positions 2 to 8 and no specific information is given in position 1, the letter X shall be inserted in position 1.

**Table 3 — Code-letters used in data block 2**

Code-letter	Position 1	Positions 2 to 8
A		Processing stabilized
B	Blow moulding	Antiblocking
C1		Coloured but transparent
C2		Coloured and non-transparent
D		Powder; dry blend
E	Extrusion of pipes, profiles and sheets	Expandable
F	Extrusion of film and thin sheeting	Special burning characteristics
G	General use	Pellets; granules
H	Coating	Heat-ageing stabilized
K	Cable and wire coating	
L	Monofilament extrusion	Light and/or weather stabilized
M	Injection moulding	
N		Natural (not coloured)
R	Rotational moulding	Moulding release agent
S	Powder coating or sintering	Lubricated
T	Tape manufacture	Improved transparency
W		Stabilized against hydrolysis
X	No indication	
Z		Antistatic

### 3.4 Data block 3

#### 3.4.1 General

In this data block, the viscosity number is represented by a two-figure code-number (see 3.4.2) and the tensile modulus of elasticity by a three-figure code-number (see 3.4.3). The two code-numbers are separated from each other by a hyphen.

Nucleated polyamides are designated by adding a hyphen followed by the letter N at the very last position in data block 3.

If no specific information is given in one of the positions, the letter X shall be inserted.

If a property value falls on or near a range limit, the manufacturer shall state which range will designate the material. If subsequent individual test values lie on, or either side of, the range limit because of manufacturing tolerances, the designation is not affected.

NOTE Not all combinations of the values of the designatory properties are provided by currently available materials.

3.4.2 Viscosity number

The viscosity number shall be determined in accordance with ISO 307, using the solvent specified in Table 4. The average value of the viscosity number is represented by a two-figure code-number as specified in Table 4.

For copolyamides, 96% (by mass) sulfuric acid should preferably be used as solvent, but some copolyamides dissolve better in *m*-cresol or phenol/1,1,2,2-tetrachloroethane (60%/40%). Information concerning the most suitable solvent can be obtained from the suppliers of copolyamides and homopolyamides which are not covered in the last column of Table 4.

Table 4 — Code-numbers used for viscosity number in data block 3

Code-number	Range of viscosity number ml/g			Applicable to
	Solvent: 96 % (by mass) sulfuric acid	Solvent: <i>m</i> -cresol	Solvent: phenol/1,1,2,2- tetrachloroethane (60%/40%)	
09	≤ 90			PA 6, PA 66, PA 69, PA 610, PA 612, PA MXD6 and copolyamides
10	> 90 but ≤ 110			
12	> 110 but ≤ 130			
14	> 130 but ≤ 160			
18	> 160 but ≤ 200			
22	> 200 but ≤ 240			
27	> 240 but ≤ 290			
32	> 290 but ≤ 340			
34	> 340			
11		≤ 110		PA 1212, PA 11, PA 12 and copolyamides
12		> 110 but ≤ 130		
14		> 130 but ≤ 150		
16		> 150 but ≤ 170		
18		> 170 but ≤ 200		
22		> 200 but ≤ 240		
24		> 240		
12			≤ 120	PA 6T/66, PA 6I/66, PA 6I/6T, PA 6T/6I/66, PA 6T/6I, PA 6I/6T/66 and copolyamides
13			> 120 but ≤ 140	
15			> 140 but ≤ 160	
17			> 160 but ≤ 180	
19			> 180 but ≤ 200	
20			> 200	

NOTE Viscosity numbers determined with 90 % (by mass) formic acid as solvent can be converted into viscosity numbers determined in 96 % (by mass) sulfuric acid using the following equations (see ISO 307:2007, Clause 13 and Annex E):

$$\text{For PA 6: } \ln y = 0,416\ 1 + 0,927\ 6 \ln x$$

$$\text{For PA 66: } \ln y = 0,454\ 1 + 0,926\ 1 \ln x$$

$$\text{For PA 69: } \ln y = 0,463\ 4 + 0,909\ 5 \ln x$$

$$\text{For PA 610: } \ln y = 0,982\ 3 + 0,793\ 2 \ln x$$

where

$x$  is the viscosity number in 90 % (by mass) formic acid;

$y$  is the viscosity number in 96 % (by mass) sulfuric acid.

For the viscosity number of PA 612, which may be determined in accordance with ISO 307 in either *m*-cresol or 96 % (by mass) sulfuric acid, the following conversion formula applies:

$$\ln y = 0,285\ 7 + 0,985\ 9 \ln x$$

where

$x$  is the viscosity number in 96 % (by mass) sulfuric acid;

$y$  is the viscosity number in *m*-cresol.

The above conversion formulae were calculated from the results of an interlaboratory investigation carried out in 1982. The accuracy of the conversions depends on both the size of the viscosity number and the type of PA, the latter resulting from the fact that different numbers of the different PA types were included in the investigation. The 95 % confidence intervals for the values of the nominal viscosity number in 96 % (by mass) sulfuric acid, converted from different values of the nominal viscosity number in the other solvent, are given in Table 5.

Table 5 — Confidence intervals

Nominal viscosity number <sup>a</sup>	95 % confidence intervals for converted nominal viscosity numbers in 96% (by mass) sulfuric acid				
	PA 6	PA 66	PA 69	PA 610	PA 612
100	±0,8	±1,6	±2,0	±4,7	±4,4
140	±0,8	±1,4	±1,9	±4,1	±4,9
180	±0,7	±1,2	±2,9	±5,8	±10,2
220	±0,7	±1,3	±4,7	±9,0	±17,6
260	±0,8	±1,7	±6,9	±12,9	±26,0
300	±1,0	±2,4	±9,3	±17,2	±35,3
340	±1,3	±3,3	±11,9	±21,8	±45,3

<sup>a</sup> Solvents: 90 % (by mass) formic acid for PA 6, PA 66, PA 69 and PA 610; *m*-cresol for PA 612.

### 3.4.3 Tensile modulus of elasticity

The tensile modulus of elasticity shall be determined in the dry state in accordance with ISO 527-2 under the test conditions specified in ISO 1874-2. The average value of the tensile modulus of elasticity is represented by a three-figure code-number as specified in Table 6.

Table 6 — Code-numbers used for tensile modulus of elasticity in data block 3

Code-number	Range of tensile modulus of elasticity
	MPa
001	≤ 150
002	> 150 but ≤ 250
003	> 250 but ≤ 350
004	> 350 but ≤ 450
005	> 450 but ≤ 600
007	> 600 but ≤ 800
010	> 800 but ≤ 1 500
020	> 1 500 but ≤ 2 500
030	> 2 500 but ≤ 3 500
040	> 3 500 but ≤ 4 500
050	> 4 500 but ≤ 5 500
060	> 5 500 but ≤ 6 500
070	> 6 500 but ≤ 7 500
080	> 7 500 but ≤ 8 500
090	> 8 500 but ≤ 9 500
100	> 9 500 but ≤ 10 500
110	> 10 500 but ≤ 11 500
120	> 11 500 but ≤ 13 000
140	> 13 000 but ≤ 15 000
160	> 15 000 but ≤ 17 000
190	> 17 000 but ≤ 20 000
220	> 20 000 but ≤ 23 000
250	> 23 000

### 3.5 Data block 4

In this data block, the type of filler or reinforcing material is represented by one code-letter in position 1 and its physical form by a second code-letter in position 2. Subsequently (without a space), the mass content may be given by a two-figure code-number in positions 3 and 4.

Mixtures of materials or forms may be indicated in parentheses by combining the relevant codes using the sign "+". For example, a mixture of 25 % (by mass) of glass fibre (GF) and 10 % (by mass) of mineral powder (MD) would be indicated by (GF25+MD10).

Table 7 — Code-letters used for fillers and reinforcing materials in data block 4

Code-letter	Material (position 1)	Form (position 2)
<b>B</b>	Boron	Balls; beads; spheres  Powder; dry blend Fibre Granules; ground Whiskers
<b>C</b>	Carbon <sup>a</sup>	
<b>D</b>		
<b>F</b>		
<b>G</b>	Glass	
<b>H</b>		
<b>K</b>	Chalk (CaCO <sub>3</sub> )	
<b>M</b>	Mineral <sup>a</sup> ; metal <sup>b</sup>	
<b>S</b>	Organic; synthetic <sup>a</sup>	
<b>T</b>	Talcum	
<b>X</b>	Not specified	Not specified
<b>Z</b>	Others <sup>a</sup>	Others

<sup>a</sup> These materials may be defined after position 4 of the data block, e.g. by chemical symbol or additional codes to be agreed upon.

<sup>b</sup> Metal fillers shall be identified by the chemical symbol (in capital letters) after the mass content. For example, steel whiskers may be designated "MH05FE".

### 3.6 Data block 5


Indication of additional requirements in optional data block 5 is a way of transforming the designation of a material into a specification for a particular application. This may be done for example by reference to a suitable national standard or to a standard-like, generally established specification (see 4.2).

## 4 Examples of designations

### 4.1 Designation only


**4.1.1** A polyamide material (PA 6) for injection moulding (M), with moulding release agent (R), having a viscosity of 150 ml/g (14) and a tensile modulus of elasticity of 2 700 MPa (030), and with a nucleating additive (N), would be designated:

**ISO 1874-1:2010(E)**




**Designation:** ISO 1874-PA 6,MR,14-030-N,,

**4.1.2** A polyamide material (PA 66) for injection moulding (M), with special burning characteristics (F) and a heat-ageing stabilizer (H), having a viscosity number of 140 ml/g (14) and a tensile modulus of elasticity of 10 200 MPa (100), and reinforced with 37 % of glass fibre (GF), would be designated:



**Designation:** ISO 1874-PA 66,MFH,14-100-X,GF37

**4.1.3** A polyamide material containing plasticizer (PA 12-P), for extrusion (E), with a heat-ageing stabilizer (H) and a light and weather stabilizer (L), and having a viscosity number of 210 ml/g (22) and a tensile modulus of elasticity of 280 MPa (003), would be designated:




**Designation:** ISO 1874-PA 12-P,EHL,22-003-X,,

## 4.2 Designation transformed into a specification


**4.2.1** This subclause provides examples of how to use the designation system to convert a designation into a specification. When used to provide a designation, the system only employs information from data blocks 1 to 4. When converting the designation into a specification, the system also includes information from data block 5.

**4.2.2** A polyamide material (PA 6) for injection moulding (M), containing a heat-ageing stabilizer (H), having a viscosity of 150 ml/g (14) and a tensile modulus of elasticity of 2 200 MPa (020), and meeting the requirements of ASTM D6779, would have the specification:



**Specification:** ISO 1874-PA 6,MH,14-020-X,,ASTM D6779 PA 0213

4.2.3 A polyamide material (PA 6T/6I) for injection moulding (M), with special burning characteristics (F), having a tensile modulus of elasticity of 8 000 MPa (080), reinforced with 33 % of glass fibre (GF), and meeting the requirements of ASTM D5336 PPA 0121FL34, would have the specification:



**Specification:** ISO 1874-PA 6T/6I,MF,X-080-X,GF33,ASTM D5336 PPA 0121FL34



## Annex A (normative)

### Definition and designation of polyamides

Polyamides are thermoplastic materials that contain carboxylic amide groups,  $-\text{CONH}-$ , at regular intervals in the linear polymer chain.

Polyamide homopolymers can be built up from a single starting material (an aminocarboxylic acid or its lactam); in this case, they are designated by a number corresponding to the number of carbon atoms in the starting material (see Table A.1).

**Table A.1 — Designation of linear aliphatic polyamides of the general formula  $-\text{[NH}-(\text{CH}_2)_x-\text{CO}]_n-$**

Symbol	Value of $x$	Number of C-atoms in the starting material
PA 6	5	6
PA 11	10	11
PA 12	11	12

However, polyamide homopolymers can also be built up from a starting material with amino groups plus another starting material with carboxylic acid groups. These polyamides, based on diamines and dicarboxylic acids, are designated by a two-digit, three-digit or four-digit number. In the case of the four-digit number, the first digit (or the first and second digits) corresponds to the number of C-atoms in the linear aliphatic diamine and the second digit (or, with some materials, the second and third or the third and fourth digits) corresponds to the number of C-atoms in the linear aliphatic dicarboxylic acid (see Table A.2).

**Table A.2 — Designation of linear aliphatic polyamides of the general formula  $-\text{[NH}-(\text{CH}_2)_x-\text{NH-CO}-(\text{CH}_2)_y-\text{CO}]_{n/2}-$**

Symbol	Value of	
	$x$	$y$
PA 46	4	4
PA 66	6	4
PA 610	6	8
PA 612	6	10
PA 1212	12	10

Copolymer polyamides, also called copolyamides, can be built up from various starting materials (lactams, aminocarboxylic acids, or equimolar amounts of diamines and dicarboxylic acids). These copolyamides are designated by PA plus numbers representing the components of the copolyamide, the numbers being separated by an oblique stroke. But copolyamides with the same numbers or symbols can give quite different properties, depending on the ratio of the starting materials. Therefore, if there is a need for a more exact designation, the mass content ratio shall be included. If it is necessary to indicate this ratio, the two figures, separated by an oblique stroke, are placed in parentheses at the end of the designation (see Table 2).

Starting materials (monomers) for copolyamides, as well as for homopolyamides, include not only linear aliphatic compounds, but also branched aliphatic-aromatic, cycloaliphatic and aromatic compounds. The

monomer units of these non-linear compounds can be derived from the substances listed, together with their designations, in Table A.3. Because of the large number of possible combinations of monomer units in copolyamides, only a few examples have been listed in Table 2.

**Table A.3 — Symbols of aromatic and non-linear aliphatic monomer units**

Symbol of monomer unit <sup>a</sup>	Monomer unit derived from
<b>T</b>	Terephthalic acid (CAS No. 100-21-0)
<b>I</b>	Isophthalic acid (CAS No. 121-95-5)
<b>N</b>	2,6-Naphthalenedicarboxylic acid (CAS No. 1141-38-4)
<b>PACP</b>	2,2-Bis( <i>p</i> -aminocyclohexyl)propane (CAS No. 3377-24-0)
<b>MACM</b>	3,3'-Dimethyl-4,4'-diaminodicyclohexylmethane (CAS No. 6864-37-5)
<b>PACM</b>	Bis( <i>p</i> -aminocyclohexyl)methane (CAS No. 1761-71-3)
<b>IPD</b>	Isophoronediamine (CAS No. 2855-13-2)
<b>ND</b>	1,6-Diamino-2,2,4-trimethylhexane (CAS No. 3236-53-1)
<b>IND</b>	1,6-Diamino-2,4,4-trimethylhexane (CAS No. 3236-54-2)
<b>PPGD</b>	Polypropylene glycoldiamine (CAS No. 9046-10-0)
<b>PBGD</b>	Polybutylene glycol diamine (CAS No. 27417-83-0)
<b>MXD</b>	<i>m</i> -Xylylenediamine (CAS No. 1477-55-0)
<b>PTD</b>	<i>p</i> -Toluylenediamine (CAS No. 95-70-5)
<b>MTD</b>	<i>m</i> -Toluylenediamine (CAS No. 95-80-7)
<b>PABM</b>	Diphenylmethane-4,4'-diamine (CAS No. 101-77-9)
<b>MC</b>	1,3-Bis(aminomethyl)cyclohexane (CAS No. 2579-20-6)
<b>MPMD</b>	Methylpentamethylenediamine
<b>X</b>	Unspecified diamine

<sup>a</sup> The designations ND and IND are derived from the chemical names nonyldiamine and isononyldiamine to avoid having to include numbers in the designations.

## Bibliography

- [1] ISO 1043-2, *Plastics — Symbols and abbreviated terms — Part 2: Fillers and reinforcing materials*
- [2] ASTM D5336, *Standard Specification for Polyphthalamide (PPA) Injection Molding Materials*
- [3] ASTM D6779, *Standard Classification System for Polyamide Molding and Extrusion Materials (PA)*

© ISO 2010. All rights reserved.

---

---

**ICS 83.080.20**

Price based on 15 pages