
**Rubber, vulcanized or thermoplastic —
Determination of density**

AMENDMENT 1: Precision data

*Caoutchouc vulcanisé ou thermoplastique — Détermination de la
masse volumique*

AMENDEMENT 1: Données de fidélité



Reference number
ISO 2781:2008/Amd.1:2010(E)

© ISO 2010

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 2781:2008 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

Rubber, vulcanized or thermoplastic — Determination of density —

AMENDMENT 1: Precision data

Page 5

At the end of Clause 11, add the following new Clause 12:

“12 Precision

See Annex A.”

Renumber the old Clause 12 as Clause 13.

At the end of the text

Add the following annex:

Annex A (informative)

Precision

A.1 Background

An interlaboratory test programme (ITP) for the determination of the precision of the density measurement method specified in this International Standard was conducted in 2008 using the precision procedures and guidelines described in ISO/TR 9272:2005, *Rubber and rubber products — Determination of precision for test method standards*.

A.2 Details of ITP

A.2.1 A total of 15 laboratories participated in the ITP. However, test results were reported by only 13 of the laboratories. A total of four materials or compounds were used, designated compounds A, B, C and D in increasing magnitude of density from 0,97 to 1,86. The ITP was conducted over a period of four sequential weeks. On a specified day in each of these four weeks, five individual density measurements were made by each laboratory on each of the four materials. A test result was taken as the mean of the five individual measurements. The analysis of the data was conducted on the basis of these test results.

A.2.2 Two separate determinations of repeatability and reproducibility were conducted. The results from weeks 1 and 2 were used for repeatability and reproducibility evaluation No. 1 (i.e. these results were obtained by the typical day 1 vs day 2 test protocol specified in ISO/TR 9272). The results of weeks 3 and 4 were used in the same way for repeatability and reproducibility evaluation No. 2. The ISO/TR 9272:2005 option 1 outlier deletion procedure was used.

A.2.3 The precision results as determined by this ITP may not be applied to acceptance or rejection testing of any group of materials or products without documentation stating that the results of this precision evaluation actually apply to the products or materials tested.

A.3 Precision results

A.3.1 The precision results are given in Table A.1. General statements for the use of the precision results are also given. The results listed in Table A.1 are the mean results for evaluations 1 and 2 as indicated above (i.e. for all four weeks). These are given in terms of both the absolute precision, r and R , and the relative precision, (r) and (R) .

A.3.2 *Repeatability*: The repeatability, or local domain precision, of the test method has been established for each material as the values given in Table A.1. Two individual test results (obtained by the proper use of this International Standard) that differ by more than the tabulated values of r , in measurement units, or (r) , in percent, should be considered suspect, i.e. to have come from different populations. Such a decision suggests that appropriate investigative action be taken.

A.3.3 *Reproducibility*: The reproducibility, or global domain precision, for the test method has been established for each material as the values given in Table A.1. Two individual test results obtained in different laboratories (by the proper use of this International Standard) that differ by more than the tabulated values of R , in measurement units, or (R) , in percent, should be considered suspect, i.e. to have come from different populations. Such a decision suggests that appropriate investigative action be taken.

Table A.1 — Precision results (type 1 precision)

Compound	Mean density	Within laboratory			Between laboratories			Number of laboratories ^a
		s_r	r	(r)	s_R	R	(R)	
A	0,966	0,001 86	0,005 21	0,54	0,002 47	0,006 91	0,72	10
B	1,223	0,001 19	0,003 34	0,27	0,001 8	0,005 04	0,41	12
C	1,366	0,000 93	0,002 61	0,19	0,002 02	0,005 65	0,41	11
D	1,857	0,001 16	0,003 25	0,17	0,002 15	0,006 02	0,32	11
Average value ^b		0,001 05	0,002 93	0,18	0,002 08	0,005 84	0,37	
Notation used: s_r is the within-laboratory standard deviation (in measurement units); s_R is the between-laboratory standard deviation (in measurement units); r is the repeatability (in measurement units); (r) is the repeatability (as a percentage of the mean value); R is the reproducibility (in measurement units); (R) is the reproducibility (as a percentage of the mean value).								
^a Number of laboratories after outliers deleted (total number of laboratories in ITP: 13).								
^b Simple averages calculated.								

A.4 Additional comments

The absolute repeatability and reproducibility, r and R , values are essentially constant over the density range of 0,97 to 1,86. This results in a slight decrease in relative precision, (r) and (R), over this range. Consult Table A.1 for the actual values.

A.5 Bias

Bias is the difference between a measured average test result and a reference or true value for the measurement in question. Reference values do not exist for this test method and therefore bias cannot be determined.

ICS 83.060

Price based on 3 pages