



INTERNATIONAL STANDARD ISO 3521:1997
TECHNICAL CORRIGENDUM 1

Published 2003-02-15

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Plastics — Unsaturated polyester and epoxy resins — Determination of overall volume shrinkage

TECHNICAL CORRIGENDUM 1

Plastiques — Résines d'époxydes et de polyesters non saturés — Détermination du retrait global en volume
RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to ISO 3521:1997 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 12, *Thermosetting materials*

Page 1

Clause 4

Replace the equation

$$\text{Overall volume shrinkage} = \frac{\text{Uncured specific gravity} - \text{Cured specific gravity}}{\text{Uncured specific gravity}} \times 100$$

by

$$\text{Overall volume shrinkage} = \frac{\text{Cured specific gravity} - \text{Uncured specific gravity}}{\text{Cured specific gravity}} \times 100$$

Page 5

Subclause 7.4

Replace the formula

$$\frac{\rho_c - \rho_0}{\rho_0} \times 100$$

by

$$\frac{\rho_c - \rho_0}{\rho_c} \times 100$$