INTERNATIONAL STANDARD

ISO 3547-4

Third edition 2017-02

Plain bearings — Wrapped bushes —

Part 4: **Materials**

Paliers lisses — Bagues roulées — Partie 4: Matériaux





COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Ch. de Blandonnet 8 • CP 401 CH-1214 Vernier, Geneva, Switzerland Tel. +41 22 749 01 11 Fax +41 22 749 09 47 copyright@iso.org www.iso.org

Coı	ntent	ts	Page		
Fore	word		iv		
1	Scop	pe	1		
2	Nori	mative references	1		
3	Terms and definitions				
4	4.1	luirements Chemical analysis Hardness values	1		
Rihl	ingranl	ahv	5		

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 3, *Dimensions, tolerances and construction details*.

This third edition cancels and replaces the second edition (ISO 3547-4:2006), which has been technically revised.

A list of all the parts in the ISO 3547 series can be found on the ISO website.

Plain bearings — Wrapped bushes —

Part 4:

Materials

1 Scope

This document gives specifications for solid and multi-layer bearing materials, such as those used for wrapped bushes in accordance with the other parts of ISO 3547.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3547-1:—1), Plain bearings — Wrapped bushes — Part 1: Dimensions

ISO 4378-1, Plain bearings — Terms, definitions, classification and symbols — Part 1: Design, bearing materials and their properties

ISO 4378-4, Plain bearings — Terms, definitions, classification and symbols — Part 4: Basic symbols

ISO 4382-2, Plain bearings — Copper alloys — Part 2: Wrought copper alloys for solid plain bearings

ISO 4383, Plain bearings — Multilayer materials for thin-walled plain bearings

ISO 4384-1, Plain bearings — Hardness testing of bearing metals — Part 1: Multilayer bearings materials

ISO 4384-2, Plain bearings — Hardness testing of bearing metals — Part 2: Solid materials

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4378-1 and ISO 4378-4 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at http://www.iso.org/obp
- IEC Electropedia: available at http://www.electropedia.org/

4 Requirements

4.1 Chemical analysis

Chemical analysis shall be definitive for the acceptance of the bearing metals. Arbitrary analyses or random sampling operations shall be performed in accordance with recognized methods and agreed between the supplier and user.

¹⁾ Under preparation. Stage at the time of publication: ISO/DIS 3547-1:2016.

4.2 Hardness values

The hardness values indicated in $\underline{\text{Tables 1}}$ and $\underline{\text{2}}$ are typical for each of the materials concerned. In practice, composition and processing variables can result in significant variations in hardness. Hardness specifications shall be agreed between the supplier and user.

Table 1 — Solid materials

Key	Designation ^a	Hardness ^b (guide values) HB 2,5/62,5/10	Notes related to application	Wall thickness tolerance series ^c
Z1	Steel (hardened)	_	Suitable for secondary applications with lightly loaded sliding characteristics.	Α
Y1		120	Very high load capacity, good antifrictional property, e.g. for vehicles, transmissions, conveyor systems and agricultural machinery.	A, C, W
Y2	CuSn8P	150		
W1	CuZn31Si	110	High load capacity, good antifrictional properties, e.g. for textile machinery, motor vehicles and agricultural machinery and lifts.	
W2		140		

^a Steel composition shall be agreed between the supplier and user. It will normally have a carbon content of less than 0,25 %; composition of bearing material in accordance with ISO 4382-2.

b Hardness testing in accordance with ISO 4384-2.

In accordance with ISO 3547-1:—, Tables 5 and 6.

Table 2 — Multi-layer materials

Vov	D	esignation ^a	Hardness ^b (guide values)		Nata valetad ta avuliantian	a
Key	Backing material	Bearing material	Backing material ^c	Bearing material	Notes related to application	d
Т2	Steel	SnSb8Cu4	130	17 HV to 24 HV	Very good emergency running characteristics, fair load capacity, e.g. for pumps, compressors, automatic transmissions, starters and camshafts.	
S1	Steel	CuPb24Sn (cast)	125	55 HB to 80 HB	High load capacity, with hard-	
S2	Steel	CuPb24Sn (sinter)	125	40 HB to 60 HB	ened shafts being necessary as a rule, e.g. for automatic transmissions, steering assemblies, camshafts and pumps.	
S3	Steel	CuPb24Sn4 (cast)	125	60 HB to 90 HB	As for the material with keys	
S4	Steel	CuPb24Sn4 (sinter)	125	45 HB to 90 HB	S1 and S2; more suitable for the embossing of grooves. Very high	
S5	Steel	CuPb10Sn10 (cast)	125	70 HB to 130 HB	load capacity, with hardened	
S6	Steel	CuPb10Sn10 (sinter)	125	60 HB to 90 HB	shafts being necessary as a rule, e.g. for gudgeon pins and rocker arm bearings, transmission shafts, steering assemblies and pumps. Available with greater Brinell hardness for special applications.	
S7	Steel	CuSn6P	125	100 HV to 160 HV	High load capacity, e.g. for small end bushes of connecting rod and for joint parts which are vibrated.	
R1	Steel	AlSn6Cu	170	35 HB to 45 HB	High load capacity, with hard- ened shafts being necessary as a rule, e.g. for transmissions and hydraulic pumps.	
R2	Steel	AlSn20Cu	170	30 HB to 40 HB	Good emergency running characteristics, fair load capacity, e.g. for refrigeration plant, compressors and pumps.	
R3	Steel	AlSn12SiCu	170	40 HB to 60 HB	High load capacity, good seizure resistance, e.g. for transmissions camshafts and hydraulic pumps.	A, C, W
R4	Steel	AlZn5	185 HB	60 HB to 100 HB	Higher load capacity.	
P1	Steel	YAZ: LI.	140		Low friction; for vehicle suspen-	
B1	Bronze	With porous sintered bronze, filler and surface coating (running-in coating) of PTFE with additives.	100	_	sion struts, gear levers, pivot bearings, pumps and lifting magnets; operating range from – 200 °C to + 280 °C, but not suitable for machining in the bearing bore; suitable for use as a dry bearing material.	В
P2	Steel		140		High load capacity, greased on	
B2	Bronze	With porous sintered bronze coated with thermoplastic.	100	_	assembly, e.g. for cranes, hoists, lifts, packaging machinery and agricultural machinery, some temperature limitation.	D, E

Table 2 (continued)

Key	D	esignation ^a	Hardness ^b (guide values)		Notes related to application	d
	Backing material	Bearing material	Backing material ^c	Bearing material	Notes related to application	u
D1	Steel	With directly bond- ed polymer bearing lining, e.g. PTFE.	140	_	For specific applications where special properties are required, e.g. limited space, corrosion resistance.	В
D2	Stainless steel		140			
D3	Bronze		100			
D4	Alumini- um alloy		60			

The materials S1 to S6 and R1 may be supplied with an additional running-in coating, for series A and W only, by agreement with the supplier.

- Steel composition shall be agreed between the supplier and user. It will normally have a carbon content of less than 0,25 %; composition of bearing material in accordance with ISO 4383.
- b Hardness testing in accordance with ISO 4384-1.
- Hardness for steel and stainless steel HB1/30/10.
 - Hardness for bronze and aluminium alloy HB1/5/30.
- d Wall thickness limit deviation series (in accordance with ISO 3547-1:—, Tables 5 and 6).
- $^{\rm e}$ Temperature limitation for continuous duty depends on the type of thermoplastic, e.g. POM: 90 °C; PVDF: 110 °C; PEEK: 250 °C.

Bibliography

- [1] ISO 683-3, Heat-treatable steels, alloy steels and free-cutting steels Part 3: Case-hardening steels
- [2] ISO 3547-2, Plain bearings Wrapped bushes Part 2: Test data for outside and inside diameters
- [3] ISO 3547-3, Plain bearings Wrapped bushes Part 3: Lubrication holes, grooves and indentations
- [4] ISO 6932, Cold-reduced carbon steel strip with a maximum carbon content of 0,25 %

