
**Rigid cellular plastics — Determination of
the volume percentage of open cells and of
closed cells**

*Plastiques alvéolaires rigides — Détermination du pourcentage volumique
de cellules ouvertes et de cellules fermées*



Reference number
ISO 4590:2002(E)

© ISO 2002

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2002

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative reference	1
3 Terms and definitions	1
4 Principle.....	2
5 Test specimens.....	3
6 Conditioning and test atmospheres	3
7 Measurement of surface area S and geometrical volume V_g	3
8 Determination of impenetrable volume V_i by method 1: Pressure variation (pycnometer).....	5
9 Determination of impenetrable volume V_i by method 2: Volume expansion	9
10 Correction for specimen surface cells opened during specimen preparation	13
11 Expression of results	14
12 Precision and accuracy.....	14
13 Test report	15
Annex A (normative) Notes on procedure.....	16

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4590 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 10, *Cellular plastics*.

This second edition cancels and replaces the first edition (ISO 4590:1981), which has been technically revised.

Annex A forms a normative part of this International Standard.

Rigid cellular plastics — Determination of the volume percentage of open cells and of closed cells

1 Scope

This International Standard specifies a general procedure for the determination of the volume percentage of open and of closed cells of rigid cellular plastics, by measurement first of the geometrical volume and then of the air-impenetrable volume of test specimens. The procedure includes the correction of the apparent open-cell volume by taking into account the surface cells opened by cutting during specimen preparation. Two alternative methods (method 1 and method 2), and corresponding apparatus, are specified for the measurement of the impenetrable volume. The results obtained from method 2 (see clause 9) are intended to be used for comparison purposes only.

2 Normative reference

The following normative document contains provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent edition of the normative document indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 1923:1981, *Cellular plastics and rubbers — Determination of linear dimensions*

3 Terms and definitions

For the purposes of this International Standard, the following terms and definitions apply.

3.1

surface area

S

the total surface area of the test specimen determined by measuring its geometrical dimensions

3.2

geometrical volume

V_g

the volume of the test specimen determined by measuring its geometrical dimensions

3.3

surface/volume ratio

r

the ratio $\frac{S}{V_g}$ for the test specimen

3.4
impenetrable volume

V_i
the volume of the test specimen into which air cannot penetrate and from which gas cannot escape, under the test conditions

3.5
apparent volume percentage of open cells

ω_r
the ratio

$$\frac{V_g - V_i}{V_g} \times 100$$

NOTE It includes the volume of the cells opened during cutting of the test specimen, and depends on the nature of the cellular plastic under test and on the surface/volume ratio r of the test specimen.

3.6
corrected volume percentage of open cells

ω_0
the apparent volume percentage of cells ω_r , corrected to take into account the surface cells opened by cutting during preparation of the test specimen

NOTE It is the limit of the apparent volume percentage of open cells ω_r , as the surface/volume ratio r approaches zero.

3.7
corrected volume percentage of closed cells

ψ_0
the volume percentage remaining after accounting for the corrected volume percentage of open cells

$$\psi_0 = 100 - \omega_0$$

NOTE This percentage includes the volume of the cell walls.

4 Principle

The surface area S and geometrical volume V_g of a number of test specimens, each having a different geometrical surface/volume ratio r , is determined.

The impenetrable volume V_i is determined by either of two methods, namely:

- a) method 1 — by pressure variation (pycnometer);
- b) method 2 — by volume expansion.

The determination of the impenetrable volume V_i is based on the application of the Boyle-Mariotte law to a gas confined in an indeformable chamber, first in the absence and then in the presence of a test specimen.

The apparent volume percentage of open cells ω_r of the test specimen is calculated by plotting the curve $\omega_r = f(r)$ and extrapolating to $r = 0$, followed by calculation of the corrected volume percentage of open cells ω_0 and the corrected volume percentage of closed cells ψ_0 .

5 Test specimens

5.1 Number

A minimum of three test specimens shall be prepared for each test. A total of three tests shall be carried out per sample.

5.2 Preparation

Cut test specimens out with a band saw and machine them if necessary, taking care that there is no deformation to the original cell structure other than at the surface. The specimens shall be free of dust, voids and moulding skins.

Hot-wire cutting shall not be used.

5.3 Dimensions

The required test specimen dimensions depend on the specific method used to measure the impenetrable volume V_i . Initial specimen sizes shall be as follows:

Method 1: Pressure variation (pycnometer)

length: (25 ± 1) mm

width: (25 ± 1) mm

thickness: (25 ± 1) mm

Method 2: Volume expansion

length: (100 ± 1) mm

width: (30 ± 1) mm

thickness: (30 ± 1) mm

5.4 Sectioning of test specimens

Both methods require that specimens r_2 and r_3 of each set be further sectioned as shown in Figure 1 to provide a range of surface/volume ratios for testing.

6 Conditioning and test atmospheres

The test specimens shall be conditioned for not less than 16 h at (23 ± 2) °C and (50 ± 5) % relative humidity prior to testing. It is important that the test be conducted at (23 ± 2) °C and preferably at controlled and moderate humidity, i.e. (50 ± 5) %.

7 Measurement of surface area S and geometrical volume V_g

7.1 Determine the linear dimensions of each test specimen in accordance with ISO 1923, except that measurements shall be made to the nearest 0,05 mm. The locations of the measurement points shall be as shown in Figure 2.

7.2 Calculate the average linear dimensions, the surface area S and the geometrical volume V_g , retaining all significant figures for test specimens r_1 (one parallelepiped), r_2 (two parallelepipeds) and r_3 (four parallelepipeds).

Round off the final values for surface area S to the nearest 0,01 cm² and for the geometrical volume V_g to the nearest 0,01 cm³.




Figure 1 — Pattern for cutting test specimens




Figure 2 — Locations of measurement points

8 Determination of impenetrable volume V_i by method 1: Pressure variation (pycnometer)

NOTE The impenetrable volume V_i is determined by either method 1 or method 2. The principle, description of apparatus, calibration, procedure and calculation for these two methods are specified in this clause and clause 9, respectively.

8.1 Principle of method 1

The following characteristics are determined for an atmospheric pressure p_{amb} and a pressure reduction p_e in the test chamber in relation to p_{amb} :

- the corresponding change in volume δV_{A1} of the test chamber in the absence of a test specimen; this determination constitutes the calibration of the apparatus;
- the corresponding change in volume δV_{A2} of the test chamber in the presence of a test specimen.

The impenetrable volume V_i of the test specimen is given by the equation

$$V_i = \frac{\delta V_{A1} - \delta V_{A2}}{-p_e} p_B$$

where $p_B = p_{\text{amb}} + p_e$.

In practice (see 8.2.2), V_i is calculated from the equivalent equation

$$V_i = \frac{l_1 - l_2}{-K p_e} p_B$$

where

l_1 is the pycnometer scale reading corresponding to $K\delta V_{A1}$;

l_2 is the pycnometer scale reading corresponding to $K\delta V_{A2}$;

K is a constant relating the pycnometer scale readings to volume change in the chamber.


8.2 Description of apparatus for method 1

8.2.1 The apparatus consists of an air pycnometer that permits instant reading of the difference between internal pressure and atmospheric pressure. A schematic diagram of the apparatus is shown in Figure 3. It consists essentially of the following items:

- test chamber A, including a removable measurement chamber D of volume approximately 50 cm³, which fits to the main part of chamber A by means of an appropriate mechanical device, a filter F and an airtight circular joint G, to ensure impermeability and reproducibility of the geometrical volume of this part of the test chamber;
- chamber B to create the reduced pressure.

8.2.2 The two chambers A and B are linked in parallel by means of tubing fitted with a valve T_1 , which can connect or disconnect them, and a differential manometer M_1 . The tubing can be connected directly to atmosphere by means of valve T_2 .

When chamber D is connected to chamber A by means of the airtight joint G and the valve T_1 is closed, the volume V_A of the combined chambers (including the free volume of the chambers and of the tubing connected to the manometer M_1 and to the valve T_1) can be modified by moving piston P_A by means of crank C_A .



Key

- | | | | |
|---------------------------------|--|----------------------------------|-------------------------|
| A | Test chamber | H | Test specimen |
| B | Reduced-pressure chamber | I | Indicator |
| C _A , C _B | Cranks | J | Scale |
| D | Measurement chamber | M ₁ , M ₂ | Differential manometers |
| E _A , E _B | End points for displacement of pistons | P _A , P _B | Pistons |
| F | Filter | T ₁ to T ₅ | Valves |
| G | Airtight joint | | |

Figure 3 — Schematic diagram of apparatus for determination of impenetrable volume V_i by method 1

The indicator I of the displacement of piston P_A permits reading directly on a scale J, with a precision of 0,25 %, a value l which has been precalibrated by the manufacturer to some corresponding change δV_A , starting from an initial reference value V_0 .

NOTE The relationship between l and δV_A is defined by a proportionality constant K ($l = K\delta V_A$) as provided by the equipment manufacturer or by calibration from standard volumes. The proper value for K is obtained only if the zero reading on scale J is previously adjusted during the setting up of the air pycnometer in accordance with the manufacturer's instructions. The value of K for one commercially available air pycnometer is 2,0.

8.2.3 Chamber B can be connected directly to the atmosphere by means of valve T_3 . Moreover, it is connected by means of tubing and valve T_4 to a differential manometer M_2 which indicates the pressure reduction that can be imposed at any time on the internal volume of chamber B with respect to the ambient atmosphere. The manometer M_2 shall permit the reading of the pressure reduction to 0,25 % (i.e. a pressure reduction p_e of $-200 \text{ mmH}_2\text{O}$ shall be read to within $\pm 0,5 \text{ mmH}_2\text{O}$).

The pressure in chamber B is adjustable (when valves T_1 and T_3 are closed) by moving piston P_B by means of crank C_B . The difference p_e (negative in the procedure for method 1) between the pressure p_B in chamber B and the atmospheric pressure p_{amb} is indicated on the manometer M_2 when valve T_4 is open:

$$p_e = p_B - p_{amb}$$

8.3 Calibration of pycnometer apparatus

Determine, in accordance with the test procedure specified in 8.4 and for the atmospheric pressure p_{amb} prevailing at the moment of test, the reading l_1 corresponding to a pressure change $p_e = -200 \text{ mmH}_2\text{O}$ in relation to p_{amb} .

NOTE 1 In order to eliminate the need to determine l_1 each time the barometric pressure p_{amb} changes, it may be desirable to establish a calibration curve of $l_1 = f(p_{amb})$ for a given value of p_e . This can be accomplished as shown in Figure 4 by repeating the calibration procedure over a period of several days over which p_{amb} varies.

NOTE 2 If it is desired, for some cellular materials, to determine the impenetrable volume of the test specimens at another pressure reduction p_e' , for example $-300 \text{ mmH}_2\text{O}$, it will be necessary to plot a calibration curve for p_e' .




Figure 4 — Calibration graph for method 1 ($p_e = -200 \text{ mmH}_2\text{O}$)

8.4 Procedure for method 1

8.4.1 Prior to testing, move pistons P_A and P_B along the whole available distance to change completely the air in chambers A and B and the tubing. For this, all the valves will have to be open. In order to obtain greater homogeneity between the internal and external environments, it is advisable to repeat the operation several times.

Determine the atmospheric pressure p_{amb} to the nearest 10 Pa¹⁾.

8.4.2 Verify the zero readings of manometers M_1 and M_2 .

8.4.3 Place chamber D (containing the test specimen, if applicable) in position.

8.4.4 Again change the air in the apparatus by moving pistons P_A and P_B in the appropriate way.

8.4.5 Adjust piston P_A so as to obtain a reading $l = 0$ on scale J. Position piston P_B to enable the desired pressure reduction to be achieved.

8.4.6 Close valves T_3 , T_2 and then T_1 . Wait a few seconds. Both manometers M_1 and M_2 should indicate zero. If such is not the case, re-open valves T_1 , T_3 and T_2 , repeat the operation specified in 8.4.4 and then proceed in accordance with 8.4.5. If the manometers continue to show instability, measurements are impossible due to anomalies discussed in annex A (see clauses A.4, A.5 and A.6).

8.4.7 When the differential manometers are stable, lower the internal pressure by progressively moving piston P_B and almost simultaneously piston P_A to maintain the indicator on manometer M_1 close to zero, while observing the pressure reduction on manometer M_2 .

Never move piston P_A backwards during this operation.

8.4.8 Proceed as specified in 8.4.7 until the pressure reduction $p_e = -200 \text{ mmH}_2\text{O}$. The equilibrium must be stable. If such is not the case, there exists one of the anomalies discussed in annex A (see clauses A.4, A.5 and A.6), namely rupture of cell walls, test specimen deformation or rapid variation of p_{amb} .

In the case of test specimens of new types of cellular material, preliminary determinations shall be performed using several values of pressure reduction p_e , chosen in arithmetic progression (for example, $-100 \text{ mmH}_2\text{O}$, $-200 \text{ mmH}_2\text{O}$, $-300 \text{ mmH}_2\text{O}$, etc.). During the test, the highest value of the pressure reduction shall be used for which l still varies directly as p_e , and which permits a stable equilibrium to be achieved. The apparatus shall be re-calibrated, in accordance with 8.3, using that value of p_e .

8.4.9 Note the value of l_1 or l_2 corresponding to the pressure reduction p_e . Then open valve T_1 and progressively bring the pyknometer apparatus to atmospheric pressure by means of piston P_B and, if necessary, piston P_A . When the reading on manometer M_2 is equal to zero, open all valves. Never return to atmospheric pressure too abruptly.

8.4.10 Repeat twice the operations from 8.4.5 to 8.4.9. Generally, the first two values of l_2 (or of l_1) will be appreciably different. Suppose that the second value is lower than the first. If the third value obtained lies between the first two and does not differ from the second by more than the precision in reading l_1 , calculate l_2 (or l_1) as the average of the last two readings.

If these two conditions are not met and particularly if the third reading is still lower than the second, carry out fresh measurements as above until two measurements do not differ by more than the "reading" error.

1) $10 \text{ Pa} \approx 1 \text{ mmH}_2\text{O}$

8.5 Calculation for method 1

Calculate the impenetrable volume V_i from the equation

$$V_i = \frac{l_1 - l_2}{-K p_e} p_B$$

where

l_1 is the value corresponding to the atmospheric pressure p_{amb} prevailing at the time of test;

p_B ($= p_{amb} + p_e$) is expressed in millimetres of water.

9 Determination of impenetrable volume V_i by method 2: Volume expansion

9.1 Principle of method 2

In accordance with the Boyle-Mariotte law, an increase in volume of a confined gas results in a proportionate decrease in pressure. If the size of a chamber is increased equally with and without a test specimen in the chamber, the pressure drop will be less for the empty chamber. In this method, the relative pressure drop, previously calibrated to standard volumes, is determined from the difference in scale readings of a manometer tube open to atmospheric pressure.

The impenetrable volume V_i is seen by the chamber as a smaller apparent standard volume as the percentage of open cells increases.


9.2 Description of apparatus for method 2

9.2.1 The apparatus consists of a glass-tubing manometer assembly as shown schematically in Figure 5. The test specimen chamber K is provided with a ground-glass cap L such that a gastight seal can be obtained by applying vacuum grease to the joint. The chamber K is connected via an expansion bulb N to a manometer M_3 filled with water containing a few drops of a surfactant and a colorant. The liquid level in the manometer is adjusted by means of a reservoir O. (This can be controlled by using a syringe.) The gas chamber K is brought to atmospheric pressure prevailing at the time of test by means of the valve T_5 . A scale Q, graduated in millimetres, is attached to the open arm of the manometer M_3 .

9.2.2 In order to avoid errors due to fluctuations in ambient temperature, the whole apparatus shall be enclosed in a draughtproof case R, fitted with a transparent front panel and a trap door S through which test specimens can be introduced into the chamber K.

NOTE Several models of such apparatus have been constructed and used successfully, observing the following parameters:

- volume V_K of the chamber K and glass tubing to mark U_1 : 310 cm³
- volume V_N of the expansion bulb between marks U_1 and U_2 : 10,5 cm³
- height of mark U_2 above the bottom of the manometer: at least 650 mm
- minimum internal diameter of the glass tubing: 10 mm.



Key

- | | | | |
|----------------|-----------------------|--|-------------------|
| K | Test specimen chamber | R | Draughtproof case |
| L | Ground-glass cap | S | Trap door |
| M ₃ | Manometer | T ₆ | Valve |
| N | Expansion bulb | U ₁ , U ₂ | Marks |
| O | Reservoir | W ₁ , W ₂ , W ₃ | Liquid levels |
| Q | Scale | | |

Figure 5 — Schematic diagram of apparatus for determination of impenetrable volume V_i by method 2

9.3 Calibration of volume-expansion apparatus

9.3.1 Six calibrated standards are required (for example brass cylinders) having volumes up to 150 cm³, known with an accuracy of 0,1 cm³.

9.3.2 With valve T₆ open, adjust the liquid level in the manometer M₃ to mark U₂ and note to the nearest millimetre the corresponding level W₁ on the open arm of the manometer.

9.3.3 Raise the liquid level up to mark U₁. Close the valve T₆. Let the volume of the chamber K (including the tubing up to U₁) be V_K and the atmospheric pressure prevailing at that moment be p_{amb} .

9.3.4 Lower both liquid levels by withdrawing the liquid until the level in the closed arm reaches mark U_2 , corresponding to an expansion δV_K . Perform this operation slowly, controlling the speed so that the liquid level passes from mark U_1 to mark U_2 in (60 ± 1) s. Wait (30 ± 1) s to allow the liquid still on the wall of the expansion bulb N to rejoin the manometric liquid, constantly keeping the liquid level at mark U_2 . At the end of this time, read the liquid level W_2 in the open arm of the manometer, rounding to the nearest millimetre. Then slowly open valve T_6 , set the liquid at mark U_1 and repeat the previous operations until two successive identical readings, rounded to the nearest millimetre, are obtained.

9.3.5 Remove the cap L, insert in the test chamber K a calibrated standard of known volume V_C and replace the cap.

IMPORTANT NOTE To meet the required stability condition for V_K (see annex A, clause A.1), it is imperative that the cap L is always placed in the same position on the chamber K because even a small variation in the position of the cap on the chamber can produce a significant variation in the initial volume.

Repeat the operations specified in 9.3.3 and 9.3.4, and record, to the nearest millimetre, the level W_3 on the open arm of the manometer.

9.3.6 Calculate the ratio

$$\frac{W_2 - W_3}{W_1 - W_3}$$

where

W_1 is the reading of the initial level;

W_2 and W_3 are, respectively, the manometric readings after expansion for the test chamber K without and with the calibrated standard present.

Then

$$\frac{W_2 - W_3}{W_1 - W_3} (V_K + \delta V_K) = V_C$$

9.3.7 Repeat the operations specified in 9.3.2 to 9.3.5 using other calibrated standards having volumes V_C' , V_C'' , etc.

For V_C' , the readings will be W_1' , W_2' , W_3' and

$$\frac{W_2' - W_3'}{W_1' - W_3'} (V_K + \delta V_K) = V_C'$$

Plot these results on a graph having, as abscissae, the values of V_C , V_C' , etc., and for the ordinates the corresponding values of the ratio

$$\frac{W_2 - W_3}{W_1 - W_3}$$

The graph should be a straight line passing through the origin.

This graph (see Figure 6) will be used for the determination of the impenetrable volume V_i of the test specimens.




Figure 6 — Calibration graph for method 2

9.4 Procedure and calculation for method 2

9.4.1 Using a test specimen in place of a calibrated volume standard, follow the same procedure as for the calibration (see 9.3).

9.4.2 Calculate the ratio

$$\frac{W_2 - W_3}{W_1 - W_3}$$

obtained with the test specimen and read from the calibration graph (see Figure 6) the corresponding value of the impenetrable volume V_i from the abscissae.

10 Correction for specimen surface cells opened during specimen preparation

10.1 For the pressure-variation method (clause 8)

After V_i has been determined for each of the (at least) three specimens, bisect each specimen three times along its three centre planes to give eight cubes. Determine the impenetrable volume of each set of eight cubes following subclauses 8.4.5 to 8.4.9 and record the average volume as V_d .

10.2 For the volume-expansion method (clause 9)

Determine the apparent volume percentage of open cells in the test specimens, ω_r , corresponding to various values of r ($= S/V_g$).

Use at least three test specimens for each of three values of r (consisting of one parallelepiped for r_1 , two parallelepipeds for r_2 , and four parallelepipeds for r_3). These values will be used for plotting the straight line $\omega_r = f(r)$ and its extrapolation to $r = 0$ which gives the desired ω_0 .

The cutting pattern for the different values of r is shown in Figure 1; an example of the straight line $\omega_r = f(r)$ is shown in Figure 7.

NOTE Should this straight line intercept the ordinate below the origin, either the apparatus is not working properly or the test procedure has not been followed properly.




Figure 7 — Graph for determining the correction factor for cells opened during test specimen preparation

11 Expression of results

11.1 Apparent volume percentage of open cells

Calculate the apparent volume percentage of open cells, ω_r , of the test specimens from the equation

$$\omega_r = \frac{V_g - V_i}{V_g} \times 100$$

where

V_g is the geometrical volume, in cubic centimetres, of the test specimens determined in accordance with 7.2;

V_i is the impenetrable volume, in cubic centimetres, of the test specimens determined in accordance with either method 1 (see 8.5) or method 2 (see 9.4.2).

11.2 Corrected volume percentage of open cells

11.2.1 For the pressure-variation method (clause 8)

$$\omega_0 = \frac{V_g - 2V_i + V_d}{V_g} \times 100$$

11.2.2 For the volume-expansion method (clause 9)

Plot the curve $\omega_r = f(r)$ and, by extrapolating to $r = 0$, determine the corrected volume percentage of open cells ω_0 .

11.3 Corrected volume percentage of closed cells

Calculate the corrected volume percentage of closed cells ψ_0 from the equation

$$\psi_0 = 100 - \omega_0$$

12 Precision and accuracy

12.1 The precision of the pressure-variation method (method 1) is shown in Table 1. The data are from a round robin conducted in 1981 (see the note). Tests were conducted in five laboratories. Each test result was the average from five specimens. Each laboratory reported one result per material.

NOTE Data are available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428, USA. Request research report RR D20-1099.

Table 1 — Percentage of open cells including correction for surface cells opened during specimen preparation — Pressure-variation method (method 1)

Material	Average %	s_r %	s_L %	I_r %	I_R %
Ext PS	0,71	0,54	1,07	1,53	3,39
Ext PS (NBS GM53)	1,97	0,38	0,55	1,08	1,89
Trimer PUR (NBS GM43)	3,54	0,40	1,39	1,13	4,09
PUR	4,43	0,50	1,14	1,42	3,52
Exp PS	7,99	0,42	0,43	1,19	1,70

where

- s_r is the within-laboratory standard deviation;
- s_L is the square root of the variance between laboratories;
- $I_r = 2,83s_r$ (see repeatability below);
- $I_R = 2,83\sqrt{(s_r^2 + s_L^2)}$ (see reproducibility below).

Repeatability: In comparing two averages (each of five specimens) for the same material, obtained by the same operator using the same equipment on the same day, the averages should be judged not equivalent if they differ by more than the I_r for the material.

Reproducibility: In comparing two averages (each of five specimens) for the same material, obtained by different operators using different equipment on different days, the averages should be judged not equivalent if they differ by more than the I_R for the material.

The accuracy of this method cannot be stated because there are no established reference materials for the characteristic being determined.

12.2 The precision of method 2 is not known, and data obtained by this method should not be used in resolving disputes between suppliers and users.

13 Test report

The test report shall include the following information:

- a) a reference to this International Standard;
- b) all details necessary for complete identification of the cellular material tested;
- c) the procedure used for the determination of impenetrable volume V_i , i.e. method 1 (pycnometer) or method 2 (volume expansion);
- d) the individual results and the mean values of the corrected volume percentage of open cells ω_0 and of closed cells ψ_0 ;
- e) when applicable, the direction of the greatest dimension A of the test specimens (see Figure 1) in relation to any anisotropy of the material;
- f) any deviation from the method specified;
- g) the date of testing;
- h) all details necessary to identify the test facility.

Annex A (normative)

Notes on procedure

A.1 Stability of reference volume

It is essential that the reference volume of the test chamber is constant. This volume affects δV_{A1} and δV_{A2} (method 1) and $V_K + \delta V_K$ (method 2).

Should the reference value not be identical in the measurements with and without the test specimen, the error in determining V_i , which is determined by difference, could become important.

A.2 Influence of atmospheric pressure

The atmospheric pressure p_{amb} normally should not vary by more than 100 Pa²⁾ during the period of testing with and without specimens.

In the case of method 1, the use of the calibration graph $l_1 = f(p_{amb})$ (see Figure 4) permits correcting for such variation in p_{amb} , if it exists.

On the contrary, method 2 requires verification of the stability of p_{amb} during the complete test period.

A.3 Choice of the value of p_e (method 1) or δV_K (method 2)

The precision of the test method increases with an increase in p_e (or δV_K).

On the other hand, it is necessary to use p_e (or δV_K) values sufficiently low to maintain V_i constant during the test and to avoid rupture of cell walls due to pressure variations.

The most appropriate values depend on the nature of the cellular material involved. For method 1, it has been found that 200 mmH₂O is a satisfactory value for most cellular plastics.

A.4 Influence of temperature

Because the Boyle-Mariotte law assumes constant temperature, it is necessary to operate in a room with temperature control. The same requirement applies if liquid differential manometers are utilized.

The apparatus and test specimens shall be conditioned in the controlled-temperature room for a sufficient period to reach equilibrium before testing.

For the same reason, it is necessary to avoid any heating or cooling of the test chamber between two measurements, for instance because of an abrupt shift of the test chamber from reduced pressure to atmospheric pressure.

2) 100 Pa \approx 10 mmH₂O

A.5 Influence of humidity

It is advisable to work under controlled and moderate humidity conditions [for example (50 ± 5) % relative humidity]. The effect of humidity variations can be detected during the measurements (instability of the equilibrium in the initial conditions of p_e or δV_K or lack of repeatability between two successive measurements). The presence of moisture in test specimens is revealed by behaviour similar to that described in clause A.6.

A.6 Influence of gas occluded in test specimens

Test specimens having in their cells gases other than normal air at atmospheric pressure behave during the pressure-variation cycle as if their impenetrable volume varies with time. In method 1, this may, for example, cause instability of δV_{A2} at a given p_e .

Diffusion of blowing-agent gases, infusion of air by permeation through the cell walls or the presence of moisture can cause this problem.

This can generally be detected by determining, prior to the beginning of the test, whether the initial equilibrium can be maintained with the test chamber isolated from the atmosphere.

If drift or instability occurs, this can be corrected in some cases by cutting the test specimens at least one week before the test measurements are made. In other cases where the diffusion rate is slower, correction can be made by determining V_i at various times for each specimen, plotting V_i versus the square root of elapsed time, and extrapolating the resulting straight line back to zero time. V_i at zero time will be free of the effect from occluded gases in the cells.

ICS 83.100

Price based on 17 pages

© ISO 2002 – All rights reserved