

# INTERNATIONAL STANDARD

# ISO 4603

Second edition  
1993-11-15

**AMENDMENT 1**  
2010-12-15

---

---

## Textile glass — Woven fabrics — Determination of thickness

### AMENDMENT 1

*Verre textile — Tissus — Détermination de l'épaisseur*  
*AMENDEMENT 1*



Reference number  
ISO 4603:1993/Amd.1:2010(E)

© ISO 2010

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2010 – All rights reserved



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 4603:1993 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 13, *Composites and reinforcement fibres*.

-----

# Textile glass — Woven fabrics — Determination of thickness

## AMENDMENT 1

### Page 1, Clause 1

In line 3 of the first paragraph, replace “a thickness of 0,1 mm or more” by “a thickness of 0,01 mm or more”.

In the associated footnote, delete the year of publication of ISO 5084 and replace the title by: *Textiles — Determination of thickness of textiles and textile products*.

### Page 1, Clause 2

Replace the clause by the following text:

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 2602, *Statistical interpretation of test results — Estimation of the mean — Confidence interval*

### Page 2

Replace Table 1 by the following table (in which the centre column has been modified to give two alternative sets of conditions):

Conditions of measurement	Woven fabrics of continuous single yarns and/or folded (plied) yarns and/or rovings		Woven fabrics of staple-fibre or textured yarns (including woven fabrics with one of these products in the weft or warp only)
	Set of conditions 1 <sup>a</sup>	Set of conditions 2 <sup>a</sup>	
Measuring-foot diameter (area)	6,35 mm (0,32 cm <sup>2</sup> )	56,43 mm (25 cm <sup>2</sup> )	56,43 mm (25 cm <sup>2</sup> )
Standard pressure	176 kPa (17,6 N/cm <sup>2</sup> )	2,0 kPa (0,2 N/cm <sup>2</sup> )	—
Low pressure	—		0,5 kPa (5 cN/cm <sup>2</sup> )
High pressure	— <sup>b</sup>		2,0 kPa (20 cN/cm <sup>2</sup> )

<sup>a</sup> The set of conditions used shall be selected by agreement between the interested parties.

<sup>b</sup> For some textile-glass fabrics (for example, those with high yarn density or for electrical and electronic uses), thickness measurements may be carried out at a pressure substantially higher than the standard pressure and with a measuring foot of smaller diameter. Such measurements are made to estimate the variation in the ply thickness of laminates (cured under high pressure) produced from the fabric under test. Such pressures shall be used only by agreement between the interested parties.

*Page 2, 7.2*

Add the following words at the beginning of the subclause:

In the case of woven fabrics of staple-fibre or textured yarns,

*Page 3, Clause 9*

Replace item e) by the following text:

e) the measurement pressure used [for woven fabrics of continuous single yarns and/or folded (plied) yarns and/or rovings, state which of the two possible pressures specified in Table 1 was used and, for all fabrics, give the actual pressure used if different from the values specified in Table 1];

Replace item f) by the following text:

f) the diameter of the measuring foot used [for woven fabrics of continuous single yarns and/or folded (plied) yarns and/or rovings, state which of the two possible diameters specified in Table 1 was used and, for all fabrics, give the actual diameter used if different from the values specified in Table 1];

www.iso.org

---

---

**ICS 59.100.10**

Price based on 2 pages