
International Standard



4620

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Cadmium pigments — Specifications and methods of test

Pigments de cadmium — Spécifications et méthodes d'essai

First edition — 1986-05-15

UDC 667.622.114.8

Ref. No. ISO 4620-1986 (E)

Descriptors : paints, pigments, specifications, tests, determination of content, cadmium, zinc, selenium, sulphur.

Price based on 9 pages

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 4620 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*.

Users should note that all International Standards undergo revision from time to time and that any reference made herein to any other International Standard implies its latest edition, unless otherwise stated.

Cadmium pigments — Specifications and methods of test

1 Scope and field of application

This International Standard specifies the requirements and the corresponding methods of test for cadmium pigments suitable for general use.

2 References

ISO 385/1, *Laboratory glassware — Burettes — Part 1: General requirements.*

ISO 648, *Laboratory glassware — One-mark pipettes.*

ISO 787, *General methods of test for pigments and extenders —*

Part 1: Comparison of colour of pigments.

Part 2: Determination of matter volatile at 105 °C.

Part 5: Determination of oil absorption value.

Part 7: Determination of residue on sieve — Water method — Manual procedure.

Part 8: Determination of matter soluble in water — Cold extraction method.

Part 9: Determination of pH value of an aqueous suspension.

Part 16: Determination of relative tinting strength (or equivalent colouring value) and colour on reduction of coloured pigments — Visual comparison method.

Part 20: Comparison of ease of dispersion (oscillatory shaking method).

Part 21: Comparison of heat stability of pigments using a stoving medium.

ISO 842, *Raw materials for paints and varnishes — Sampling.*

ISO 1042, *Laboratory glassware — One-mark volumetric flasks.*

ISO 3696, *Water for laboratory use — Specifications.*¹⁾

ISO 3856, *Paints and varnishes — Determination of "soluble" metal content —*

Part 1: Determination of lead content — Flame atomic absorption spectrometric method and dithizone spectrophotometric method.

Part 2: Determination of antimony content — Flame atomic absorption spectrometric method and Rhodamine B spectrophotometric method.

Part 3: Determination of barium content — Flame atomic emission spectrometric method.

Part 4: Determination of cadmium content — Flame atomic absorption spectrometric method and polarographic method.

Part 6: Determination of total chromium content of the liquid portion of the paint — Flame atomic absorption spectrometric method.

Part 7: Determination of mercury content of the pigment portion of the paint and of the liquid portion of water-dilutable paints — Flameless atomic absorption spectrometric method.

*Part 8: Determination of selenium content — Flame atomic absorption spectrometric method and X-ray fluorescence method.*²⁾

*Part 9: Determination of arsenic content — Atomic absorption and silver diethyldithiocarbamate spectrometric methods.*¹⁾

ISO 4793, *Laboratory sintered (fritted) filters — Porosity grading, classification and designation.*

ISO 6713, *Paints and varnishes — Preparation of acid extracts from paints in liquid or powder form.*

1) At present at the stage of draft.

2) In preparation.

ISO 4620-1986 (E)

3 Definition

cadmium pigment: An inorganic coloured pigment consisting predominantly of cadmium sulfide or of mixed crystals of cadmium sulfide and cadmium selenide, in which the cadmium may be partially replaced by zinc.

NOTES

1 To adjust the relative tinting strength and/or to obtain certain application properties, cadmium pigments may contain colourless additives.

2 Cadmium pigments are characterized by a very low solubility in water and diluted acids and by a very high heat stability.

3 Yellow cadmium pigments consist mainly of mixed crystals of cadmium sulfide and zinc sulfide (Pigment yellow No. 37, part 2, ref. 77 199)¹⁾ or of cadmium sulfide (Pigment orange No. 20, part 2, ref. 77 199).¹⁾

Orange to maroon cadmium pigments consist mainly of mixed crystals of cadmium sulfide and cadmium selenide (Pigment red No. 108, part 2, ref. 77 202¹⁾).

4 Classification

This International Standard specifies the following three types of pigment, which shall be free from organic materials, other coloured inorganic pigments and brightening agents:

Type 1: Cadmium pigments, concentrated. These pigments contain not more than 30 % (*m/m*) of extenders to adjust their relative tinting strength.

Type 2: Cadmium pigments, extended. These pigments contain not more than 70 % (*m/m*) of extenders to facilitate processing.

Type 3: Cadmium pigments, unextended. These are essentially pure and do not contain any extenders.

NOTE — Type 1 and type 2 pigments are generally suitable for use in paints, plastics, rubber, etc. Type 3 pigments are mainly suitable for use in ceramics.

5 Required characteristics and their tolerances

5.1 For cadmium pigments complying with this International Standard, the essential requirements are specified in table 1 and the conditional requirements are referred to in table 2. For the conditional requirements to be specified, prior agreement between the interested parties is necessary.

5.2 The agreed reference pigment, which is referred to in table 2, shall conform with the requirements specified in table 1.

6 Sampling

Take a representative sample of the product to be tested as described in ISO 842.

7 Determination of total cadmium and zinc contents

NOTE — The method given in this clause allows the separate determination of the alkali earth metals present. However, it should be used only for cadmium pigments with a zinc content greater than 5 %. For pigments with lower zinc contents, a suitable atomic absorption spectrometric method should be agreed between the interested parties.

7.1 Principle

Dissolution of a test portion in hydrochloric acid and nitric acid. After neutralization, addition of potassium cyanide and titration of the alkali earth metals with EDTA solution. Addition of formaldehyde solution to destroy the cadmium and zinc cyanide complexes. Titration of the sum of cadmium and zinc ions with EDTA solution. Destruction of the cadmium-EDTA complex in the titrated solution with sodium diethyldithiocarbamate and precipitation of the cadmium with ammonia solution. Back-titration of the excess of EDTA corresponding to the cadmium, with magnesium sulfate solution.

7.2 Reagents

During the analysis, use only reagents of recognized analytical grade and only water of at least grade 3 purity according to ISO 3696.

WARNING — Use the reagents in accordance with the appropriate health and safety regulations.

7.2.1 Hydrochloric acid, approximately 37 % (*m/m*), ρ approximately 1,18 g/ml.

7.2.2 Hydrochloric acid, diluted, $c(\text{HCl})$ approximately 0,1 mol/l.

7.2.3 Nitric acid, approximately 65 % (*m/m*), ρ approximately 1,40 g/ml.

7.2.4 Sodium hydroxide, 10 % (*m/m*) solution.

7.2.5 Ammonia solution, approximately 25 % (*m/m*), ρ approximately 0,91 g/ml.

7.2.6 EDTA, standard volumetric solution, $c(\text{EDTA}) = 0,1 \text{ mol/l}$.

Dissolve 37,225 g of disodium ethylenediamine-tetraacetate dihydrate (EDTA disodium salt) in water in a 1 000 ml one-mark volumetric flask, dilute to the mark and mix well.

1) Classification according to the Colour Index. The Colour Index is published by the Society of Dyers and Colourists, Bradford, England and the American Association of Textile Chemists and Colorists, Lowell, Mass. (USA), revised edition 1971.

Table 1 — Essential requirements

Characteristic	Requirement	Test method
Total (Cd + Zn + Se + S)	type 1, % (m/m)	min. 70
	type 2, % (m/m)	min. 30
	type 3, % (m/m)	min. 98
Matter volatile at 105 °C	% (m/m)	max. 0,5
Matter soluble in water (cold extraction method)	% (m/m)	max. 0,3
Matter soluble in 0,07 mol/l hydrochloric acid ¹⁾		
Antimony (Sb)	% (m/m)	max. 0,05
Arsenic (As) ²⁾	% (m/m)	max. 0,01
Barium (Ba)	% (m/m)	max. 0,01
Cadmium (Cd)	% (m/m)	max. 0,1
Chromium (Cr)	% (m/m)	max. 0,1
Lead (Pb) ²⁾	% (m/m)	max. 0,01
Mercury (Hg)	% (m/m)	max. 0,005
Selenium (Se)	% (m/m)	max. 0,01
pH of the aqueous suspension		5 to 8
Residue on sieve (45 µm)	% (m/m)	max. 0,1

Table 2 — Conditional requirements

Characteristic	Requirement	Test method
Colour	Shall closely match that of the agreed reference pigment (5.2)	ISO 787/1
Relative tinting strength	Shall closely match that of the agreed reference pigment (5.2)	ISO 787/16
Ease of dispersion	Shall not be inferior to that of the agreed reference pigment (5.2)	ISO 787/20
Oil absorption value	Shall not differ by more than 15 % from the value agreed between the interested parties ³⁾	ISO 787/5
Heat stability	Shall show no greater change in colour or relative tinting strength than that of the agreed reference pigment (5.2)	ISO 787/21, carried out at 400 ± 25 °C in an inert atmosphere for 5 min

1) Where national legislation specifies different limits for the content of metals "soluble" in 0,07 mol/l hydrochloric acid and if the limits are less than those specified in this International Standard, then those limits will take precedence over those in this specification. In certain cases, limits for additional metals may be specified, for example zinc, for which a test method is described in clause 20.

2) It may be necessary to determine the arsenic or lead contents in the pigment itself, instead of in the hydrochloric acid extract, because of the national legislation of the country in which the pigment is to be used. The methods of determination should be agreed between the interested parties.

3) The oil absorption value of cadmium pigments lies generally in the range 15 to 25 g/100 g.

ISO 4620-1986 (E)

7.2.7 Magnesium sulfate, standard volumetric solution, $c(\text{MgSO}_4) = 0,1 \text{ mol/l}$.

7.2.8 Formaldehyde, 30 % (*m/m*) solution.

7.2.9 Methyl orange, 0,01 % (*m/m*) solution.

7.2.10 Buffered indicator tablets, containing mordant black II (Eriochrome Black T)¹⁾ and a buffer substance.

NOTE — Instead of an indicator tablet, 0,25 g of a mixture of 1 g of mordant black II (Eriochrome Black T) and 100 g of ammonium chloride may be added. In this case the colour changes in 7.3.2 and 7.3.3 are from red to blue and in 7.3.4 from blue to red.

7.2.11 Buffer solution, pH 10.

Dissolve 70 g of NH_4Cl in 774 ml of the ammonia solution (7.2.5) and dilute to 1 000 ml with water.

7.2.12 Sodium diethyldithiocarbamate.

7.2.13 Potassium cyanide.

WARNING — Potassium cyanide is a deadly poison.

7.3 Procedure

Carry out the determination in duplicate.

7.3.1 Weigh, to the nearest 0,1 mg, 0,3 to 0,4 g of the sample into a 250 ml beaker and add about 10 ml of the hydrochloric acid (7.2.1). Heat carefully until the hydrochloric acid is evaporated. Add 2 ml of the nitric acid solution (7.2.3) to the residue, cover the beaker with a watch glass and heat on a hotplate for 10 min or until a clear solution is obtained. Add 100 ml of water, boil for a few minutes, filter off any remaining residue if present, using a fine filter paper, wash first with the diluted hydrochloric acid (7.2.2) then with water, and collect the solution and washwater.

7.3.2 Add 1 or 2 drops of the methyl orange solution (7.2.9) to the solution obtained according to 7.3.1 and neutralize with the sodium hydroxide solution (7.2.4). Add a few millilitres of the buffer solution (7.2.11), one indicator tablet (7.2.10) or 0,25 g of the mordant black II mixture and about 2 g of the potassium cyanide (7.2.13). Titrate the solution with the EDTA solution (7.2.6) until the colour changes from red to greyish green (see the note to 7.2.10).

7.3.3 Add about 20 ml of the formaldehyde solution (7.2.8) to the solution obtained according to 7.3.2. Titrate the solution with the EDTA solution (7.2.6) until the colour changes from red to greyish green (see the note to 7.2.10). Record the volume of EDTA solution used (V_0).

7.3.4 Add approximately 1 g of the sodium diethyldithiocarbamate (7.2.12) and a few drops of the ammonia solution (7.2.5) to the titrated solution (7.3.3) and titrate with the magnesium sulfate solution (7.2.7) until the colour changes from greyish green to red (see the note to 7.2.10). Record the volume of magnesium sulfate solution used (V_1).

7.4 Expression of results

Calculate the total cadmium content of the pigment, using the equation

$$w_{\text{Cd,t}} = \frac{V_1 \times 1,124}{m}$$

Calculate the total zinc content of the pigment, using the equation

$$w_{\text{Zn,t}} = \frac{(V_0 - V_1) \times 0,654}{m}$$

where

m is the mass, in grams, of the test portion;

V_0 is the volume in millilitres, of the EDTA solution (7.2.6) required for the titration of the sum of (Cd + Zn) in 7.3.3;

V_1 is the volume in millilitres, of the magnesium sulfate solution (7.2.7) required for the titration of Cd in 7.3.4;

$w_{\text{Cd,t}}$ is the total cadmium content of the pigment, expressed as a percentage by mass;

$w_{\text{Zn,t}}$ is the total zinc content of the pigment, expressed as a percentage by mass;

1,124 is the factor ($\times 100$) for the conversion of millilitres of EDTA solution (7.2.6) to grams of Cd;

0,654 is the factor ($\times 100$) for the conversion of millilitres of EDTA solution (7.2.6) to grams of Zn.

Take the mean of the two determinations, but if the duplicate determinations differ by more than 0,4 %, repeat the procedure.

8 Determination of selenium content

8.1 Principle

Dissolution of a test portion in bromine water. After driving off the bromine, reduction of the selenium present and precipitation with hydrazinium dichloride followed by weighing.

1) Sodium 1-(1-hydroxy-2-naphthylazo)-6-nitronaphthalene-4-sulfonate.

8.2 Reagents

During the analysis, use only reagents of recognized analytical grade and only water of at least grade 3 purity according to ISO 3696.

WARNING — A number of reagents used in this determination, as well as selenium itself, are hazardous. Use the reagents in accordance with the appropriate health and safety regulations. Care must be taken when handling these materials and, wherever possible, operations shall be carried out in a fume cupboard.

8.2.1 Hydrochloric acid, approximately 37 % (*m/m*), ρ approximately 1,18 g/ml.

8.2.2 Hydrochloric acid, diluted, *c*(HCl) approximately 0,1 mol/l.

8.2.3 Bromine.

8.2.4 Hydrazinium dichloride, ($\text{H}_2\text{N}\cdot\text{NH}_2\cdot 2\text{HCl}$).

WARNING — Hydrazinium dichloride is a severe poison.

8.2.5 Carbon dioxide or nitrogen, as the compressed gas.

8.3 Procedure

WARNING — All procedures involving bromine shall be carried out in a fume cupboard. Use safety gloves.

Carry out the determination in duplicate.

Weigh to the nearest 0,1 mg, about 0,5 g of the sample, suspend it in 10 ml of water in a 100 ml conical flask fitted with a ground glass stopper and add 1 ml of the bromine (8.2.3) by means of a safety pipette. Close the flask and allow it to stand for at least 3 h or overnight.

Dilute the solution with about 20 ml of water. Fit a Liebig condenser on to the conical flask and insert a glass tube with a drawn-out tip through the condenser almost to the bottom of the flask. Connect the tube to the source of the carbon dioxide or nitrogen (8.2.5). While gently heating, pass carbon dioxide or nitrogen through the solution until the bromine has been driven off completely. Test with potassium iodine-starch paper for the presence of bromine at the top of the condenser.

Add 5 ml of the hydrochloric acid (8.2.1) to the bromine-free solution and filter off any remaining residue, if present, using a fine filter paper. Wash the residue and filter paper first with the diluted hydrochloric acid (8.2.2) and then with hot water until free from chloride.

To the filtrate and washings add 20 to 30 ml of the hydrochloric acid (8.2.1) for each 100 ml of solution. Add about 5 g of the hydrazinium dichloride (8.2.4) to the cooled solution and heat the solution on a water bath or on a gently heated sand bath. When the precipitated red selenium has been totally converted to the black form, filter off the selenium using a previously weighed sintered crucible of porosity 7 to 8 μm complying with the requirements of ISO 4793 and wash the selenium with hot

water. Collect the filtrate and washings, and retain for the determination of sulfur content (see clause 9).

Dry the crucible and selenium at 105 °C for 1 h, and after cooling to room temperature in a desiccator, weigh to the nearest 0,1 mg. Repeat the drying, cooling and weighing procedure until successive weighings differ by not more than 0,1 mg.

8.4 Expression of results

Calculate the total selenium content of the pigment, using the equation

$$w_{\text{Se,t}} = \frac{m_2}{m_1} \times 100$$

where

m_1 is the mass, in grams, of the test portion;

m_2 is the mass, in grams, of the precipitate;

$w_{\text{Se,t}}$ is the total selenium content of the pigment, expressed as a percentage by mass.

Take the mean of the two determinations but, if the duplicate determinations differ by more than 0,4 %, repeat the procedure.

9 Determination of sulfur content

NOTE — Using this method, both the sulfide content and the sulfate content are determined, with the exception of insoluble sulfates, such as barium sulfate.

9.1 Reagents

During the analysis, use only reagents of recognized analytical grade and only water of at least grade 3 purity according to ISO 3696.

WARNING — Use the reagents in accordance with the appropriate health and safety regulations.

9.1.1 Methyl orange, 0,01 % (*m/m*) solution.

9.1.2 Ammonia solution, approximately 25 % (*m/m*), ρ approximately 0,91 g/ml.

9.1.3 Hydrochloric acid, *c*(HCl) approximately 1 mol/l.

9.1.4 Barium chloride, 10 % (*m/m*) solution.

9.2 Procedure

Carry out the determination in duplicate.

Add 5 to 6 drops of the methyl orange (9.1.1) to the filtrate and washings obtained during the determination of selenium content, described in 8.3, and neutralize with the ammonia solution (9.1.2). To this solution add 3 to 5 ml of the hydrochloric acid

ISO 4620-1986 (E)

(9.1.3) for each 100 ml of solution. Heat to boiling. Add, drop by drop, while stirring, about 15 ml of the barium chloride solution (9.1.4) and boil again.

After the precipitate has settled (allow to stand overnight, if necessary), filter through a fine filter paper and wash the precipitate first with the hydrochloric acid (9.1.3) and then with hot water. Ash the filter paper slowly with access to air and heat the residue to about 800 °C. After cooling to room temperature weigh the residue.

9.3 Expression of results

Calculate the total sulfur content of the pigment, using the equation

$$w_{S,t} = \frac{m_3}{m_1} \times 13,74$$

where

m_1 is the mass, in grams, of the test portion (see 8.3);

m_3 is the mass, in grams, of the precipitate ($BaSO_4$);

$w_{S,t}$ is the total sulfur content of the pigment, expressed as a percentage by mass;

13,74 is the factor ($\times 100$) for the conversion of grams of $BaSO_4$ to grams of S.

Take the mean of the two determinations but if the duplicate determinations differ by more than 0,4 %, repeat the procedure.

10 Calculation of the total content of cadmium, zinc selenium and sulfur

Calculate the total Cd, Zn, Se and S content expressed as a percentage by mass, using the formula

$$w_{Cd,t} + w_{Zn,t} + w_{Se,t} + w_{S,t}$$

where

$w_{Cd,t}$ is the total cadmium content of the pigment, determined according to clause 7;

$w_{Zn,t}$ is the total zinc content of the pigment, determined according to clause 7;

$w_{Se,t}$ is the total selenium content of the pigment, determined according to clause 8;

$w_{S,t}$ is the total sulfur content of the pigment, determined according to clause 9.

11 Preparation of the hydrochloric acid extract

Prepare the hydrochloric acid extract of the pigment sample, for all metals including lead, by the procedure described in ISO 6713, sub-clause 8.2.

12 Determination of "soluble" antimony content

Determine the "soluble" antimony content of the pigment sample by the method described in ISO 3856/2, clause 3 (flame atomic absorption spectrometric method). Calculate the "soluble" antimony content, using the first equation given in sub-clause 3.6.1.1 of ISO 3856/2, but multiply the result by the volume, in millilitres, of the extract taken (assumed to be 20 ml).

13 Determination of "soluble" arsenic content

Determine the "soluble" arsenic content of the pigment sample by the method described in ISO 3856/9. Calculate the "soluble" arsenic content, using the first equation given in sub-clause 3.5.1.1 of ISO 3856/9, but multiply the result by the volume, in millilitres, of the extract taken (assumed to be 20 ml).

14 Determination of "soluble" barium content

Determine the "soluble" barium content of the pigment sample by the method described in ISO 3856/3. Calculate the "soluble" barium content, using the first equation given in sub-clause 7.1.1 of ISO 3856/3, but multiply the result by the volume, in millilitres, of the extract taken (assumed to be 20 ml).

15 Determination of "soluble" cadmium content

NOTE — For the determination of acid-soluble cadmium content, two methods are provided. The AAS method (15.1) should be used as the referee method in cases of dispute. Other methods can be used by agreement between the interested parties. If a complexometric method is agreed, the method described in 15.2 should be used.

15.1 Flame atomic absorption spectrometric method

Determine the "soluble" cadmium content of the pigment sample by the method described in ISO 3856/4, clause 3 (flame atomic absorption spectrometric method). Calculate the "soluble" cadmium content, using the first equation given in sub-clause 3.5.1.1 of ISO 3856/4, but multiply the result by the volume, in millilitres, of the extract taken (assumed to be 20 ml).

15.2 Complexometric method

15.2.1 Principle

Titration of the sum of cadmium and zinc ions with EDTA solution. Destruction of the cadmium-EDTA complex in the titrated solution with sodium diethyldithiocarbamate and back-titration of the excess of EDTA, corresponding to the cadmium, with magnesium sulfate solution.

Titration of the alkali earth metals in a further volume of the test solution with EDTA solution and calculation by difference of the volume of EDTA solution required for the titration of zinc.

15.2.2 Reagents

During the analysis, use only reagents of recognized analytical grade and only distilled water of at least grade 3 purity according to ISO 3696.

WARNING — Use the reagents in accordance with the appropriate health and safety regulations.

15.2.2.1 Ammonia solution, approximately 25 % (m/m), ρ approximately 0,91 g/ml.

15.2.2.2 EDTA, standard volumetric solution, $c(\text{EDTA}) = 0,01 \text{ mol/l}$.

Dissolve 3,722 5 g of disodium ethylenediamine tetraacetate dihydrate (EDTA disodium salt) in water in a 1 000 ml, one-mark volumetric flask, dilute to the mark and mix well.

15.2.2.3 Magnesium sulfate, standard volumetric solution, $c(\text{MgSO}_4) = 0,01 \text{ mol/l}$.

15.2.2.4 Sodium diethyldithiocarbamate.

15.2.2.5 Potassium cyanide, 65 g/l solution.

WARNING — Potassium cyanide is a deadly poison.

15.2.2.6 Mordant black II (Eriochrome Black T), mixture.

Mix 1 g of mordant black II with 100 g of ammonium chloride.

15.2.2.7 Methyl orange, 0,01 % (m/m) solution.

15.2.3 Apparatus

NOTE — For general use, Class B laboratory glassware is considered adequate, but, in cases of dispute, Class A apparatus should be used.

Ordinary laboratory apparatus and

15.2.3.1 Pipette, of capacity 20 ml, complying with the requirements of ISO 648.

15.2.4 Procedure

Carry out the determination in duplicate.

Measure with the pipette (15.2.3.1) into a conical flask 20 ml of the hydrochloric acid extract obtained as described in clause 11 and dilute to 50 ml with water. Neutralize with the ammonia solution (15.2.2.1) after adding one or two drops of the methyl orange solution (15.2.2.7). Add a further 1 ml of the ammonia solution and then add 0,25 g of the mordant black II mixture (15.2.2.6). Titrate with the EDTA solution (15.2.2.2) until the colour changes from red to blue. Then add exactly further 3 ml of the EDTA solution, shake carefully, note the total volume of EDTA solution added (V_3) and back-titrate with the magnesium sulfate solution (15.2.2.3) until the red colour is stable. Record the volume of magnesium sulfate solution used (V_4).

Add approximately 1 g of the sodium diethyldithiocarbamate (15.2.2.4). Shake carefully and titrate the liberated EDTA with the magnesium sulfate solution (15.2.2.3) until the colour changes. Record the volume of magnesium sulfate solution used (V_5).

Measure a fresh 20 ml portion of the hydrochloric acid extract (clause 11) with the pipette (15.2.3.1) and dilute to 50 ml with water. Neutralize with the ammonia solution (15.2.2.1) after adding one or two drops of the methyl orange solution (15.2.2.7). Add a further 1 ml of the ammonia solution and add 10 ml of the potassium cyanide solution (15.2.2.5). Add 0,25 g of the mordant black II mixture (15.2.2.6) and titrate with the EDTA solution (15.2.2.2) until the colour changes. Record the volume of EDTA solution used (V_6).

15.2.5 Expression of results

Calculate the "soluble" cadmium content of the pigment, using the equation

$$w_{\text{Cd,s}} = \frac{V_5 \times V_1 \times 0,1124}{m_4 \times V_2}$$

Calculate the "soluble" zinc content of the pigment, using the equation

$$w_{\text{Zn,s}} = [V_3 - (V_4 + V_5 + V_6)] \times 0,654 \times \frac{V_1}{V_2} \times \frac{100}{m_4 \times 1\,000}$$

where

m_4 is the mass, in grams, of the test portion (assumed to be $5,00 \pm 0,01 \text{ g}$);

V_1 is the volume, in millilitres, of the hydrochloric acid plus ethanol used for the extraction described in sub-clause 8.2 of ISO 6713 (assumed to be 77 ml);

V_2 is the volume, in millilitres, of the hydrochloric acid plus ethanol extract used for the determination (assumed to be 20 ml);

V_3 is the volume, in millilitres, of the EDTA solution (15.2.2.2) added to the test solution;

V_4 is the volume, in millilitres, of the magnesium sulfate solution (15.2.2.3) used for the titration before addition of sodium diethyldithiocarbamate;

V_5 is the volume, in millilitres, of the magnesium sulfate solution (15.2.2.3) used for the titration, after addition of sodium diethyldithiocarbamate;

V_6 is the volume, in millilitres, of the EDTA solution (15.2.2.2) used for the titration of the potassium cyanide treated solution;

$w_{\text{Cd,s}}$ is the "soluble" cadmium content of the pigment, expressed as a percentage by mass;

$w_{\text{Zn,s}}$ is the "soluble" zinc content of the pigment, expressed as a percentage by mass;

ISO 4620-1986 (E)

0,112 4 is the factor ($\times 100$) for the conversion of millilitres of EDTA solution (15.2.2.2) to grams of Cd;

0,065 4 is the factor ($\times 100$) for the conversion of millilitres of EDTA solution (15.2.2.2) to grams of Zn.

16 Determination of "soluble" chromium content

Determine the "soluble" chromium content of the pigment sample by the method described in ISO 3856/6. Calculate the "soluble" chromium content using the first equation given in sub-clause 7.1 of ISO 3856/6, but multiply the result by the volume, in millilitres, of the extract taken (assumed to be 20 ml).

17 Determination of "soluble" lead content

Determine the "soluble" lead content of the pigment sample by the method described in ISO 3856/1, clause 3 (flame atomic absorption spectrometric method). Calculate the "soluble" lead content, using the first equation given in sub-clause 3.5.1.1 of ISO 3856/1, but multiply the result by the volume, in millilitres, of the extract taken (assumed to be 20 ml).

18 Determination of "soluble" mercury content

Determine the "soluble" mercury content of the pigment sample by the method described in ISO 3856/7. Calculate the "soluble" mercury content, using the first equation given in sub-clause 7.1.1 of ISO 3856/7, but multiply the result by the volume, in millilitres, of the extract taken (assumed to be 20 ml).

19 Determination of "soluble" selenium content

Determine the "soluble" selenium content of the pigment sample by the method described in ISO 3856/8. Calculate the "soluble" selenium content, using the first equation given in sub-clause 3.5.1.1 of ISO 3856/8, but multiply the result by the volume, in millilitres, of the extract taken (assumed to be 20 ml).

20 Determination of "soluble" zinc content

NOTE — For the determination of acid-soluble zinc content, two methods are provided. The AAS method (20.1) should be used as the referee method in cases of dispute. Other methods can be used by agreement between the interested parties. If a complexometric method is agreed, the method described in 15.2 should be used.

20.1 Flame atomic absorption spectrometric method — Principle

Aspiration of the test solution into an acetylene-air flame. Measurement of the absorption of the selected spectral line emitted by a zinc hollow-cathode lamp or zinc discharge lamp, in the region of 213,9 nm.

20.2 Reagents and materials

During the analysis, use only reagents of recognized analytical grade and only water of at least grade 3 purity according to ISO 3696.

WARNING — Use the reagents in accordance with the appropriate health and safety regulations.

20.2.1 Hydrochloric acid, $c(\text{HCl}) = 0,07$ mol/l.

20.2.2 Acetylene, commercial grade, in a steel cylinder.

20.2.3 Compressed air.

20.2.4 Zinc, standard stock solution containing 1 g of Zn per litre.

Either

a) transfer the contents of an ampoule of standard zinc solution containing exactly 1 g of Zn into a 1 000 ml one-mark volumetric flask, dilute to the mark with the hydrochloric acid (20.2.1) and mix well;

or

b) weigh to the nearest 0,1 mg, 4,398 6 g of zinc sulfate heptahydrate ($\text{ZnSO}_4 \cdot 7\text{H}_2\text{O}$), dissolve in the hydrochloric acid (20.2.1), in a 1 000 ml one-mark volumetric flask, dilute to the mark with the same hydrochloric acid and mix well.

1 ml of this standard stock solution contains 1 mg of Zn.

20.2.5 Zinc, standard solution containing 10 mg of Zn per litre.

Prepare this solution on the day of use.

Pipette 10 mg of the standard stock solution (20.2.4) into a 1 000 ml one-mark volumetric flask, dilute to the mark with the hydrochloric acid (20.2.1) and mix well.

1 ml of this standard solution contains 10 μg of Zn.

20.3 Apparatus

NOTE — For general use, Class B laboratory glassware is considered adequate, but, in cases of dispute, Class A apparatus should be used.

Ordinary laboratory apparatus and

20.3.1 Flame atomic absorption spectrometer, suitable for measurements at a wavelength of 213,9 nm and fitted with a burner fed with acetylene and air.

20.3.2 Zinc hollow-cathode lamp or zinc discharge lamp.

20.3.3 Pipettes, of capacity 10 ml, complying with the requirements of ISO 648.

20.3.4 Burette, of capacity 50 ml, complying with the requirements of ISO 385/1.

20.3.5 One-mark volumetric flasks, of capacity 100 ml and 1 000 ml, complying with the requirements of ISO 1042.

20.4 Procedure

20.4.1 Preparation of the calibration graph

20.4.1.1 Preparation of the standard matching solutions

Into a series of seven 100 ml one-mark volumetric flasks (20.3.5), introduce from the burette (20.3.4), respectively, the volumes of the standard zinc solution (20.2.5) shown in table 3, dilute each to the mark with the hydrochloric acid (20.2.1) and mix well.

Table 3 — Standard matching solutions

Standard matching solution No.	Volume of the standard zinc solution (20.2.5)	Corresponding concentration of Zn in the standard matching solution
	ml	µg/ml
0*	0	0
1	5	0,5
2	10	1,0
3	15	1,5
4	20	2,0
5	25	2,5
6	30	3,0

* Blank matching solution.

20.4.1.2 Spectrometric measurements

Install the zinc spectral source (20.3.2) in the spectrometer (20.3.1) and optimize the conditions for the determination of zinc. Adjust the instrument in accordance with the manufacturer's instructions and adjust the monochromator to the region of 213,9 nm in order to obtain the maximum absorbance.

Adjust the flow of the acetylene (20.2.2) and the air (20.2.3) according to the characteristics of the aspirator-burner, and ignite the flame. Set the scale expansion, if fitted, so that the standard matching solution No. 6 (see table 3) gives almost a full-scale deflexion.

Aspirate into the flame each of the standard matching solutions (see 20.4.1.1) in ascending order of concentration, and repeat with the standard matching solution No. 5 to verify that the instrument has achieved stability. Aspirate water through the burner between each measurement, taking care to keep the rate of aspiration uniform.

20.4.1.3 Calibration graph

Plot a graph having the masses, in micrograms, of Zn contained in 1 ml of the standard matching solutions as abscissae and the corresponding values of the absorbances, reduced by the reading for the blank matching solution, as ordinates.

20.4.3 Determination

Carry out the determination in duplicate.

Measure first the absorbance of the hydrochloric acid (20.2.1) in the spectrometer (20.3.1) after having adjusted it as described in 20.4.1.2. Then measure the absorbance of each test solution obtained as described in clause 11 three times and, afterwards, that of the hydrochloric acid again. Finally, re-determine the absorbance of standard matching solution No. 5 (see 20.4.1.1) in order to verify that the response of the apparatus has not changed. If the absorbance of a test solution is higher than that of the standard matching solution with the highest concentration, dilute the test solution appropriately (dilution factor F) with a known volume of the hydrochloric acid (20.2.1).

20.5 Expression of results

Calculate the "soluble" zinc content of the pigment, using the equation

$$w_{Zn,s} = \frac{a \times F \times 0,015}{m_5}$$

where

a is the zinc concentration, in micrograms per millilitre, of the test solution, obtained from the calibration graph;

F is the dilution factor, if required;

m_5 is the mass, in grams, of the test portion (assumed to be $5,00 \pm 0,01$ g);

$w_{Zn,s}$ is the "soluble" zinc content of the pigment, expressed as a percentage by mass.

21 Test report

The test report shall contain at least the following information:

- the type and identification of the product tested;
- a reference to this International Standard (ISO 4620);
- the results of the test, the method used where a choice is available, and whether or not the product complies with the relevant specification limits;
- any deviation, by agreement or otherwise, from the procedures specified;
- the dates of the tests.