



Rubber and rubber products — Guide to the identification of antidegradants — Thin layer chromatographic methods

TECHNICAL CORRIGENDUM 1

Caoutchouc et produits en caoutchouc — Guide d'identification des agents de protection — Méthodes par chromatographie en couche mince

RECTIFICATIF TECHNIQUE 1

Technical corrigendum 1 to International Standard ISO 4645 : 1984 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*.

Page 6

Subclause A.2.2

Replace the second paragraph by the following:

“Most phenolic compounds, except hindered phenols, give a red colour. Phenolic resins give a red colour.”

Subclause A.2.5

Replace the second and third sentences by the following paragraph:

“Dialkylphenylenediamines give a pink colour, alkylarylphenylenediamines give a blue colour, and diarylphenylenediamines give a green colour.”

This page intentionally left blank