

INTERNATIONAL STANDARD

ISO 4714

Second edition
2000-03-15

Composition cork — Specifications, sampling, packaging and marking

*Aggloméré composé de liège — Spécifications, échantillonnage,
emballage et marquage*



Reference number
ISO 4714:2000(E)

© ISO 2000

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 734 10 79
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 4714 was prepared by Technical Committee ISO/TC 87, *Cork*.

This second edition cancels and revises the first edition (ISO 4714:1986), which has been technically revised. The classification of composition cork and the behaviour in boiling hydrochloric acid have been removed.

Introduction

Composition cork is a material with many different compositions and applications.

This International Standard gives the specifications required to provide its minimum characterization.

Performance requirements related to an intended use are specified in relevant International Standards.

Composition cork of low thickness may be obtained as such by direct compression or may be obtained either by reslicing blocks or by unwinding and cutting cylindrical rolls.

Composition cork — Specifications, sampling, packaging and marking

1 Scope

This International Standard establishes the minimum requirements for agglomerated composition cork in the sheet form and specifies the requirements for sampling, packaging and marking.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 633, *Cork — Vocabulary*.

ISO 2859-1, *Sampling procedures for inspection by attributes — Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection*.

ISO 7322, *Composition cork — Test methods*.

3 Terms and definitions

For the purposes of this International Standard, the terms and definitions given in ISO 633 and the following apply.

3.1

composition cork

agglomerated composition cork

product obtained from the agglutination of cork granules with the addition of a binder which is not derived from cork cells

3.2

rubbercork

product manufactured as a compound of cork granules and rubber, which can be used either in the form of granules or as a binder

4 Sampling

From each lot, the number of packages (at least three) and the quantity of material to be taken from the sample shall be in accordance with ISO 2859-1, for the inspection level agreed between parties.

5 Specifications

5.1 Thickness

The thickness of agglomerated composition cork shall be determined in accordance with ISO 7322. The accepted deviations from nominal thickness are indicated in Table 1.

Table 1 — Thickness tolerances

Thickness mm	Tolerance %
≤ 3	± 15
> 3	+ 15 0

5.2 Apparent density

The apparent density of agglomerated composition cork shall be determined in accordance with ISO 7322. The minimum value shall be fixed by agreement between parties and shall be declared by the manufacturer.

5.3 Tensile strength

The minimum¹⁾ tensile strength of agglomerated composition cork, determined in accordance with ISO 7322, shall be at least 200 kPa.

5.4 Compressibility and recovery

The compressibility and the recovery of agglomerated composition cork shall be determined in accordance with ISO 7322. The minimum¹⁾ value shall be fixed by agreement between parties and shall be declared by the manufacturer.

5.5 Resistance to boiling water

The resistance to boiling water of composition cork shall be determined in accordance with ISO 7322. Test specimens shall not disaggregate.²⁾

6 Packaging

Agglomerated composition cork shall be packed in moisture-resistant packages or palettes which shall ensure transportation to their destination without damage to the product.

1) Minimum value is the average of the results obtained.

2) A test specimen is said to “disaggregate” if it splits open and/or if it shows substantial loss of particles during the test.

7 Marking

Packages shall show the following information:

- a) reference to this International Standard, i.e. ISO 4714;
- b) the product designation;
- c) the manufacturer's identification, even coded;
- d) the origin of the composition cork.

© ISO 2000. All rights reserved.

ICS 79.100

Price based on 3 pages

© ISO 2000 – All rights reserved