

INTERNATIONAL STANDARD

ISO
5173

Third edition
2009-06-15

AMENDMENT 1
2011-11-01

Destructive tests on welds in metallic materials — Bend tests

AMENDMENT 1

*Essais destructifs des soudures sur matériaux métalliques — Essais de
pliage*

AMENDEMENT 1



Reference number
ISO 5173:2009/Amd.1:2011(E)

© ISO 2011



COPYRIGHT PROTECTED DOCUMENT

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 5173:2009 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 5, *Testing and inspection of welds*.

Requests for official interpretations of any aspect of this Amendment should be directed to the Secretariat of ISO/TC 44/SC 5 via your national standards body. A complete listing of these bodies can be found at www.iso.org.

Destructive tests on welds in metallic materials — Bend tests

AMENDMENT 1

Page 9, 5.6.7.3, a), 2)

Replace the text with the following:

2) For pipes, the width, b , of the test specimen shall be at least:

— for pipe diameter ≤ 50 mm:

$$b = t + 0,1D$$

(minimum width, 8 mm);

— for pipe diameter > 50 mm:

$$b = t + 0,05D$$

(minimum width 8 mm, but should not exceed 40 mm).

