



INTERNATIONAL STANDARD ISO 5267-1:1999
TECHNICAL CORRIGENDUM 1

Published 2001-03-01

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Pulps — Determination of drainability —

Part 1: Schopper-Riegler method

TECHNICAL CORRIGENDUM 1

Pâtes — Détermination de l'égouttabilité —

Partie 1: Méthode Schopper-Riegler

RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to International Standard ISO 5267-1:1999 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 5, *Test methods and quality specifications for pulp*.

Page 4, A.2

Replace the last sentence with the following text.

The sealing cone shall be raised at a constant rate of 100 mm/s \pm 10 mm/s.