

First edition
2007-02-01

Steel wire and wire products — Non-ferrous metallic coatings on steel wire —

**Part 2:
Zinc or zinc-alloy coating**

Fils et produits tréfilés en acier — Revêtements métalliques non ferreux sur fils d'acier —

Partie 2: Revêtements de zinc ou d'alliages de zinc



Reference number
ISO 7989-2:2007(E)

© ISO 2007

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Coating requirements	2
4.1	Requirements for the coating material	2
4.2	Requirements relating to coating on the wire	3
4.2.1	Coating mass per unit area	3
4.2.2	Appearance of coating	3
4.2.3	Dipping test	4
4.2.4	Special finishes	4
4.2.5	Adherence of coating	4
5	Test conditions	6
5.1	Selection of samples	6
5.2	Determination of coating mass per unit area	6
5.2.1	General	6
5.2.2	Gravimetric method	6
5.2.3	Gaseous volumetric method	7
5.3	Dipping test	11
5.3.1	Principle	11
5.3.2	Reagents	12
5.3.3	Preparation of test piece	12
5.3.4	Test procedure	12
5.3.5	Interpretation of results	12
	Bibliography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 7989-2 was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 17, *Steel wire rod and wire products*.

This first edition of ISO 7989-2, together with ISO 7989-1, cancels and replaces ISO 7989:1988, which has been technically revised.

ISO 7989 consists of the following parts, under the general title *Steel wire and wire products — Non-ferrous metallic coatings on steel wire*:

- *Part 1: General principles*
- *Part 2: Zinc or zinc-alloy coating*

Steel wire and wire products — Non-ferrous metallic coatings on steel wire —

Part 2: Zinc or zinc-alloy coating

1 Scope

This part of ISO 7989 specifies the requirements for the coating mass per unit area, for other properties and also for testing of zinc or zinc-alloy coatings on steel wire and steel wire products, of circular or other section.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1460:1992, *Metallic coatings — Hot dip galvanized coatings on ferrous materials — Gravimetric determination of the mass per unit area*

ISO 7802:1983, *Metallic materials — Wire — Wrapping test*

ISO 7989-1:2006, *Steel wire and wire products — Non-ferrous metallic coatings on steel wire — Part 1: General principles*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

wire with zinc or zinc-alloy coating

wire to which zinc or zinc-alloy coating has first been applied to protect it against corrosion

NOTE The coating method may be hot dipping in a bath of molten zinc, or by means of an aqueous solution of suitable electrolyte. In the hot dipping process, wiping media may be used to modify the coating mass per unit area.

3.2

zinc or zinc alloy coating

coating composed of zinc or zinc alloy, where the zinc alloy is zinc to which other elements have been deliberately added in order to obtain particular characteristics, and in which the quantity of zinc is at least 50 %

NOTE The most common alloy elements are aluminium, tin and nickel, but other elements may also be considered.

3.3

coating mass per unit area

mass of zinc or zinc alloy per unit of surface area of bare wire

NOTE This is expressed in grams per square metre of surface.

Table 1 — Coating mass per unit area

Diameter d mm	Classes ^a					
	A g/m ²	AB g/m ²	B g/m ²	C g/m ²	D g/m ²	A×3 ^b g/m ²
0,15 ≤ d < 0,20	—	—	15	—	10	
0,20 ≤ d < 0,25	30	20	20	20	15	
0,25 ≤ d < 0,32	45	30	30	25	15	
0,32 ≤ d < 0,40	60	30	30	25	15	
0,40 ≤ d < 0,50	85	55	40	30	15	
0,50 ≤ d < 0,60	100	70	50	35	20	
0,60 ≤ d < 0,70	115	80	60	40	20	
0,70 ≤ d < 0,80	130	90	60	45	20	
0,80 ≤ d < 0,90	145	100	70	50	20	
0,90 ≤ d < 1,00	155	110	70	55	25	
1,00 ≤ d < 1,20	165	115	80	60	25	
1,20 ≤ d < 1,40	180	125	90	65	25	540
1,40 ≤ d < 1,65	195	135	100	70	30	585
1,65 ≤ d < 1,85	205	145	100	75	30	615
1,85 ≤ d < 2,15	215	155	115	80	40	645
2,15 ≤ d < 2,50	230	170	125	85	45	690
2,50 ≤ d < 2,80	245	185	125	95	45	735
2,80 ≤ d < 3,20	255	195	135	100	50	765
3,20 ≤ d < 3,80	265	210	135	105	60	795
3,80 ≤ d < 4,40	275	220	135	110	60	825
4,40 ≤ d < 5,20	280	220	150	110	70	840
5,20 ≤ d < 8,20	290			110	80	870
8,20 ≤ d ≤ 10,00	300			110	80	900

^a The coating class with a designation starting with A relates to thick coatings (generally final coating). Designations ending in B relate to classes usually but not always obtained by (zinc coating) and subsequent drawing. Classes C and D are standard classes for low mass coating which are usually produced but not exclusively, produced by hot zinc dipping and then wiping.

^b A ×3 relates to very high mass requirement three times higher than Class A. Other multiples of Class A are possible, and these classes will be identified in the same way, e.g. A×4.

4 Coating requirements

4.1 Requirements for the coating material

The zinc or zinc alloy used for the coating shall be specified at the time of the enquiry and order. For zinc alloys not mentioned in this part of ISO 7989, the alloy shall be specified at the enquiry and order.

NOTE For Zn95Al5, reference is made to ASTM B 750^[1] with or without mischmetal (MM).

The ingot of the material used for the zinc coating shall be of minimum 99,9 % purity unless otherwise stated in the relevant product standard or other specification in the order. Coatings applied by electrolysis shall contain a minimum of 99 % zinc.

4.2 Requirements relating to coating on the wire

4.2.1 Coating mass per unit area

The minimum mass of zinc per unit of surface area of the wire shall comply with the requirements of Table 1.

If no class of zinc coating or no coating mass per unit area is specified, the coating shall be called “regular coating”. Such a coating shall have not less than 1 g zinc per kilogram of zinc-coated wire, equivalent to the coating mass in grams per square metre (g/m^2) which is not less than two times the wire diameter, expressed in millimetres (mm).

The requirements for zinc-aluminium coatings of type Zn95Al5 are given in Table 2.

For other zinc-alloy coatings, the manufacturer and supplier shall agree on the required coating mass.

Table 2 — Mass requirements for a coating of Zn95Al5

Diameter d mm	Coating mass per unit area		
	Class A ^a g/m ²	Class B ^b g/m ²	Class AB ^c g/m ²
$0,20 \leq d < 0,25$		20	20
$0,25 \leq d < 0,40$		30	30
$0,40 \leq d < 0,50$	85	40	55
$0,50 \leq d < 0,60$	100	50	70
$0,60 \leq d < 0,70$	115	60	80
$0,70 \leq d < 0,80$	130	60	90
$0,80 \leq d < 0,90$	145	70	100
$0,90 \leq d < 1,00$	155	70	110
$1,00 \leq d < 1,20$	165	80	115
$1,20 \leq d < 1,40$	180	90	125
$1,40 \leq d < 1,65$	195	100	135
$1,65 \leq d < 1,85$	205	100	145
$1,85 \leq d < 2,15$	215	115	155
$2,15 \leq d < 2,50$	230	125	170
$2,50 \leq d < 2,80$	245	125	185
$2,80 \leq d < 3,20$	255	135	195
$3,20 \leq d < 3,80$	265	135	210
$3,80 \leq d < 4,40$	275	135	220
$4,40 \leq d < 5,20$	280	150	220
$5,20 \leq d < 8,20$	290		
$8,20 \leq d \leq 10,00$	300		

^a Class A: Usually zinc alloy coated at final size.
^b Class B: Usually coated and drawn after coating.
^c Class AB: Re-drawn or coated with zinc-aluminium alloy after final drawing.

4.2.2 Appearance of coating

The coating applied to the wire shall be reasonably smooth and as evenly distributed as industrial technology allows and not show discontinuities such as bare patches, dross contamination, etc.

NOTE The Zn95Al5 zinc-aluminium alloy might show difference in colour and become darker with time. This does not affect the corrosion protection performance.

4.2.3 Dipping test

If agreed at the time of the enquiry and order, the dipping (immersion) test shall be carried out according to the procedure detailed in 5.3. However, it should be pointed out that there is no direct link between the number of dips and the coating mass per unit area and that the result is determined as much by the conditions of manufacture of the coating as by the uniformity of the coating.

Table 3 gives the minimum number of immersions for coatings of classes A and AB.

The dipping test does not apply to classes B, C and D.

Table 3 — Minimum number of dips

Nominal diameter <i>d</i> mm	Class A		Class AB	
	Number of dips		Number of dips	
	of 1 min	of 1/2 min	of 1 min	of 1/2 min
$0,40 \leq d < 0,60$	—	1	—	—
$0,60 \leq d < 0,90$	1	—	—	1
$0,90 \leq d < 1,00$	1	1	—	1
$1,00 \leq d < 1,40$	1	1	1	—
$1,40 \leq d < 1,65$	2	—	1	—
$1,65 \leq d < 1,85$	2	—	1	—
$1,85 \leq d < 2,15$	2	—	1	1
$2,15 \leq d < 2,80$	2	1	1	1
$2,80 \leq d < 4,40$	3	—	2	—
$4,40 \leq d < 5,20$	3	1	2	—
$5,20 \leq d < 8,20$	3	1	—	—
$8,20 \leq d \leq 10,00$	4	—	—	—

4.2.4 Special finishes

If drawing after galvanizing is required, it shall be stipulated at the time of enquiry and order or in the appropriate product standard. The same also applies for other special finishes such as wax coating, a polished surface or an exceptionally smooth surface.

4.2.5 Adherence of coating

4.2.5.1 Wrapping test


During the test carried out in accordance with ISO 7802, the coating shall adhere to the steel when subjected to the conditions of wrapping test for adherence. It shall not crack or split to such an extent that slivers of coating can be removed by simply rubbing with the bare fingers. The loosening or detachment during testing of small particles of zinc resulting from mechanical polishing of the surface of the zinc or zinc-alloy coating shall not be considered to be a cause for rejection.

The wrapping test shall be carried out according to ISO 7989-1:2006, 5.3.


4.2.5.2 Assessment of adherence

To assess the adherence of the coating as may be specified in the relevant product standard or for evaluating different conditions of manufacturing, the following procedure may be applied.

Compare the coiled wire to the reference chart (see Figure 1). Allocate a value of 1 to 5 to the quality of adherence of the coating in accordance with the reference chart in Figure 1.




1



2



3



4



5

Figure 1 — Assessment of the adherence of the coating

5 Test conditions

5.1 Selection of samples

The number and the basis for the selection of test pieces shall be defined in the product standard. In the absence of such a standard, the manufacturer and purchaser shall agree between them on the degree of sampling.

When taking the samples, care shall be taken to avoid damaging the surface. Parts of the wire which are visibly damaged shall not be used.

A test piece of wire, which is of a suitable length for the specified tests shall be taken from one or both ends of each reel selected for sampling.

In the case of coated wire products, the product standard shall specify the length of the samples to be taken.

5.2 Determination of coating mass per unit area

5.2.1 General

In the case of wire with a zinc or zinc-alloy coating, the coating mass per unit area shall be determined either by the gravimetric method or the volumetric method. The second offers an acceptable degree of accuracy and has the advantage of being quick. This is why it is the preferred method for routine testing of wire of all dimensions which can easily be fitted into the measuring equipment. In the event of any dispute, the gravimetric method shall be used as the reference test method.

The test methods in this part of ISO 7989 do not necessarily include in detail all the precautions necessary to satisfy hygiene and safety requirements in the workplace, etc. Care should be taken to ensure that all necessary precautions are taken and procedures are implemented only by people who have received suitable training.

5.2.2 Gravimetric method

5.2.2.1 General

The method shall be applied in accordance with ISO 7989-1 with the following additional requirements.

5.2.2.2 Reagents

5.2.2.2.1 Hydrochloric acid, used as a stripping solution, with a concentration of 1,13 g/ml to 1,19 g/ml by density to which an appropriate inhibitor is added.

5.2.2.2.2 Inhibitor, added to the stripping solution.

Dissolve 3,5 g of hexamethylene-tetramine ($C_6H_{12}N_4$) in 500 ml of concentrated hydrochloric acid ($\rho = 1,19$ g/ml). Dilute this solution to 1 000 ml with distilled water.

Any other suitable inhibitor can be used.

It is recommended that preference be given to inhibitors which do not contain antimony.

5.2.2.3 Calculation of coating mass per unit area

The coating mass of zinc or zinc alloy per unit area shall be calculated according the following formulae:

$$m_A = \frac{\Delta m}{A} \times 10^6$$

where

A is the coated surface of the sample, in square millimetres (mm²) (surface of the stripped wire);

Δm is the mass loss of the sample by chemical stripping, in grams (g);

m_A is the coating mass, in grams per square metre (g/m²).

or

$$m_A = 1\,962 \times d \times \frac{\Delta m}{m_2}$$

where

m_2 is the mass of the sample after chemical stripping, in grams (g);

d is the diameter of (round) wire, in millimetres (mm);

m_A is the coating mass, in grams per square metre (g/m²).

5.2.2.4 Test pieces

After carefully straightening out the wire samples, cut the test pieces accurately to a suitable length depending on the size of the tube, the diameter of the wire and the assumed mass of the coating. The lengths given in Table 4 are generally applicable for proper gas release. Different lengths may be necessary depending on the release of gas.

Table 4 — Recommended length of test pieces

Dimensions in millimetres	
Diameter d	Length of test piece
$0,15 \leq d < 1,00$	600
$1,00 \leq d < 1,50$	500
$1,50 \leq d < 3,00$	300
$3,00 \leq d < 5,00$	200
$5,00 \leq d \leq 10,00$	100

5.2.3 Gaseous volumetric method

5.2.3.1 Principle

The volumetric method for determining the mass of the coating depends on the property by which a metal dissolved in an acid releases a quantity of hydrogen proportional to the mass of metal dissolved, i.e. representing the chemical equivalent of the metal in question.

In the case of zinc, this relationship is very simple. For zinc alloys, each case shall be examined individually on the basis of the metals present in the zinc alloy. Only the method for zinc and the “zinc 95 % – aluminium 5 %” alloy is described in detail.

By measuring the volume of hydrogen released by dissolving the coating, the quantity of coating can be determined. By relating this result to the surface area of the test piece, measured once the coating has dissolved, the coating mass per unit area is obtained.

5.2.3.2 Reagents

5.2.3.2.1 Hydrochloric acid, used to dissolve the coating, with a density between 1,13 g/ml and 1,19 g/ml.


NOTE The concentration of the acid may affect the result of the volumetric method; a powerful acid will produce slightly lower results.

5.2.3.2.2 Inhibitor, added to the stripping solution, to protect the steel base against dissolving.

The inhibitors may be hexamethylene-tetramine ($C_6H_{12}N_4$), formaldehyde (HCHO) or any other suitable inhibitor.

5.2.3.3 Apparatus

The apparatus used is made up of the following items (see Figure 2).



Key

- 1 base
- 2 tap B
- 3 hose
- 4 graduated tube
- 5 tap A
- 6 acid reservoir
- 7 container

Figure 2 — Apparatus for the determination of the coating mass per unit area by the gaseous volumetric method

5.2.3.3.1 Tube (4), graduated in millimetres, with a tap at each end.

5.2.3.3.2 Flask (6), with an opening near the bottom, connected by rubber tube to the opening near the bottom of the graduated tube.

5.2.3.3.3 Container (7), to hold the test piece once the zinc coating or zinc-alloy coating has been removed.

5.2.3.4 Test pieces

After carefully straightening out the wire samples, cut the test pieces accurately to a suitable length depending on the size of the tube, the diameter of the wire and the assumed mass of the coating. The lengths given in Table 5 are generally applicable for proper gas release. Different lengths may be necessary depending on the release of gas.

Table 5 — Recommended length of test pieces

Dimensions in millimetres

Diameter <i>d</i>	Length of test piece
$d < 1,00$	300
$1,00 \leq d < 1,50$	150
$1,50 \leq d < 3,00$	100
$3,00 \leq d \leq 5,00$	50

5.2.3.5 Procedure

With tap B closed, fill the graduated tube and part of the flask with as reagent an hydrochloric acid solution containing a suitable inhibitor.

Raise the level of liquid in the graduated tube to just below A by raising the acid reservoir C. The levels in the tube and flask shall be identical [see Figure 3 a)].

After placing the test piece in the graduated tube through tap A, close tap A and hydrogen released by the action of the acid on the coating will accumulate in the upper part of the graduated tube.


When the release of hydrogen is completed, apart from a few small bubbles, lower the flask [see Figure 3 b)] in relation to the graduated tube, in order to bring the levels of solution in the tube and flask to the same height. The position of the surface of the liquid in the tube then shows the volume of hydrogen released. The volume shall be read from the lower level of the liquid surface to ensure minimum error.

When the test is completed, open tap A and remove all the acid reagent from the tube, placing the flask on a table.

Open tap B so that the test piece can be removed from the tube and placed in the container. The test piece is then washed and carefully wiped before its diameter is measured.

The test shall be carried out on one test piece at a time and the temperature in the tube shall be maintained at $20\text{ }^{\circ}\text{C} \pm 2\text{ }^{\circ}\text{C}$. The laboratory temperature shall be noted and when necessary a temperature correction shall be applied.

It is not recommended that the volumetric method be used for wire with a diameter greater than 5 mm.



a) Arrangement of apparatus at start of test

b) Arrangement of apparatus when measuring the volume of hydrogen released

Figure 3 — Apparatus to determine the coating mass per unit area by gaseous volumetric method

5.2.3.6 Expression of results

The result is determined once the test piece has been tested. The coating mass per unit area depends on the type of alloy. The volume of hydrogen released is directly related to the mass of zinc dissolved by the acid. For a non-alloy zinc coating, the coating mass of zinc per unit area, expressed in grams per square meter, is supplied by the equation ($t = 20\text{ }^{\circ}\text{C}$):

$$m = \frac{2\,717 \cdot V}{\pi \cdot d \cdot l}$$

NOTE 1 mol of hydrogen equals 22,4 l of hydrogen, corresponding to 65,37 g of zinc. A volume V of hydrogen, expressed in millilitres (ml), corresponds to a mass m of zinc, expressed in grams (g).

$$m = \frac{65,37 \cdot V}{22,4 \times 10^3} = 2,918 \cdot V \times 10^{-3}$$

The mass per unit surface (m_A), in g/m² equals:

$$m_A = \frac{2,918 \cdot V \times 10^{-3}}{\pi \cdot d \cdot l \times 10^{-6}} = \frac{2\,918 \cdot V}{\pi \cdot d \cdot l} \text{ g/m}^2$$

where

d is the diameter of the wire without coating, in millimetres (mm);

l is the length of the test piece, in millimetres (mm);

V is the volume of hydrogen released during each of the tests, in millilitres (ml).

In the case of shaped wire, πd is replaced by the circumference of the shape; this is generally obtained from a sketch of the section of the wire.

If the temperature t , in degrees Celsius (°C) is very different from 20 °C, a temperature correction shall be applied for the volume by multiplying the right side of the equation above by the factor:

$$\frac{293}{t + 273}$$

If the atmospheric pressure, P , is not between 987 mbar and 1 040 mbar, the same formula should be multiplied by:

$$\frac{P}{1,014}$$

In practice, tables can be used to read the mass of zinc per square meter of surface of uncoated wire, as a function of the diameter of the wire, the length of the test piece and the volume of hydrogen released.

In the case of the alloy Zn95Al5, the mass of the alloy (m_A) is supplied by the equation:

$$m_A = \frac{2\,601 \cdot V}{\pi \cdot d \cdot l} \text{ g/m}^2$$

This formula is only valid if the mean aluminium content is between 4,5 % and 5,5 %.

The equation above may be used for circular section wire. In the case of shaped wire, the factor πd shall be replaced by the nominal circumference of the shape.

For other zinc alloys, the volumetric method may be applied in so far as a reliable relationship can be established between the gas released and the coating mass per unit area.

5.3 Dipping test

5.3.1 Principle

The test consists of immersing a wire sample for a given period once or several times consecutively in a saturated copper sulfate solution which gradually dissolves the zinc coating and reveals the defects in the continuity of this coating.

The dipping test is solely intended to reveal any significant eccentricity defect in the coating or any other significant uniformity defect which could exist even if the mass of zinc per unit of surface area complies with the mass requirements for the coating.

5.3.2 Reagents

5.3.2.1 Saturated copper sulfate solution, prepared from copper sulfate crystals ($\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$) "in the pure for analysis state" in a proportion of 314 g of salts to 1 l of deionized water at a temperature of $20\text{ }^\circ\text{C} \pm 2\text{ }^\circ\text{C}$.

The solution shall be prepared completely from cold. The liquid shall under no circumstances be heated, even to complete the dissolving process.

To prevent this operation from taking too long, the procedure may be applied as follows.

- The salts to be dissolved are crushed then reduced bit by bit by successive amounts of the water used.
- Once the salts have dissolved completely, the various solutions which have been prepared separately are mixed together and stirred.
- A small quantity of salt shall remain undissolved at the bottom of the container as proof of the state of saturation.

The solution shall be neutralized using an excess of chemically pure copper oxide (1 g per litre of solution), and then the solution shall be left to rest for at least 24 h before decanting for use.

5.3.3 Preparation of test piece

The test piece shall consist of a piece of wire approximately 250 mm long, straightened by hand to a greater or lesser degree. This test piece shall be completely degreased using benzene or any other suitable degreasing solvent. It is then rinsed in distilled water and wiped with a clean piece of cotton wool. After degreasing, the wire shall only be held at the end which is not to be dipped. In the case of a corroded wire, or if other chemical substances remain present on the surface of the wire after degreasing (for example, chromate or phosphates), the wire shall first be dipped in a 0,2 % sulfuric acid solution for 15 s and then rinsed.

IMPORTANT — Take into account health and safety aspects for this preparation.

5.3.4 Test procedure

The test shall be performed in a glass container of at least 8 cm internal diameter. It is filled with the reagent, prepared as in 5.3.2, to a depth of at least 10 cm. During the test, the temperature shall be kept at $20\text{ }^\circ\text{C} \pm 2\text{ }^\circ\text{C}$. The real temperature shall be noted.

The test specimen shall be dipped in the reagent for half a minute if the required number of dips is only half a minute. In all other cases, the test sample shall be dipped in the solution for a period of one minute.

During the period of immersion, the test specimens shall be held vertically; the immersed part shall not touch the wall of the container and shall not be moved. After each dip, any deposited but not adhering copper shall be removed by slightly rubbing with cotton wool under running water.

This procedure shall be repeated with additional dips until the sample shows adherent coating of metallic copper for the first time or until the number of dips in Table 3 is reached, whichever is the smallest. After the last dip, the sample shall be rinsed again under running water and dried with cotton wool.

Where Table 3 specifies a dip of half a minute, the dip shall be done after execution of the specified number of one minute dips. The solution used shall be renewed whenever the series of tests carried out has resulted in dissolving a maximum of 5 g of zinc per litre of reagents. In order to save time, several test samples, with a maximum of six, may be dipped at the same time without touching each other.

5.3.5 Interpretation of results

The test sample shall satisfy the test if the number of dips without adherent copper is equal or larger than the prescribed number of dips in Table 3. Any deposit of metallic copper within 25 mm of the cut end shall be discarded.

In case of doubt about the adherence of copper, the remaining zinc may be removed by dissolution in hydrochloric acid. If the copper is not adhering to the steel base but is sticking on top of the zinc surface, it will be removed together with the zinc.

© ISO 2007. All rights reserved.

Bibliography

- [1] ASTM B 750, *Standard Specification for GALFAN (Zinc-5 % Aluminum-Mischmetal) Alloy in Ingot Form for Hot-Dip Coatings*

© ISO 2015

ICS 25.220.40; 77.140.65

Price based on 14 pages