

# INTERNATIONAL STANDARD

# ISO 8130-14

First edition  
2004-05-15

---

---

## Coating powders —

### Part 14: Terminology

*Poudres pour revêtement —  
Partie 14: Terminologie*



Reference number  
ISO 8130-14:2004(E)

© ISO 2004

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2004

The reproduction of the terms and definitions contained in this International Standard is permitted in teaching manuals, instruction booklets, technical publications and journals for strictly educational or implementation purposes. The conditions for such reproduction are: that no modifications are made to the terms and definitions; that such reproduction is not permitted for dictionaries or similar publications offered for sale; and that this International Standard is referenced as the source document.

With the sole exceptions noted above, no other part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 8130-14 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

ISO 8130 consists of the following parts, under the general title *Coating powders*:

- *Part 1: Determination of particle size distribution by sieving*
- *Part 2: Determination of density by gas comparison pycnometer (referee method)*
- *Part 3: Determination of density by liquid displacement pycnometer*
- *Part 4: Calculation of lower explosion limit*
- *Part 5: Determination of flow properties of a powder/air mixture*
- *Part 6: Determination of gel time of thermosetting coating powders at a given temperature*
- *Part 7: Determination of loss of mass on stoving*
- *Part 8: Assessment of the storage stability of thermosetting powders*
- *Part 9: Sampling*
- *Part 10: Determination of deposition efficiency*
- *Part 11: Inclined-plane flow test*
- *Part 12: Determination of compatibility*
- *Part 13: Particle size analysis by laser diffraction*
- *Part 14: Terminology*

.....

# Coating powders —

## Part 14: Terminology

### 1 Scope

This part of ISO 8130 defines special terms used in the field of coating powders.

Other terms and definitions related to paints and varnishes are given in ISO 4618, *Paints and varnishes — Terms and definitions for coating materials*.

### 2 Terms and definitions

#### 2.1

##### **agglomeration**

condition in which individual particles become joined together into larger assemblies

#### 2.2

##### **back ionization**

electrostatic rejection

electrostatic repulsion

dielectric breakdown in an electrostatically deposited powder caused by an excess accumulation of charge

NOTE The phenomenon is associated with the disruption of the layer, leading to surface defects and to the eventual disintegration of the coating.

#### 2.3

##### **charge-to-mass ratio**

ratio of the electric charge on a powder sample to its mass

NOTE A ratio of at least  $10^{-4}$  C · kg<sup>-1</sup> is normally required for acceptable coating performance.

#### 2.4

##### **classification**

division of a powder sample into two fractions, one above, the other below a predetermined particle size

#### 2.5

##### **coating powder**

finely divided particles of resin, either thermoplastic or thermosetting, generally incorporating pigments, fillers (extenders) and additives, and remaining finely divided during storage under suitable conditions, which, after fusion and possibly curing, give a continuous film

#### 2.6

##### **compaction**

agglomeration of particles under pressure

**2.7**

**deposition efficiency**

proportion of the mass of powder deposited on a substrate compared to the mass of powder sprayed

**2.8**

**electrostatic fluidized bed**

apparatus which allows a powder sample to be fluidized and which, at the same time, has a means of electrically charging the powder particles

NOTE The charged powder forms a cloud above the bed and will deposit on an earthed article brought in contact with it.

**2.9**

**electrostatic rejection**

electrostatic repulsion  
See 2.2 back ionization

**2.10**

**electrostatic spraying**

powder application process in which the powder particles are given an electric charge resulting in their attraction to an earthed workpiece

**2.11**

**Faraday cage effect**

prevention of charged particles from entering and properly covering corners or recesses, due to the diversion of electric force lines to more accessible ground points, during electrostatic spraying

**2.12**

**fines**

particles having a size below an accepted minimum value

NOTE The fines are often regarded as the reject portion from a grinding process.

**2.13**

**gelation**

conversion of a molten coating powder into a non-flowing state

NOTE Gelation will occur at the instant the curing process changes the material into a three-dimensional structure.

**2.14**

**gel time**

time taken for a specified volume of coating powder to become non-deformable, under specified conditions, after melting

**2.15**

**hybrid coating powder**

powder product based on the fusion of different resin species in which part or all of the crosslinking reaction occurs between the functional groups of the resins

**2.16**

**impact fusion**

tendency of finely divided powder particles to fuse when in high-speed contact with other particles in the application equipment during the spraying process

**2.17**

**inclined-plate flow**

inclined-plane flow

measurement of the flow characteristics of a molten thermosetting coating powder down a plane inclined at a set angle to the horizontal

**2.18****incompatibility**

tendency of the mixing of two different coating powders to result in the deterioration of the surface quality of the final coating

**2.19****lower explosion limit**

minimum explosion concentration

concentration of coating powder in a mixture of powder and air, below which self-propagation of flames is not probable

NOTE The lower explosion limit is expressed in  $\text{g} \cdot \text{m}^{-3}$ .

**2.20****melt flow**

gravimetric movement of material liquified by heat

**2.21****obscuration**

percentage or fraction of incident light that is attenuated due to extinction (scattering and/or absorption) by the particles during a laser diffraction measurement

**2.22****oversize**

particles having a size above a stated maximum value

NOTE The oversize is often regarded as a reject portion from the grinding process.

**2.23****particle size**

linear dimensions of particles of coating powders

NOTE 1 The particle size is usually quoted as a mean value.

NOTE 2 Coating powder particles are irregular in shape and, consequently, size data will only have any value if qualified by reference to the specific method of measurement.

**2.24****particle size distribution**

spread of particle sizes in a given sample of powder, expressed as a sequence of percentage masses, or volumes, of particles lying between given sizes

**2.25****powder blocking**

agglomeration of coating powder so as to render it unsuitable for application

**2.26****powder coating**

protective and/or decorative coating formed by the application of a coating powder to a substrate and fusion (and curing, if necessary) to give a continuous film

**2.27****powder flow**

pourability

ability of a dry powder to flow or to be poured

**2.28****powder flow rate**

mass of powder flowing in a given time across a given boundary

NOTE For example, this may be through a tube of known diameter or through a given opening in a vessel.

**2.29**

**reclaimed powder**

powder which has been sprayed but not deposited and, subsequently, captured for reuse

**2.30**

**storage stability**

ability of coating powders to maintain satisfactory physical and chemical properties when stored for a specific time under appropriate conditions

**2.31**

**tribo-charging**

means of applying an electric charge to a coating powder by friction rather than by the use of an electrostatic generator





---

---

**ICS 87.040**

Price based on 4 pages