
**Cylindrical cork stoppers — Physical
tests —**

**Part 1:
Determination of dimensions**

*Bouchons cylindriques en liège — Essais physiques —
Partie 1: Détermination des dimensions*



Reference number
ISO 9727-1:2007(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9727-1 was prepared by Technical Committee ISO/TC 87, *Cork*.

This first edition of ISO 9727-1, together with the other parts of ISO 9727:2007, cancels and replaces ISO 9727:1991, which has been technically revised.

ISO 9727 consists of the following parts, under the general title *Cylindrical cork stoppers — Physical tests*:

- *Part 1: Determination of dimensions*
- *Part 2: Determination of mass and apparent density for agglomerated cork stoppers*
- *Part 3: Determination of humidity content*
- *Part 4: Determination of dimensional recovery after compression*
- *Part 5: Determination of extraction force*
- *Part 6: Determination of liquid tightness*
- *Part 7: Determination of dust content*

© 2010 International Organization for Standardization

Cylindrical cork stoppers — Physical tests —

Part 1: Determination of dimensions

1 Scope

This part of ISO 9727 specifies a test method for determining the dimensions of cylindrical cork stoppers, namely diameter, length and, in some cases, ovalisation.

It is applicable to all types of cylindrical cork stoppers as defined in ISO 633, ready for use or semi-worked.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 633, *Cork — Vocabulary*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 633 and the following apply.

3.1

ovalisation

⟨natural cork stoppers⟩ difference between measurements of diameter carried out along the perpendicular and along the parallel to the cork growth layer

4 Apparatus

4.1 Vernier gauge, with a constant contact force and a maximum resolution of 0,05 mm, or any other device allowing the same precision to be reached.

5 Test conditions

5.1 Environment

The test shall be carried out in an environment with the following characteristics:

- temperature 21 °C ± 4 °C;
- relative humidity of air 60 % ± 20 %.

5.2 Cork stoppers

5.2.1 Temperature

At the beginning of the test, confirm that the stoppers of the test sample are at a temperature of $21\text{ °C} \pm 4\text{ °C}$.

5.2.2 Humidity

At the beginning of the test, confirm that the stoppers of the test sample are at a humidity of $6\% \pm 2\%$.

When the humidity is not between 4 % and 8 %, the result of the humidity obtained shall be referred to in the test report.

6 Sampling

From each lot, take the amount of stoppers that correspond to the sampling plan previously agreed between the interested parties.

Stoppers from the sample shall not show visible defects that may interfere with the performance of the measurement, namely:

- stoppers with an abnormal shape (asymmetric, truncated, bevel);
- stoppers with gutters or belly irregularities.

7 Procedure

Before testing, each stopper shall be numerated.

7.1 Determination of diameter

7.1.1 Natural corkwood stoppers

On each stopper of the test sample and using the vernier gauge or any other device allowing the same precision (4.1) to be reached, measure the diameter at half the distance between ends and following the parallel to the growth layers of cork, in millimetres. Register the value obtained. Repeat the procedure following the perpendicular to the growth layers of cork, in millimetres. Register the value obtained.

7.1.2 Agglomerated cork stoppers and stoppers “1+1” (a disc on each end)

On each stopper of the test sample and using the vernier gauge or any other device allowing the same precision (4.1) to be reached, measure the diameter at half the distance between ends, in millimetres. Register the value obtained (only one measurement per stopper).

7.1.3 Agglomerated cork stoppers with one or several discs on the same end

On each stopper of the test sample and using the vernier gauge or any other device allowing the same precision (4.1) to be reached, measure the diameter, in millimetres, at the limit line between the agglomerated body and disc(s), at the glued surface. Register the value obtained (only one measurement per stopper).

7.2 Determination of length

On each stopper of the test sample and using the vernier gauge or any other device allowing the same precision (4.1) to be reached, measure the length, in millimetres. Carry out the measurement by introducing the stopper between stands of the vernier gauge, in such a way that the central axis of the stopper goes through the stand of the vernier gauge. Register the value obtained.

8 Results

8.1 Diameter

8.1.1 Natural cork stoppers

For each stopper, calculate the arithmetic average of both measurements taken. Express the result in millimetres, rounded off to the nearest tenth. The final test result is the arithmetic average of the results obtained with each stopper of the test sample, expressed in millimetres rounded off to 0,1, and also the standard deviation, the maximum and the minimum results rounded off to 0,1.

8.1.2 Other stoppers

For each stopper, the diameter is expressed in millimetres, rounded off to the nearest tenth. The final test result is the arithmetic average of the results obtained with each stopper of the test sample, expressed in millimetres, rounded off to 0,1, and also the standard deviation, the maximum and the minimum results rounded off to 0,1.

8.2 Length

For each stopper, the length is expressed in millimetres, rounded off to the nearest tenth. The final test result is the arithmetic average of the results obtained with each stopper of the test sample, expressed in millimetres, rounded off to 0,1, and also the standard deviation, the maximum and the minimum results rounded off to 0,1.

8.3 Ovalisation

For each natural cork stopper, calculate the difference between the two measurements taken. Express the result in millimetres, rounded off to the nearest tenth. The final test result is the arithmetic average of the result obtained with each stopper of the test sample, expressed in millimetres, rounded off to 0,1, and also the standard deviation, the maximum and the minimum results rounded off to 0,1.

9 Test report

The test report shall include the following information:

- a) a reference to this part of ISO 9727;
- b) complete identification of the sample, including its type and origin;
- c) sampling report;
- d) results obtained;
- e) any deviation from this part of ISO 9727 that may have affected the results.

ICS 55.100; 79.100

Price based on 3 pages