

INTERNATIONAL STANDARD

ISO 9749

First edition
2000-12-15

Aerospace — Stud-ends, in corrosion-resistant steel, swaged on aircraft control wire rope — Dimensions and loads

Aéronautique et espace — Embouts tendeurs, en acier résistant à la corrosion, à sertir sur câbles de commande d'aéronefs — Dimensions et charges



Reference number
ISO 9748:2000(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 9749 was prepared by Technical Committee ISO/TC 20, *Aircraft and space vehicles*, Subcommittee SC 12, *Mechanical system parts*.

Annex A forms a normative part of this International Standard.

.....

Aerospace — Stud-ends, in corrosion-resistant steel, swaged on aircraft control wire rope — Dimensions and loads

1 Scope

This International Standard specifies the characteristics of stud-ends in corrosion-resistant steel swaged on aircraft control wire rope.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 2020-1:1997, *Aerospace — Preformed flexible steel wire rope for aircraft controls — Part 1: Dimensions and loads.*

ISO 8074:1985, *Aerospace — Surface treatment of austenitic stainless steel parts.*

ISO 9761:1999, *Aerospace — Locking clips, in corrosion-resistant steel, for aircraft control wire rope turnbuckles — Dimensions.*

ISO 10955:1999, *Aerospace — End fittings and turnbarrels for aircraft control wire rope — Technical specification.*

ISO 13715:2000, *Technical drawings — Edges of undefined shape — Vocabulary and indication on drawings.*

EN 2465—¹⁾, *Aerospace series — Steel FE-PA11 — Softened — Bars $D_e \leq 100$ mm.²⁾*

SAE AMS 2431/6A, *Peening Media, Glass Shot.*

SAE AMS 5639G, *Steel, Corrosion Resistant, Bars, Wire, Forgings, Tubing, and Rings, 19Cr 10Ni, Solution Heat Treated.*

SAE AMS 5641F, *Steel, Corrosion Resistant, Bars, Wire, and Forgings, 18.5Cr 10Ni 0.22Se Free-Machining; Swaging or Upsetting, Solution Heat Treated.*

3 Configuration, dimensions, loads and masses







Configuration, dimensions, loads and masses shall be in accordance with Figure 1 and Table 1.

Stud-ends should be manufactured from a hexagonal bar (type 1); however, where bars of hexagonal cross section are difficult to obtain, they may be produced from milled flats (type 2).

¹⁾ To be published.

²⁾ AECMA.

Dimensions in millimetres/Surface roughness in micrometres



- a Thread
- b Pitch diameter
- c Marking
- d Slot for locking clip in accordance with ISO 9761
- e Groove marking thread on left only; the bottom of the groove shall not reach the across flat.

Figure 1

Table 1

Dimensions in millimetres

Wire rope		Thread ^a	D ₁		D ₂		D ₃	D ₄	D ₅	D ₆	D ₇	L ₁		L ₂	L ₃	L ₄	L ₅	L ₆	L ₇		M	P		Masse g/piece	Minimum breaking load ^b kN
Code	Nom. diam. ^b		nom.	lim. dev.	min.	max.	0 $-0,12$	$+0,12$ 0	$+0,25$ 0	0 $-0,15$	H13	Code	± 1	$\pm 0,5$	$\pm 0,5$	$\pm 0,5$	$+0,5$ 0	$+1$ 0	nom.	lim. div.	$\pm 0,5$	min.	max.	\approx	
16	1,6	MJ4 × 0,7 — 4h6h	2,9	0 $-0,1$	5,5	6	4,1	2	2,3	3,5	1,5	S	57	27,5	35	8	29	26	25	$+1$ 0	5	3,26	3,36	4,6	2,15
24	2,4	MJ5 × 0,8 — 4h6h	3,8	0 $-0,15$	7,7	8,5	5,6	2,8	3	4,8		S	69	27	42	10	35,5	32	30		7	4,18	4,33	10,2	4,45
32	3,2	MJ6 × 1 — 4h6h	4,6		6,4	3,6	3,9	5,6	S	81		27,5	49	12	43	39	37	5,1	5,27		14,2	8,9			
40	4	MJ7 × 1 — 4h6h	5,6		8,8	9,5	7,5	4,4	4,8	6,4	L	97	49,5	25,5	25,5	8	6,09	6,27	22,1	12,45					
48	4,8	MJ8 × 1 — 4h6h	6,6	$+15$ 0	11,1	12	9,1	5,2	5,6	8	2,5	S	105	27	63	16	56	51	49	10	7,1	7,27	36,6	18,6	
56	5,6	MJ10 × 1,25 — 4h6h	7,8		13,6	14,5	10,9	6	6,5	9,5		S	123	49	70	20	62,5	57	55	12	8,93	9,11	62,3	24,9	
64	6,4	MJ12 × 1,25 — 4h6h	9,8		14,5	15,5	12,6	6,8	7,4	11		S	130	77	24	70	64	62	13	10,91	11,11	92	31,2		

^a In accordance with ISO 5855-2.

^b In accordance with ISO 2020-1.

4 Material

Corrosion-resistant steel (in accordance with annex A).


5 Surface treatment

Passivation (code P) in accordance with ISO 8074 or peening (code G) (in accordance with annex A).

6 Designation

Each stud-end in accordance with this International Standard shall be designated as shown in the following example.

EXAMPLE



Where the following codes are applied for the thread direction:

- code R: right-hand thread;
- code L: left-hand thread.

7 Marking

The marking position shall be in accordance with Figure 1.

In addition to the manufacturer's own marking, each stud-end in accordance with this International Standard shall be marked using the identity block specified in clause 6.

The marking method is at the manufacturer's option.

8 Technical specification

In accordance with ISO 10955.

.....

Annex A (normative)

Correspondence between national standards

This annex establishes a correspondence between different materials and surface treatment standards from certain user countries. Other member bodies are invited to declare their materials and surface treatment standards in this annex.

The materials and processes cited in Tables A.1 and A.2 are considered to be equivalent, assuming that the requirements for stud-ends specified in this International Standard are respected.

Table A.1 — European standards

Code	Material		Surface treatment	
	Family	Standard	Nature	Standard
No code	Corrosion-resistant steel	EN 2465	Passivation	ISO 8074
			Peening	SAE AMS 2431/6A

Table A.2 — U.S. standards

Code	Material		Surface treatment	
	Family	Standard	Nature	Standard
No code	Corrosion-resistant steel	SAE AMS 5639 or SAE AMS 5641	Passivation	ISO 8074
			Peening	SAE AMS 2431/6A

.....

ICS 49.035

Price based on 5 pages
