

INTERNATIONAL
STANDARD

ISO
9862

Second edition
2005-02-15

**Geosynthetics — Sampling and
preparation of test specimens**

Géosynthétiques — Échantillonnage et préparation des éprouvettes



Reference number
ISO 9862:2005(E)

© ISO 2005

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9862 was prepared by the European Committee for Standardization (CEN) in collaboration with Technical Committee ISO/TC 221, *Geosynthetics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 9862:1990), which has been technically revised.

Contents

Page

Foreword.....	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Procedure	1
3.1 Sampling	1
3.1.1 Selection of rolls	1
3.1.2 Cutting	1
3.1.3 Identification of sample.....	1
3.2 Preparation of specimens	1
4 Sampling report	3
Annex A (informative) Recommendation for test samples and test specimens.....	4
Bibliography	5

.....

Foreword

This document (EN ISO 9862:2005) has been prepared by Technical Committee CEN/TC 189 "Geosynthetics", the secretariat of which is held by IBN, in collaboration with Technical Committee ISO/TC 221 "Geosynthetics".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2005, and conflicting national standards shall be withdrawn at the latest by August 2005.

This document supersedes EN 963:1995.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Introduction

Geosynthetics are produced in many different ways, partly using traditional textile procedures, partly using procedures not commonly recognized as textile procedures. Geosynthetics are defined in prEN ISO 10318.

Geosynthetics are typically supplied in rolls.

Whilst sampling should ensure the best possible statistical significance of the average finding and its coefficient of variation, there are practical limits to the possible distribution of samples and specimens over the entire lot and its single units supplied to a construction site.

1 Scope

This document establishes general principles for the sampling of geosynthetics delivered to construction sites, and for the preparation of test specimens from the samples.

The sampling principles are applicable to geosynthetics supplied in rolls.

NOTE EN ISO 186 may be used for products supplied in sheet form.

The specimen-preparation principles are applicable to all geosynthetics.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 10320, *Geotextiles and geotextile-related products — Identification on site (ISO 10320:1999)*.

3 Procedure

3.1 Sampling

3.1.1 Selection of rolls

3.1.1.1 For each product type delivered to a construction site, take samples at frequencies as agreed between the parties involved (see annex A).

3.1.1.2 With the exception of tests made in connection with claims, each roll selected shall appear undamaged and the wrapping, if any, shall be intact.

3.1.2 Cutting

3.1.2.1 Information regarding the number of test specimens, their shape and any requirements shall be obtained from the relevant test standard(s) for all tests to be made on the sample.

3.1.2.2 The first two turns of the roll shall not be used for sampling.

3.1.2.3 Cut from the roll over its full width perpendicular to the machine direction (production direction — roll length direction) the length of the sample necessary to obtain all specimens required, distributed in accordance with the principles in this document (see 3.2).

3.1.2.4 Since specimens shall not contain damaged parts as defined in 3.2.4, either such parts shall be avoided in selecting the sample, or the sample shall be cut large enough to obtain the necessary number of acceptable specimens (except for the case specified in 3.1.1.2).

3.1.3 Identification of sample

Identification of samples shall be in accordance with EN ISO 10320.

3.2 Preparation of specimens

3.2.1 Both during and after sampling, care shall be taken to ensure that the physical condition of the sample remains unchanged prior to testing. For example, samples of clay geosynthetic barriers shall be maintained at the moisture content prevailing at the time of sampling.

3.2.2 If the sample is not to be cut into specimens immediately, it shall be kept in a dry, dark place, free from dust, at ambient temperature and protected against chemical and physical changes.

NOTE 1 The sample may be rolled up but preferably not folded.

NOTE 2 GBR-R samples shall be neither rolled nor folded.

3.2.3 For each type of test, the required number of specimens shall be cut from positions evenly distributed over the full width and length of the sample, but not closer than 100 mm to the edge.

3.2.4 Except for specimens for tests to be made in connection with claims (see 3.1.1.2), specimens shall not contain any dirt, irregular areas, creases, holes or other visible defects of accidental origin produced subsequent to manufacture.

3.2.5 Unless otherwise required in a test standard, for the same type of test, the same longitudinal or transverse position of two or more specimens shall be avoided. If unavoidable (e.g. due to narrow roll width) a note to this effect shall be included in the sampling report.

3.2.6 Except when additional tests are required, the specimens shall be cut along the machine and cross-machine directions. When the test procedure calls for the specimen to be marked with the machine direction, the marking indicating the machine direction on the sample shall be transferred to the specimen, or the specimen shall be kept separate in such a way that there can be no risk of a misunderstanding.

3.2.7 When cutting test specimens reference shall be made to the particular test standards for which the specimens are being prepared. In tests where accuracy of dimensions is of special importance, the specimens may be cut to an oversize and then cut or frayed to the exact dimensions after conditioning.

3.2.8 Appropriate identification markings on the sample shall be transferred to all specimens to ensure correct specimen identification.

3.2.9 If the cutting causes fragments of the geosynthetic to become loose, or if accidental fraying occurs, all loose fragments shall be kept with the specimen until the test is carried out. If the loosening of fragments cannot be avoided and this is likely to influence the test result, the fact that loosening has occurred shall be reported in the sampling report as well as in the test report.

3.2.10 The specimens shall be kept in a dry, dark place free from dust, at ambient temperature and protected against chemical and physical changes until the test is performed.

4 Sampling report

The sampling report shall include the following particulars:

- a) statement that the sampling and preparation of specimens was performed in accordance with this document;
- b) details of any special observations made during the selection, sampling or preparation of specimens, such as:
 - the number and type of defects;
 - loosening of fragments from the geosynthetic;
 - the necessity for taking specimens for the same test in only one longitudinal or transverse position;
- c) details of any deviation from the specified sampling procedure;
- d) date of cutting of the sample, and reference number(s) of the rolls selected.

Annex A (informative)

Recommendation for test samples and test specimens

Test	Reference	Sample length ^a [m]	Number of test specimens required ^b
Thickness	EN ISO 9863-1	1	10
Mass per unit area	EN ISO 9864	1	10
Tensile properties	EN ISO 10319	2	10
Static puncture resistance	EN ISO 12236	2	10
Dynamic puncture resistance	EN 918	2	10
Characteristic opening size	EN ISO 12956	2	5
Permeability normal to the plane	EN ISO 11058	1	5
In-plane flow capacity	EN ISO 12958	2	5
Weathering resistance	EN 12224	3	12
Oxidation resistance	EN ISO 13438	3	12
Hydrolysis resistance	EN 12447	3	12
Chemical resistance	EN 14030	3	12
Microbiological resistance	EN 12225	3	12
^a Length along roll for full production width. ^b These are minimum quantities. Some test methods may require additional test specimens.			

Bibliography

EN ISO 186, *Paper and board — Sampling to determine average quality (ISO 186:2002)*.

prEN ISO 10318, *Geosynthetics - Terms and definitions (ISO/DIS 10318:2000)*

ICS 59.080.70

Price based on 5 pages