



**INTERNATIONAL STANDARD ISO 12137-1:1997**  
**TECHNICAL CORRIGENDUM 1**

Published 1998-12-15

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

## **Paints and varnishes — Determination of mar resistance —**

### **Part 1:** **Method using a curved stylus**

#### **TECHNICAL CORRIGENDUM 1**

*Peintures et vernis — Détermination de la résistance à la détérioration —*

*Partie 1: Méthode utilisant un stylet arrondi*

*RECTIFICATIF TECHNIQUE 1*

Technical Corrigendum 1 to International Standard ISO 12137-1:1997 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

---

*Page 5*

#### **Subclause 9.3**

The test speed given in the third paragraph is incorrect. Replace “30 mm/s to 60 mm/s” by “3 mm/s to 6 mm/s”.