



INTERNATIONAL STANDARD ISO 12947-3:1998
TECHNICAL CORRIGENDUM 1

Published 2002-11-01

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

**Textiles — Determination of the abrasion resistance of fabrics
by the Martindale method —**

**Part 3:
Determination of mass loss**

TECHNICAL CORRIGENDUM 1

Textiles — Détermination de la résistance à l'abrasion des étoffes par la méthode Martindale —

Partie 3: Détermination de la perte de masse

RECTIFICATIF TECHNIQUE 1

Technical Corrigendum 1 to ISO 12947-3:1998 was prepared by Technical Committee ISO/TC 38, *Textiles*.

Page 2

6 Conditioning and testing atmosphere, new text to read:

A standard temperate atmosphere for conditioning and testing textiles shall be used, i.e. a temperature of (20 ± 2) °C and a relative humidity of (65 ± 2) % as defined in ISO 139.

Page 3

7.4.1: change dimension $38 \begin{smallmatrix} +5 \\ 0 \end{smallmatrix}$ to $38,0 \begin{smallmatrix} +0,5 \\ 0 \end{smallmatrix}$

7.4.4: change dimension $38 \begin{smallmatrix} +5 \\ 0 \end{smallmatrix}$ to $38,0 \begin{smallmatrix} +0,5 \\ 0 \end{smallmatrix}$

Page 6

A.2, paragraph 2, line 3:

change dimension $38 \begin{smallmatrix} +0,5 \\ 0 \end{smallmatrix}$ to $38,0 \begin{smallmatrix} +0,5 \\ 0 \end{smallmatrix}$

ICS 59.080.30

Ref. No. ISO 12947-3:1998/Cor.1:2002(E)