



**INTERNATIONAL STANDARD ISO 12947-4:1998**  
**TECHNICAL CORRIGENDUM 1**

Published 2002-11-01

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

**Textiles — Determination of the abrasion resistance of fabrics  
by the Martindale method —**

**Part 4:  
Assessment of appearance change**

**TECHNICAL CORRIGENDUM 1**

*Textiles — Détermination de la résistance à l'abrasion des étoffes par la méthode Martindale —*

*Partie 4: Évaluation du changement d'aspect*

*RECTIFICATIF TECHNIQUE 1*

Technical Corrigendum 1 to ISO 12947-4:1998 was prepared by Technical Committee ISO/TC 38, *Textiles*.

---

*Page 2*

**6 Conditioning and testing atmosphere**, new text to read:

A standard temperate atmosphere for conditioning and testing textiles shall be used, i.e. a temperature of  $(20 \pm 2)$  °C and a relative humidity of  $(65 \pm 2)$  % as defined in ISO 139.

*Page 3*

**7.4.2:** change dimension  $38 \begin{smallmatrix} +5 \\ 0 \end{smallmatrix}$  to  $38,0 \begin{smallmatrix} +0,5 \\ 0 \end{smallmatrix}$

**7.4.4:** change dimension  $38 \begin{smallmatrix} +5 \\ 0 \end{smallmatrix}$  to  $38,0 \begin{smallmatrix} +0,5 \\ 0 \end{smallmatrix}$

*Page 6*

**A.2**, paragraph 2, line 3:

change dimension  $38 \begin{smallmatrix} +0,5 \\ 0 \end{smallmatrix}$  to  $38,0 \begin{smallmatrix} +0,5 \\ 0 \end{smallmatrix}$

---

**ICS 59.080.30**

**Ref. No. ISO 12947-4:1998/Cor.1:2002(E)**

© ISO 2002 – All rights reserved

Published in Switzerland