

INTERNATIONAL STANDARD

ISO 13640

First edition
1999-12-15

Building construction — Jointing products — Specifications for test substrates

*Construction immobilière — Matériaux pour joints — Prescriptions relatives
aux supports d'essais*



Reference number
ISO 13640:1999(E)

© ISO 1999

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 1999

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 734 10 79
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 13640 was prepared by Technical Committee ISO/TC 59, *Building construction*, Subcommittee SC 8, *Jointing products*.

Building construction — Jointing products — Specifications for test substrates

1 Scope

This International Standard specifies the procedures for producing substrates of mortar, glass and anodized aluminium used for testing sealants.

The purpose of these requirements is to ensure the reproducibility of the standardized tests conducted on sealants through the precise definition of both the composition and the method of preparation of the test substrates.

The substrates defined in this International Standard are indicators of the sealant's performance and not substrates which reproduce the characteristics of the construction materials.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 209-1:1989, *Wrought aluminium and aluminium alloys — Chemical composition and forms of products — Part 1: Chemical composition.*

ISO 2143:1981, *Anodizing of aluminium and its alloys — Estimation of loss of absorptive power of anodic oxide coatings after sealing — Dye spot test with prior acid treatment.*

ISO 6707-1:1989, *Building and civil engineering — Vocabulary — Part 1: General terms.*

ISO 6927:1981, *Building construction — Jointing products — Sealants — Vocabulary.*

ISO 7599:1983, *Anodizing of aluminium and its alloys — General specifications for anodic oxide coatings on aluminium.*

EN 196-1:1994, *Methods of testing cement — Part 1: Determination of strength.*

EN 197-1:—¹⁾, *Cement — Composition, specifications and conformity criteria — Part 1: Common cements.*

EN 515:1993, *Aluminium and aluminium alloys — Wrought products — Temper designations*

EN 572-1:1994, *Glass in building — Basic soda lime silicate glass products — Part 1: Definitions and general physical and mechanical properties.*

EN 572-2:1994, *Glass in building — Basic soda lime silicate glass products — Part 2: Float glass.*

3 Terms and definitions

For the purposes of this International Standard, the terms and definitions for sealants given in ISO 6927 and the general construction terms and definitions given in ISO 6701-1 apply.

1) To be published.

4 Test substrates

4.1 Mortar substrates

4.1.1 Dimensions

The substrate dimensions shall be 75 mm × 12 mm × 25 mm.

NOTE The preparation of mortar substrates can be influenced directly by the geometry of the substrate.

4.1.2 Mortar composition

The mortar used for the preparation of the substrates shall be as defined in Table 1.

Table 1 — Mortar composition

Components	Cement (C)	Sand (S)	Water (W)
Nature of components	Cement - EN 197-1CEM I-42,5 ^a	Sand CEN - EN 196-1	Distilled water
Ratio by mass	1	3	W/C = 0,5
^a ENV Portland cement according to EN 197-1 belonging to strength class 42.5, having a high strength in green concrete. ACP or Z45 cements may also be used.			

4.1.3 Preparation of substrates

4.1.3.1 General

The surface of the mortar substrates shall have a sufficient cohesive strength in order to be able to withstand the stresses induced during the tests on the sealants.

The surface in contact with the sealant shall be free from laitance, free from loosely bound sand grains and free from release agent.

Method M1 (see 4.1.3.3) leads to smooth-surface substrates whereas M2 (see 4.1.3.4) leads to rough-surface substrates.

4.1.3.2 Mixing of mortar

The mortar shall be mixed using equipment described in 4.4 of EN 196-1:1994, following the method described in 6.3 of EN 196-1:1994.

4.1.3.3 Preparation of substrates according to method M1

Fill the mould in two layers within 2 min with a vibration frequency of about 3 KHz for each layer. Level and smooth the surface using a trowel.

Condition the substrates at $(20 \pm 1) ^\circ\text{C}$ and $(90 \pm 5) \%$ relative humidity.

Remove the substrates from their moulds 24 h after filling the moulds, and store the substrates for 28 days under distilled water at $(20 \pm 1) ^\circ\text{C}$. Then wet grind the mortar blocks or saw them with a diamond saw under water. Dry them until constant mass.

The resulting surface shall be smooth but may contain a few holes.

4.1.3.4 Preparation of substrates according to method M2

Fill the mould, in one layer, with a small surplus of mortar and shake the mortar using the jolting apparatus (30 jolts) according to EN 196-1.

Store the substrates at (20 ± 1) °C and (90 ± 5) % relative humidity.

Level the mortar 2 h to 3 h after filling the mould to eliminate the laitence and smooth with a trowel. Condition the substrates at (20 ± 1) °C and (90 ± 5) % relative humidity.

About 20 h after filling the mould, brush the surfaces vigorously with a metal brush with repeated backward and forward movements, in the direction of the longest dimension, until the sand grains are exposed.

Remove the substrates from their moulds and store them for 28 days in distilled water at (20 ± 1) °C. Dry until constant mass.

The resulting surface shall be rough and shall not contain any holes.

4.2 Glass substrates

Make glass substrates from clear float glass having a transmission factor of 0,85 for a nominal thickness of $(6,0 \pm 0,1)$ mm in accordance with EN 572-1 and EN 572-2.

For sealants of high modulus, provide adequate reinforcement of the flat glass substrates.

If optical transmission is not a factor in the test standard, then the nominal thickness of the glass may be higher, for example 8 mm.

4.3 Anodized aluminium substrates

4.3.1 Dimensions

Substrate dimensions shall be 75 mm × 12 mm × 5 mm.

4.3.2 Aluminium alloys

The alloys shall have one of the following compositions, in accordance with ISO 209-1:

Al MgSi (number 6060); or

Al Mg_{0,7}Si (number 6063).

Use finishing method T5 or T6 in accordance with EN 515.

4.3.3 Anodization

Carry out anodization in accordance with ISO 7599, with the following details:

- clear anodized aluminium;
- class AA 15 or AA 20;
- sealing index ≤ 2 according to ISO 2143;
- sealing bath additives shall be checked, in accordance with 10.2.1 of ISO 7599:1983.

ICS 91.100.50

Price based on 3 pages

© ISO 1999 – All rights reserved