



**INTERNATIONAL STANDARD ISO 15360-2:2001**  
**TECHNICAL CORRIGENDUM 1**

Published 2007-06-01

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

**Recycled pulps — Estimation of Stickies and Plastics —**  
**Part 2:**  
**Image analysis method**

TECHNICAL CORRIGENDUM 1

*Pâtes recyclées — Estimation des matières collantes et des matières plastiques —*

*Partie 2: Méthode par analyse d'image*

*RECTIFICATIF TECHNIQUE 1*

Technical Corrigendum 1 to ISO 15360-2:2001 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 5, *Test methods and quality specifications for pulps*.

---

Page 3

In 5.4, add the following note.

NOTE The calibration method uses dark spots on a white background but this test detects light contraries on the dark background. The effect of this difference is yet unknown.

Replace 5.12 with the following (change underlined).

**5.12 Filter washing device** (see 10.4.2) to wash the filter with a gentle stream of water at a pressure of about 0,1 MPa (1 bar ), flow rate of about 10 l/min and distance of delivery tip from filter of about 180 mm.

*Page 12, Annex B*

Add the following note at the end of Annex B.

NOTE The calibration method uses dark spots on a white background but this test detects light contraries on the dark background. The effect of this difference is yet unknown.