
**Magnesium and magnesium alloys —
Magnesium alloy ingots and castings**

AMENDMENT 1: Additional alloys

*Magnésium et alliages de magnésium — Lingots et pièces moulées en
alliage de magnésium*

AMENDEMENT 1: Alliages supplémentaires



Reference number
ISO 16220:2005/Amd.1:2007(E)

© ISO 2007

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 16220:2005 was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 5, *Magnesium and alloys of cast or wrought magnesium*.

Introduction

The purpose of ISO 16220:2005/Amd.1:2007 is to include two new commercial alloys based on the combination of rare earth metals, gadolinium and zirconium as alloying elements.

.....

Magnesium and magnesium alloys — Magnesium alloy ingots and castings

AMENDMENT 1: Additional alloys

Page 5, Table 1 — Chemical composition of magnesium alloy ingots

Replace the existing Table 1 with the following new Table 1, where two new grades are added: ISO-MgAl4RE4 and ISO-MgRE3Gd1Zr.

NOTE 1 The new grades ISO-MgAl4RE4 and ISO-MgRE3Gd1Zr are not included in EN 1753.

Page 6, Table 2 — Chemical composition of magnesium alloy castings

Replace the existing Table 2 with the following new Table 2, where two new grades are added: ISO-MgAl4RE4 and ISO-MgRE3Gd1Zr.

NOTE 2 The new grades ISO-MgAl4RE4 and ISO-MgRE3Gd1Zr are not included in EN 1753.

Page 7, Table 3 — Mechanical properties of sand-cast magnesium alloys

Replace the existing Table 3 with the following new Table 3, where the new grade ISO-MgRE3Gd1Zr is added at the bottom of the table.

NOTE 3 The new grade ISO-MgRE3Gd1Zr is not included in EN 1753.

Page 7, Table 4 — Mechanical properties of permanent-mould cast magnesium alloys

Replace the existing Table 4 with the following new Table 4, where the new grade ISO-MgRE3Gd1Zr is added at the bottom of the table.

NOTE 4 The new grade ISO-MgRE3Gd1Zr is not included in EN 1753.

Page 8, Table 5 — Mechanical properties of pressure die cast magnesium alloys

Replace the existing Table 5 with the following new Table 5, where the new grade ISO-MgAl4RE4 is added.

NOTE 5 The new grade ISO-MgAl4RE4 is not included in EN 1753.

Table 1 — Chemical composition of magnesium alloy ingots

Alloy group	Material designation		Composition % by mass																RE/Al ratio	
	In accordance with ISO 2092:1981 ^a	In accordance with EN 1753	Min. or max.	Mg	Al	Zn	Mn ^b	RE ^c	Zr	Ag	Y	Gd	Li	Si	Fe	Cu	Ni	Others each		
MgAlZn	ISO-MgAl9Zn1 (A)	ISO-MB21120	min.	Rem.	8,5	0,45	0,17	-	-	-	-	-	-	-	0,08	0,004	0,025	0,001	-	
			max.		9,5	0,9	0,40	-	-	-	-	-	-	-	-	0,04	0,004	0,025	0,001	0,01
				Rem.	8,0	0,3	0,1	-	-	-	-	-	-	-	-	0,3	0,03	0,20	0,01	0,05
MgAlMn	ISO-MgAl9Zn1 (B)	ISO-MB21121	min.	Rem.	10,0	1,0	0,50	-	-	-	-	-	-	-	0,05	0,004	0,008	0,001	0,01	-
			max.		1,7	0,35	0,60	-	-	-	-	-	-	-	0,05	0,004	0,008	0,001	0,01	-
				Rem.	2,5	0,20	0,60	-	-	-	-	-	-	-	-	0,05	0,004	0,008	0,001	0,01
MgAlSi	ISO-MgAl5Mn	ISO-MB21220	min.	Rem.	4,5	-	0,28	-	-	-	-	-	-	-	0,08	0,004	0,008	0,001	0,01	-
			max.		5,3	0,30	0,50	-	-	-	-	-	-	-	0,08	0,004	0,008	0,001	0,01	-
				Rem.	5,6	0,30	0,26	-	-	-	-	-	-	-	-	0,08	0,004	0,008	0,001	0,01
MgAlRE ^d	ISO-MgAl6Mn	ISO-MB21230	min.	Rem.	6,4	0,30	0,50	-	-	-	-	-	-	-	0,7	0,004	0,008	0,001	0,01	-
			max.		1,9	0,2	0,6	-	-	-	-	-	-	-	1,2	0,004	0,008	0,001	0,01	-
				Rem.	2,5	0,20	0,6	-	-	-	-	-	-	-	0,7	0,004	0,008	0,001	0,01	-
MgZnCu	ISO-MgAl4Si	ISO-MB21320	min.	Rem.	3,7	-	0,2	-	-	-	-	-	-	-	0,7	0,004	0,008	0,001	0,01	-
			max.		4,8	0,20	0,6	-	-	-	-	-	-	-	1,2	0,004	0,008	0,001	0,01	-
				Rem.	3,6	0,20	0,15	3,6	-	-	-	-	-	-	0,08	0,004	0,008	0,001	0,01	0,9
MgZnREZr ^d	ISO-MgAl4RE4	ISO-MB21410	min.	Rem.	4,4	0,20	0,50	4,6	-	-	-	-	-	-	0,08	0,004	0,008	0,001	0,01	-
			max.		0,2	5,5	0,25	-	-	-	-	-	-	-	0,20	0,05	2,4	0,01	0,01	-
				Rem.	0,2	6,5	0,75	-	-	-	-	-	-	-	0,20	0,05	3,0	0,01	0,01	-
MgREAgZr ^e	ISO-MgZn4RE1Zr	ISO-MB35110	min.	Rem.	-	3,5	-	1,0	1,0	-	-	-	-	-	0,01	0,01	0,03	0,005	0,01	-
			max.		-	5,0	0,15	1,75	1,0	-	-	-	-	-	0,01	0,01	0,03	0,005	0,01	-
				Rem.	-	2,0	-	2,4	4,0	1,0	-	-	-	-	0,01	0,01	0,03	0,005	0,01	-
MgYREZr ^{f,g}	ISO-MgRE3Zn2Zr	ISO-MB65120	min.	Rem.	-	0,2	0,15	3,0	1,0	2,0	-	-	-	0,01	0,01	0,03	0,005	0,01	-	
			max.		-	0,2	0,15	3,0	1,0	3,0	-	-	-	-	0,01	0,01	0,03	0,005	0,01	-
				Rem.	-	0,2	0,15	1,5	0,1	1,3	1,0	1,7	-	-	-	0,01	0,01	0,05	0,005	0,01
MgYREZr ^{f,g}	ISO-MgY5RE4Zr	ISO-MB95310	min.	Rem.	-	0,20	0,15	4,0	1,0	-	4,75	-	-	0,20	0,01	0,01	0,03	0,005	0,01	-
			max.		-	0,20	0,15	4,0	1,0	-	5,5	-	-	-	0,20	0,01	0,03	0,005	0,01	-
				Rem.	-	0,20	0,15	2,4	4,4	1,0	3,7	-	-	-	0,20	0,01	0,03	0,005	0,01	-
MgREAgZr ^h	ISO-MgY4RE3Zr	ISO-MB95320	min.	Rem.	-	0,20	0,15	4,4	1,0	-	4,3	-	-	0,01	0,01	0,03	0,005	0,01	-	
			max.		-	0,20	0,15	4,4	1,0	-	4,3	-	-	-	0,01	0,01	0,03	0,005	0,01	-
				Rem.	-	0,20	0,15	2,6	3,1	0,1	-	-	1,0	-	-	0,010	0,01	0,0020	0,01	-

^a Withdrawn in 2002.
^b For maximum manganese content, see Annex B.
^c RE = rare earth metals.
^d Cerium-rich.
^e Neodymium-rich.
^f Neodymium- and heavy RE-rich.
^g Improved corrosion resistance may be obtained by reducing the maximum manganese content to 0,03 %, the maximum iron content to 0,01 %, the maximum copper content to 0,02 % and the maximum zinc + silver content to 0,2 %.
^h Neodymium is 2,6 % to 3,1 %; other rare earth metals may also be present to a total maximum of 0,4 %. These RE shall principally be cerium, lanthanum and praseodymium.

Table 2 — Chemical composition of magnesium alloy castings

Alloy group	Material designation		Composition % by mass														RE/Al ratio			
	In accordance with ISO 2092:1981 ^a	In accordance with EN 1753	Min. or max.	Casting process	Mg	Al	Zn	Mn ^b	RE ^c	Zr	Ag	Y	Gd	Li	Si	Fe		Cu	Ni	Others each
MgAlZn	ISO-MgAl9Zn1(A)	ISO-MC21120	min. max.	D	Rem.	8,3 9,5	0,35 0,9	0,15 0,50	-	-	-	-	-	-	0,08	0,005	0,025	0,001	-	0,032
	ISO-MgAl9Zn1(A)	ISO-MC21120	min. max.	S, K, L	Rem.	8,3 9,7	0,40 1,0	0,17 0,35	-	-	-	-	-	-	0,20	0,005	0,030	0,001	-	0,032
	ISO-MgAl9Zn1(B)	ISO-MC21121	min. max.	D, S, K, L	Rem.	8,0 10,0	0,3 1,0	0,1 0,6	-	-	-	-	-	-	0,3	0,03	0,20	0,01	-	-
	ISO-MgAl2Mn	ISO-MC21210	min. max.	D	Rem.	1,6 2,5	0,20 0,20	0,33 0,70	-	-	-	-	-	-	0,08	0,004	0,008	0,001	-	0,012
MgAlMn	ISO-MgAl5Mn	ISO-MC21220	min. max.	D	Rem.	4,4 5,3	0,26 0,30	0,60	-	-	-	-	-	-	0,08	0,004	0,008	0,001	-	0,015
	ISO-MgAl6Mn	ISO-MC21230	min. max.	D	Rem.	5,5 6,4	0,24 0,30	0,60	-	-	-	-	-	0,08	0,005	0,008	0,001	-	0,021	
	ISO-MgAl2Si	ISO-MC21310	min. max.	D	Rem.	1,8 2,5	0,18 0,20	0,70	-	-	-	-	-	0,7 1,2	0,004	0,008	0,001	-	0,022	
MgAlSi	ISO-MgAl4Si	ISO-MC21320	min. max.	D	Rem.	3,5 4,8	0,18 0,20	0,70	-	-	-	-	-	0,5 1,2	0,004	0,008	0,001	-	0,022	
	ISO-MgAl4RE4	ISO-MC21410	min. max.	D	Rem.	3,5 4,5	0,15 0,20	0,50 0,75	3,5 4,5	-	-	-	-	0,08	0,005	0,008	0,001	-	0,8	
MgZnCu	ISO-MgZn6Cu3Mn	ISO-MC32110	min. max.	S, K, L	Rem.	0,2	5,5 6,5	0,25 0,75	-	-	-	-	-	-	0,20	0,05	2,4 3,0	0,01	0,01	-
	ISO-MgZn4RE1Zr	ISO-MC35110	min. max.	S, K, L	Rem.	-	3,5 5,0	0,15 0,75	0,75 1,75	0,4 1,0	-	-	-	0,01	0,01	0,03	0,005	0,005	0,01	-
MgZnREZr ^e	ISO-MgRE3Zn2Zr	ISO-MC65120	min. max.	S, K, L	Rem.	-	2 3	1,5 4,0	2,5 4,0	0,4 1,0	-	-	-	0,01	0,01	0,03	0,005	0,005	0,01	-
	ISO-MgAg2RE2Zr	ISO-MC65210	min. max.	S, K, L	Rem.	-	0,2 0,2	0,15 0,15	2 3	1,0 3,0	-	-	-	0,01	0,01	0,03	0,005	0,005	0,01	-
MgREAgZr ^f	ISO-MgRE2Ag1Zr	ISO-MC65220	min. max.	S, K, L	Rem.	-	0,2	0,15	3,0 3,0	1,0 1,7	-	-	-	0,01	0,01	0,10	0,005	0,005	0,01	-
	ISO-MgY9RE4Zr	ISO-MC95310	min. max.	S, K, L	Rem.	-	0,2	0,15	4,0 4,0	1,0 1,0	4,75 5,5	-	0,2	0,01	0,01	0,03	0,005	0,005	0,01	-
MgYREZr ^{g, h}	ISO-MgY4RE3Zr	ISO-MC95320	min. max.	S, K, L	Rem.	-	0,2	0,15	2,4 4,4	1,0 1,0	3,7 4,3	-	0,2	0,01	0,01	0,03	0,005	0,005	0,01	-
	ISO-MgRE3Gd1Zr	ISO-MB65410	min. max.	S, K, L	Rem.	-	0,20 0,50	0,4 0,03	2,6 3,1	0,4 1,0	-	1,0 1,7	-	-	-	0,010	0,01	0,0020	0,01	-

^a Withdrawn in 2002.

^b For maximum manganese content, see Annex B.

^c RE = rare earth metals.

^d If the minimum Mn limit is not met.

^e Cerium-rich.

^f Neodymium-rich.

^g Neodymium- and heavy RE-rich.

^h Improved corrosion resistance may be obtained by reducing the maximum manganese content to 0,03 %, the maximum iron content to 0,01 %, the maximum copper content to 0,02 % and the maximum zinc + silver content to 0,2 %.

ⁱ Neodymium is 2,6 % to 3,1 %; other rare earth metals may also be present to a total maximum of 0,4 %. These RE shall principally be cerium, lanthanum and praseodymium.

Table 3 — Mechanical properties of sand-cast magnesium alloys

Alloy group	Material designation		Temper designation	Tensile strength R_m N/mm ² min.	0,2% proof stress $R_{p0,2}$ N/mm ² min.	Elongation ΔL % min.	Brinell hardness HBW ^a
	In accordance with ISO 2092:1981 ^b	In accordance with EN 1753					
MgAlZn	ISO-MgAl9Zn1(A)	ISO-MC21120	F	160	90	2	50 to 65
			T4	240	110	6	55 to 70
			T6	240	150	2	60 to 90
MgZnCu	ISO-MgZn6Cu3Mn	ISO-MC32110	T6	195	125	2	55 to 65
MgZnREZr	ISO-MgZn4RE1Zr	ISO-MC35110	T5	200	135	2,5	55 to 70
	ISO-MgRE3Zn2Zr	ISO-MC65120	T5	140	95	2,5	50 to 60
MgREAgZr	ISO-MgAg2RE2Zr	ISO-MC65210	T6	240	175	2	70 to 90
	ISO-MgRE2Ag1Zr	ISO-MC65220	T6	240	175	2	70 to 90
MgYREZr	ISO-MgY5RE4Zr	ISO-MC95310	T6	250	170	2	80 to 90
	ISO-MgY4RE3Zr	ISO-MC95320	T6	220	170	2	75 to 90
MgREGdZr	ISO-MgRE3Gd1Zr	ISO-MC65410	T6	248 ^c	145 ^c	2	70 to 90

NOTE 1 Values given are for separately cast test pieces. The properties of the casting are expected to be 70 % of the values from separately cast test pieces, for thicknesses of casting up to 20 mm, except for ISO-MgRE3Gd1Zr where samples cut from castings are the same as separately cast test bars, see footnote c.

NOTE 2 1 N/mm² is equivalent to 1 MPa.

^a These values are for guidance only.

^b Withdrawn in 2002.

^c This value applies to both separately cast test pieces and samples cut from castings, for thicknesses up to 30 mm.

Table 4 — Mechanical properties of permanent-mould cast magnesium alloys

Alloy group	Material designation		Temper designation	Tensile strength R_m N/mm ² min.	0,2% proof stress $R_{p0,2}$ N/mm ² min.	Elongation ΔL % min.	Brinell hardness HBW ^a
	In accordance with ISO 2092:1981 ^b	In accordance with EN 1753					
MgAlZn	ISO-MgAl9Zn1(A)	ISO-MC21120	F	160	110	2	55 to 70
			T4	240	120	6	55 to 70
			T6	240	150	2	60 to 90
MgZnCu	ISO-MgZn6Cu3Mn	ISO-MC32110	T6	195	125	2	55 to 65
MgZnREZr	ISO-MgZn4RE1Zr	ISO-MC35110	T5	210	135	3	55 to 70
	ISO-MgRE3Zn2Zr	ISO-MC65120	T5	145	100	3	50 to 60
MgREAgZr	ISO-MgAg2RE2Zr	ISO-MC65210	T6	240	175	3	70 to 90
	ISO-MgRE2Ag1Zr	ISO-MC65220	T6	240	175	2	70 to 90
MgYREZr	ISO-MgY5RE4Zr	ISO-MC95310	T6	250	170	2	80 to 90
	ISO-MgY4RE3Zr	ISO-MC95320	T6	220	170	2	75 to 90
MgREGdZr	ISO-MgRE3Gd1Zr	ISO-MC65410	T6	248 ^c	145 ^c	2	70 to 90

NOTE 1 Values given are for separately cast test pieces. The properties of the casting are expected to be 70% of the values from separately cast test pieces for thicknesses of casting up to 20 mm, except for ISO-MgRE3Gd1Zr where samples cut from castings are the same as separately cast test bars, see footnote c.

NOTE 2 1 N/mm² is equivalent to 1 MPa.

^a These values are for guidance only.

^b Withdrawn in 2002.

^c This value applies to both separately cast test pieces and samples cut from castings, for thicknesses up to 30 mm.

Table 5 — Mechanical properties of pressure die cast magnesium alloys

Alloy group	Material designation		Temper designation	Tensile strength R_m N/mm ²	0,2% proof stress $R_{p0,2}$ N/mm ²	Elongation ΔL %	Brinell hardness HBW
	In accordance with ISO 2092:1981 ^a	In accordance with EN 1753					
MgAlZn	ISO-MgAl9Zn1(A)	ISO-MC21120	F	200 to 260	140 to 170	1 to 9	65 to 85
MgAlMn	ISO-MgAl2Mn	ISO-MC21210	F	150 to 220	80 to 100	8 to 25	40 to 55
	ISO-MgAl5Mn	ISO-MC21220	F	180 to 230	110 to 130	5 to 20	50 to 65
	ISO-MgAl6Mn	ISO-MC21230	F	190 to 250	120 to 150	4 to 18	55 to 70
MgAlSi	ISO-MgAl2Si	ISO-MC21310	F	170 to 230	110 to 130	4 to 14	50 to 70
	ISO-MgAl4Si	ISO-MC21320	F	200 to 250	120 to 150	3 to 12	55 to 80
MgAlRE ^b	ISO-MgAl4RE4	ISO-MC21410	F	220 to 260	130 to 160	6 to 15	60 to 80
NOTE 1 The values given in this table are for guidance only, see 4.2.							
NOTE 2 Values given are for separately cast test pieces of 20 mm ² cross-sectional area and a minimum thickness of 2 mm. For MgAlRE see footnote b.							
NOTE 3 1 N/mm ² is equivalent to 1 MPa.							
^a Withdrawn in 2002.							
^b Values given are from separately cast test bars produced in a cold chamber machine using a multicavity die giving 6 mm round tensile test bars ($L_0 = 50$ mm).							

ICS 77.150.20

Price based on 5 pages