

---

---

**Plastics — Thermoplastic polyester  
(TP) moulding and extrusion  
materials —**

**Part 1:  
Designation system and basis for  
specifications**

*Plastiques — Matériaux polyesters thermoplastiques (TP) pour  
moulage et extrusion —*

*Partie 1: Système de désignation et base de spécification*





**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Ch. de Blandonnet 8 • CP 401  
CH-1214 Vernier, Geneva, Switzerland  
Tel. +41 22 749 01 11  
Fax +41 22 749 09 47  
copyright@iso.org  
www.iso.org

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>2</b>
<b>4 Designation system</b> .....	<b>2</b>
4.1 General .....	2
4.2 Data block 1 .....	2
4.3 Data block 2 .....	3
4.4 Data block 3 .....	4
4.5 Data block 4 .....	5
4.5.1 General .....	5
4.5.2 Viscosity number .....	5
4.5.3 Tensile modulus of elasticity .....	6
4.6 Data block 5 .....	7
<b>5 Examples of designations</b> .....	<b>7</b>
5.1 Designation only .....	7
5.2 Designation transformed into a specification .....	9
<b>Annex A (normative) Designation of thermoplastic polyesters</b> .....	<b>10</b>
<b>Bibliography</b> .....	<b>13</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This first edition of ISO 20028-1 cancels and replaces ISO 7792-1:2012, which has been technically revised to introduce a new designation system.

The revised designation system is published under a new ISO number, as many existing documents refer to ISO 7792-1. If the existing ISO 7792-1 would be replaced by the new designation system, these documents would refer to the incorrect designation system.

In order to give users time to switch from ISO 7792-1 to ISO 20028-1, any designation system according to ISO 7792-1 is to be phased out in 5 to 10 years.

A list of all parts in the ISO 20028 series can be found on the ISO website.

## Introduction

ISO 7792-1 is complex and does not fit with daily practice anymore. In practice, ISO 1043 and ISO 11469 are, in combination, “improperly” being used as a designation system for, for example, marking. The aim of this revision is to simplify the data block system and to connect more to ISO 1043 and ISO 11469, where the first two blocks are used for generic identification and marking of products.



# Plastics — Thermoplastic polyester (TP) moulding and extrusion materials —

## Part 1: Designation system and basis for specifications

### 1 Scope

This document establishes a system of designation for thermoplastic polyester (TP) material, which can be used as the basis for specifications. It covers polyester homopolymers for moulding and extrusion based on poly(ethylene terephthalate) (PET), poly(butylene terephthalate) (PBT), poly(cyclohexylenedimethylene terephthalate) (PCT), poly(ethylene naphthalate) (PEN), poly(butylene naphthalates) (PBN) and other TP-types and copolyesters of various compositions for moulding and extrusion.

The types of thermoplastic polyester are differentiated from each other by a classification system based on appropriate levels of the designatory properties:

- a) viscosity number;
- b) tensile modulus of elasticity;

and on information about the intended application and/or method of processing, important properties, additives, colorants, fillers and reinforcing materials.

This designation system is applicable to thermoplastic polyester homopolymers and copolymers. It applies to materials ready for normal use in the form of powder, granules or pellets, unmodified or modified by colorants, fillers and other additives. This document does not apply to the saturated polyester/ester and polyether/ester thermoplastic elastomers covered by ISO 20029.

It is not intended to imply that materials having the same designation give necessarily the same performance. This document does not provide engineering data, performance data or data on processing conditions which can be required to specify a material. If such additional properties are required, they are intended to be determined in accordance with the test methods specified in ISO 20028-2, if suitable.

In order to designate a thermoplastic polyester material to meet particular specifications, the requirements are to be given in data block 5 (see 3.1).

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*

ISO 1043-2, *Plastics — Symbols and abbreviated terms — Part 2: Fillers and reinforcing materials*

ISO 1628-5, *Plastics — Determination of the viscosity of polymers in dilute solution using capillary viscometers — Part 5: Thermoplastic polyester (TP) homopolymers and copolymers*

ISO 20028-2, *Plastics — Thermoplastic polyester (TP) moulding and extrusion materials — Part 2: Preparation of test specimens and determination of properties*

ASTM D5927, *Standard Classification System for and Basis for Specifications for Thermoplastic Polyester (TPES) Injection and Extrusion Materials Based on ISO Test Methods*

**3 Terms and definitions**

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

**4 Designation system**

**4.1 General**

The designation system for thermoplastics is based on the following standardized pattern.

Designation						
Description Block (optional)	Identity block					
	International Standard number block	Individual item block				
		Data block 1	Data block 2	Data block 3	Data block 4	Data block 5

The designation consists of an optional description block, reading “Thermoplastics”, and an identity block comprising the International Standard number and an individual-item block. For unambiguous designation, the individual-item block is subdivided into five data blocks comprising the following information.

- Data block 1: Identification of the plastic by its symbol PET, PBT, PCT, PEN, PBN or TP for all such polyesters and copolyesters in general, in accordance with ISO 1043-1 (see 4.2).
- Data block 2: Position 1: Fillers or reinforcing materials and their nominal content (see 4.3).  
Position 2: Declaration of recyclate (REC) plastics and their contents if desired.
- Data block 3: Position 1: Intended application and/or method of processing (see 4.4).  
Positions 2 to 8: Important properties, additives and supplementary information (see 4.4).
- Data block 4: Designatory properties (see 4.5).
- Data block 5: For the purpose of specifications, a fifth data block contains appropriate information (see 4.6).

The first character of the individual item block shall be a hyphen. The five data blocks shall be separated from each other by a comma. If a data block is not used, this shall be indicated by doubling the separation sign, i.e. by two commas (,,). Terminal commas may be omitted.

NOTE Data blocks 1 and 2, when separated by a hyphen, form the part marking symbol

**4.2 Data block 1**

In this data block, after the hyphen, thermoplastic polyesters are identified using the symbols and designations listed in [Table 1](#) and [Table 2](#).



**Table 1 — Symbols indicating the chemical structure of polyester materials in data block 1**

Symbol <sup>a</sup>	Name and chemical identification
PET, TP 2T	Poly(ethylene terephthalate): polyester based on ethylene glycol and terephthalic acid (or its ester).
PTT, TP 3T	Poly(trimethylene terephthalate): polyester based on 1,3-propanediol and terephthalic acid (or its ester).
PBT, TP 4T	Poly(butylene terephthalate): polyester based on 1,4-butanediol and terephthalic acid (or its ester).
PCT, TP CHT	Poly(cyclohexylenedimethylene terephthalate): polyester based on cyclohexanedimethanol and terephthalic acid (or its ester).
PEN, TP 2N	Poly(ethylene naphthalate): polyester based on ethylene glycol and 2,6-naphthalenedicarboxylic acid (or its ester).
PBN, TP 4N	Poly(butylene naphthalate): polyester based on 1,4-butanediol and 2,6-naphthalenedicarboxylic acid (or its ester).
TP 26	Poly(ethylene adipate): polyester based on ethylene glycol and adipic acid.
TP 4I	Poly(butylene isophthalate): polyester based on 1,4-butanediol and isophthalic acid.
TP CH10	Polyester based on cyclohexanedimethanol and sebacic acid.
<sup>a</sup> See <a href="#">Annex A</a> (Designation of thermoplastic polyesters).	

**Table 2 — Symbols indicating the chemical structure of copolyester materials in data block 1 (examples)**

Symbol <sup>a</sup>	Chemical identification
TP 6I/6T	Copolyester based on hexanediol, isophthalic acid and terephthalic acid.
TP BAI/BAT	Copolyester based on bisphenol A, isophthalic acid and terephthalic acid.
TP 2T/CHT	Copolyester based on ethylene glycol, cyclohexanedimethanol and terephthalic acid (or its derivatives).
TP 2T/2I	Copolyester based on ethylene glycol, terephthalic acid and isophthalic acid (or its ester).
TP 2/6/NG// T/I/6	Copolyester based on ethylene glycol, 1,6-hexanediol, neopentyl glycol, terephthalic acid, isophthalic acid and adipic acids.
The following two designations include an indication of the mass content ratio:	
TP 2T/26 (90/10)	Copolyester based on 90 % ( <i>mass by mass</i> ) ethylene glycol and terephthalic acid and 10 % ( <i>mass by mass</i> ) ethylene glycol and adipic acid.
TP NGT/6I (75/25)	Copolyester based on 75 % ( <i>mass by mass</i> ) neopentyl glycol and terephthalic acid and 25 % ( <i>mass by mass</i> ) 1,6-hexanediol and isophthalic acid.
<sup>a</sup> See <a href="#">Annex A</a> (Designation of thermoplastic polyesters).	

Blends of thermoplastic polyesters or thermoplastic polyesters with other polymers are identified using the symbols for the basic polymers separated by a plus sign.

EXAMPLE PBT + ASA for a blend of poly(butylene terephthalate) and acrylonitrile/styrene/acrylate.

### 4.3 Data block 2

In this data block, the type of filler and/or reinforcing material is represented by a single code-letter in position 1 and its physical form by a second code-letter in position 2, the code-letters being as specified in [Table 3](#). Subsequently (without a space), the actual content may be given by a two-figure code-number in positions 3 and 4.

Mixtures of materials and/or forms may be indicated by combining the relevant codes using the sign “+” and placing the whole between parentheses followed by the total filler content.

EXAMPLE 1 A mixture of 25 % (mass by mass) of glass fibres (GF) and 10 % (mass by mass) mineral powder (MD) would be indicated by (GF25+MD10).

In the second position of this data block, recyclate declaration is represented by symbol “REC” and by following the content between parentheses, if desirable.

EXAMPLE 2 A mixture of 50% (mass by mass) of recyclate would be indicated by REC(50).

**Table 3 — Code-letters for fillers and reinforcing materials in data block 2**

Code-letter	Material	Code-letter	Form
<b>B</b>	Boron	<b>B</b>	Beads, spheres, balls
<b>C</b>	Carbon <sup>a</sup>	<b>D</b>	Powder
<b>G</b>	Glass	<b>F</b>	Fibre
<b>K</b>	Calcium carbonate	<b>G</b>	Ground
<b>M</b>	Mineral <sup>a</sup> , metal <sup>b</sup>	<b>H</b>	Whiskers
<b>S</b>	Synthetic, organic <sup>a</sup>	<b>X</b>	Not specified
<b>T</b>	Talc	<b>Z</b>	Others
<b>X</b>	Not specified		
<b>Z</b>	Others <sup>a</sup>		

<sup>a</sup> These materials may be further defined after position 4 of the data block by their chemical symbol, for example, or additional symbols defined in ISO 1043-2 or by additional symbols agreed between the interested parties.

<sup>b</sup> Metal fillers shall be identified by their chemical symbol (in capital letters) after the mass content. For example, 5 % steel whiskers may be designated “MH05FE”.

#### 4.4 Data block 3

In this data block, information about intended application and/or method of processing is given in position 1 and information about important properties, additives and colour in positions 2 to 8. The code-letters used are specified in [Table 4](#).

If information is presented in positions 2 to 8 and no specific information is given in position 1, the letter X shall be inserted in position 1.

**Table 4 — Code-letters used in data block 3**

Code-letter	Position 1	Code-letter	Positions 2 to 8
<b>A</b>	Adhesive	<b>A</b>	Processing stabilized
<b>B</b>	Blow moulding	<b>B</b>	Antiblocking
<b>C</b>	Calendering	<b>C</b>	Coloured
<b>D</b>	Disc manufacture	<b>D</b>	Powder
<b>E</b>	Extrusion	<b>E</b>	Expandable
<b>F</b>	Extrusion of films	<b>F</b>	Special burning characteristics
<b>G</b>	General use	<b>G</b>	Granules
<b>H</b>	Coating	<b>H</b>	Heat-ageing stabilized
<b>K</b>	Cable and wire coating	<b>L</b>	Light or weather stabilized
<b>L</b>	Monofilament extrusion	<b>M</b>	Nucleated
<b>M</b>	Injection moulding	<b>N</b>	Natural (no colour added)
<b>R</b>	Rotational moulding	<b>P</b>	Impact modified
<b>S</b>	Sintering	<b>R</b>	Mould release agent
<b>X</b>	No indication	<b>S</b>	Lubricated

Table 4 (continued)

Code-letter	Position 1	Code-letter	Positions 2 to 8
		<b>T</b>	Transparent
		<b>W</b>	Stabilized against hydrolysis
		<b>Z</b>	Antistatic

## 4.5 Data block 4

### 4.5.1 General

In this data block, the range of designatory property 1 is represented by a two-figure code-number (see 4.5.2), the range of designatory property 2 by a three-figure code-number (see 4.5.3). The code-numbers are separated from each other by hyphens.

If a property value falls on or near a range limit, the manufacturer shall state which range will designate the material. If subsequent individual test values lie on, or on either side of, the limit because of manufacturing tolerances, the designation is not affected.

NOTE Not all the combinations of the values of the designatory properties are provided by currently available polymers.

### 4.5.2 Viscosity number

The viscosity number shall be determined in accordance with ISO 1628-5, using 50/50 phenol/1,2-dichlorobenzene for PET and *m*-cresol for PBT.

The possible values of viscosity number are divided into 8 ranges, each represented by a two-figure code-number as specified in Table 5.

Table 5 — Code-numbers used for viscosity number in data block 4

Code-number	Range of viscosity number ml/g
<b>03</b>	≤40
<b>05</b>	>40 but ≤60
<b>07</b>	>60 but ≤80
<b>09</b>	>80 but ≤100
<b>11</b>	>100 but ≤120
<b>13</b>	>120 but ≤140
<b>15</b>	>140 but ≤160
<b>17</b>	>160 but ≤180

NOTE 1 Viscosity numbers determined in other solvents can be converted into viscosity numbers determined in phenol/1,2-dichlorobenzene using the following formulae.

For phenol/1,1,2,2-tetrachloroethane (50/50):  $x = 0,93y + 1,87$

For phenol/1,1,2,2-tetrachloroethane (60/40):  $x = 1,20y - 13,34$

For *o*-chlorophenol:  $x = 1,22y - 10,24$

For dichloroacetic acid:  $x = 1,20y - 18,07$

where

$x$  is the viscosity number in phenol/1,2-dichlorobenzene (50/50);

$y$  is the viscosity number in the alternative solvent.

NOTE 2 Viscosity numbers determined in other solvents can be converted into viscosity numbers determined in *m*-cresol using the following formulae.

For phenol/1,1,2,2-tetrachloroethane (50/50):  $x = 0,70y + 5,59$

For phenol/1,1,2,2-tetrachloroethane (60/40):  $x = 0,57y + 29,22$

For *o*-chlorophenol:  $x = 0,85y + 3,14$

For dichloroacetic acid:  $x = 0,70y + 7,34$

For phenol/1,2-dichlorobenzene:  $x = 0,75y + 0,96$

where

$x$  is the viscosity number in *m*-cresol;

$y$  is the viscosity number in the alternative solvent.

For PCT, the viscosity number shall be determined using phenol/1,1,2,2-tetrachloroethane (60/40) as the solvent.

For amorphous PEN, the viscosity number shall be determined using phenol/1,1,2,2-tetrachloroethane (60/40) as the solvent, and for crystalline PEN, phenol/2,4,6-trichlorophenol (60/40) is the specified solvent.

For PBN, the viscosity number shall be determined using phenol/1,1,2,2-tetrachloroethane (60/40) as the solvent.

For other TP homopolymers and copolymers, the use of *m*-cresol is preferred.

### 4.5.3 Tensile modulus of elasticity

The tensile modulus of elasticity shall be determined in accordance with ISO 20028-2.

The possible values of tensile modulus of elasticity are divided into 23 ranges, each represented by a three-figure code-number as specified in [Table 6](#).

**Table 6 — Code-numbers used for tensile modulus of elasticity in data block 4**

Code-number	Range of tensile modulus of elasticity MPa
<b>001</b>	<150
<b>002</b>	>150 but ≤250
<b>003</b>	>250 but ≤350
<b>004</b>	>350 but ≤450
<b>005</b>	>450 but ≤600
<b>007</b>	>600 but ≤800
<b>010</b>	>800 but ≤1 500
<b>020</b>	>1 500 but ≤2 500
<b>030</b>	>2 500 but ≤3 500
<b>040</b>	>3 500 but ≤4 500
<b>050</b>	>4 500 but ≤5 500
<b>060</b>	>5 500 but ≤6 500
<b>070</b>	>6 500 but ≤7 500

Table 6 (continued)

Code-number	Range of tensile modulus of elasticity MPa
080	>7 500 but ≤8 500
090	>8 500 but ≤9 500
100	>9 500 but ≤10 500
110	>10 500 but ≤11 500
120	>11 500 but ≤13 500
140	>13 500 but ≤15 500
160	>15 500 but ≤17 500
190	>17 500 but ≤20 500
220	>20 500 but ≤23 500
250	>23 500

4.6 Data block 5

Indication of additional requirements in this optional data block is a way of transforming the designation of a material into a specification for a particular application. This may be done, for example, by reference to a suitable national standard or to a standard-like, generally established specification.

5 Examples of designations

5.1 Designation only

5.1.1 A poly(ethylene terephthalate) thermoplastic material (PET), with special burning characteristics (F), stabilized against heat ageing (H), with a nucleating agent (M), having a viscosity number of 85 ml/g (09) and a tensile modulus of elasticity of 10 300 MPa (100), and reinforced by a nominal glass fibre content of 30 % (mass by mass) (GF30), would be designated:

DESIGNATION								
Description block (optional)	Identity block							
	ISO Standard	Individual item block						
		Data Block 1	Data Block 2		Data Block 3		Data Block 4	Data Block 5
		Polymer	Performance and origin related information		Application and Processing		Properties	Additional information
Type	Filler	Recyclate	Processing	Characteristics				
Thermoplastics	20028	PET	GF30		X	FHM	09-100	
>Part marking<								
No	No	Yes	Yes		No	No	No	

Designation: Thermoplastics ISO 20028-PET,GF30,XFHM,09-100,, or

Thermoplastics ISO 20028-TP 2T,GF30,XFHM,09-100,, or

ISO 20028-PET,GF30,XFHM,09-100,, or ISO 20028-TP 2T,GF30,XFHM,09-100,, or

ISO 20028-PET,GF30,XFHM,09-100 or ISO 20028-TP 2T,GF30,XFHM,09-100

## ISO 20028-1:2017(E)

Part marking: >PET-GF30< or >TP 2T-GF30<

**5.1.2** A poly(butylene terephthalate) thermoplastic material (PBT) for injection moulding (M), with special burning characteristics (F), natural (no colour added) (N), provided with a mould release agent (R), having a viscosity number of 96 ml/g (09) and a tensile modulus of elasticity of 5 900 MPa (060), and reinforced with 12 % (mass by mass) of glass fibres (GF12), would be designated:

DESIGNATION								
Description block (optional)	Identity block							
	ISO Standard	Individual item block						
		Data Block 1	Data Block 2		Data Block 3		Data Block 4	Data Block 5
		Polymer	Performance and origin related information		Application and Processing		Properties	Additional information
Type	Filler	Recyclate	Processing	Characteristics				
Thermoplastics	20028	PBT	GF12		M	FNR	09-060	
>Part marking<								
No	No	Yes	Yes		No	No	No	

Designation: Thermoplastics ISO 20028-PBT,GF12,MFNR,09-060,, or

ISO 20028-PBT,GF12,MFNR,09-060,, or

ISO 20028-PBT,GF12,MFNR,09-060

Part marking: >PBT-GF12<

**5.1.3** A thermoplastic copolyester (TP) based on 50 % (mass by mass) bisphenol A (BA) and terephthalic acid (T) and 50 % (mass by mass) bisphenol A (BA) and isophthalic acid (I), for general use (G), transparent (T), natural (no colour added) (N) and having a viscosity number of 115 ml/g (11) and a tensile modulus of elasticity of 1 900 MPa (020), would be designated:

DESIGNATION								
Description block (optional)	Identity block							
	ISO Standard	Individual item block						
		Data Block 1	Data Block 2		Data Block 3		Data Block 4	Data Block 5
		Polymer	Performance and origin related information		Application and Processing		Properties	Additional information
Type	Filler	Recyclate	Processing	Characteristics				
Thermoplastics	20028	TP BAT/BAI(50/50)			G	TN	11-020	
>Part marking<								
No	No	Yes	Yes		No	No	No	

Designation: Thermoplastics ISO 20028-TP BAT/BAI(50/50),,GTN,11-020,, or

ISO 20028-TP BAT/BAI(50/50),,GTN,11-020,, or

ISO 20028-TP BAT/BAI(50/50),,GTN,11-020

Part marking: >TP BAT/BAI<

### 5.2 Designation transformed into a specification

A poly(ethylene terephthalate) thermoplastic material (PET) for injection moulding (M), coloured (C), having a viscosity number of 75 ml/g (07) and a tensile modulus of elasticity of 13 800 MPa (140), reinforced with 45 % (mass by mass) of glass fibres (GF45) and meeting the requirements of the specification ASTM D5927 TPES0210G45A88560, would be specified:

DESIGNATION								
Description block (optional)	Identity block							
	ISO Standard	Individual item block						
		Data Block 1	Data Block 2		Data Block 3		Data Block 4	Data Block 5
		Polymer	Performance and origin related information		Application and Processing		Properties	Additional information
Type	Filler	Recy-clate	Process-ing	Characteris-tics				
Thermo-plastics	20028	PET	GF45		M	C	07-140	ASTM D5927 TPES-0210G45A88560
>Part marking<								
No	No	Yes	Yes	No	No	No	No	No

Designation: Thermoplastics ISO 20028-PET,GF45,MC,07-140, ASTM D5927 TPES0210G45A88560 or ISO 20028-PET,GF45,MC,07-140, ASTM D5927 TPES0210G45A88560

Part marking: >PET-GF45<

## Annex A (normative)

### Designation of thermoplastic polyesters

Thermoplastic polyester materials contain ester groups, -CO-O-, at regular intervals in the linear polymer chain.

Straight-chain polyesters are built up from one starting material with two hydroxyl (-OH) groups, also called diols, plus one starting material with two carboxylic acid (-COOH) groups, also called dicarboxylic acids, or esters of such acids, by a polycondensation process. A hydroxycarboxylic acid or its lactone may also be used to build up polyesters. If a tricarboxylic acid and/or a triol is used, branched polymer chains will result.

The following six homopolyester thermoplastics are well known:

PET	Poly(ethylene terephthalate)
PTT	Poly(trimethylene terephthalate)
PBT	Poly(butylene terephthalate)
PCT	Poly(cyclohexylenedimethylene terephthalate)
PEN	Poly(ethylene naphthalate)
PBN	Poly(butylene naphthalate)

For polyesters and copolyesters, a designation system similar to that for polyamides and copolyamides (see ISO 16396) has been developed to avoid creating new abbreviations for each member of this large family.

TP is the symbol for thermoplastic polyester, in accordance with ISO 1043-1.

Aliphatic polyesters based on linear diols and linear dicarboxylic acids or esters of such acids are designated by two or more code-numbers. The first code-number (which may have one or two digits) corresponds to the number of C-atoms in the linear diol (see [Table A.1](#)) and the second code-number (which may also have one or two digits) corresponds to the number of C-atoms in the linear dicarboxylic acid (see [Table A.2](#)).

Nonlinear aliphatic, cycloaliphatic and aromatic compounds used as monomer units in the polyester chain are designated by code-letters (see [Tables A.1, A.2 and A.3](#)).

Copolyesters are designated by an oblique stroke (/) between the code-numbers representing the components of the copolyester (cf. A.6, in ISO 1043-1:2011). Copolyesters with the same code-numbers or code-letters can have quite different properties, depending on the ratio of the starting materials. Therefore, the ratio, in mass percent, may optionally be indicated in parentheses at the end of the designation (see [Table 2](#)).

Copolyesters containing more than three monomers can also be represented by a simplified designation, TP DO<sub>1</sub>/DO<sub>2</sub>/DO<sub>3</sub>//DA<sub>1</sub>/DA<sub>2</sub>/DA<sub>3</sub>, where DO<sub>1</sub>, DO<sub>2</sub> and DO<sub>3</sub> are three different diols and DA<sub>1</sub>, DA<sub>2</sub> and DA<sub>3</sub> are three different dicarboxylic acids. Two oblique strokes (//) are used between the diols and dicarboxylic acids.

Due to the great variety of polyesters and copolyesters, only a few examples are given below.



Using this system, PET, PTT, PBT, PCT and PEN can also be designated as follows:

PET TP 2T  
 PTT TP 3T  
 PBT TP 4T  
 PCT TP CHT  
 PEN TP 2N  
 PBN TP 4N

**Table A.1 — Symbols for hydroxy units [first digit(s)]**

Symbol	Monomer unit derived from	CAS No.
2	Ethylene glycol	107-21-1
3	1,3-Propanediol	504-63-2
4	1,4-Butanediol	110-63-4
6	1,6-Hexanediol	629-11-8
14	1,14-Tetradecanediol	19812-64-7
CH	Cyclohexanedimethanol	105-08-8
NG	Neopentyl glycol	126-30-7
TM	1,1,1-Trimethylolpropane	77-99-6
BA	Bisphenol A	80-05-7
DG	Diethylene glycol	111-46-6
BF	Bisphenol F	2467-02-9
XX	Not specified	

**Table A.2 — Symbols for carboxylic units [second digit(s)]**

Symbol	Monomer unit derived from	CAS No.
6	Adipic acid	124-04-9
9	Azelaic acid	123-99-9
10	Sebacic acid	111-20-6
12	Dodecanedioic acid	693-23-2
36	Hydrogenated dimeric fatty acid	68783-41-5
T	Terephthalic acid	100-21-0
I	Isophthalic acid	121-91-5
M	Trimellitic acid	528-44-9
N	2,6-Naphthalenedicarboxylic acid	1141-38-4
P	Phthalic acid	88-99-3
C	1,4-Cyclohexanedicarboxylic acid	1076-97-7
YY	Not specified	

**Table A.3 — Symbols for hydroxycarboxylic units**

<b>Symbol</b>	<b>Monomer unit derived from</b>	<b>CAS No.</b>
CL	Caprolactone	502-44-3
HB	<i>p</i> -Hydroxybenzoic acid	99-96-7
HV	4-Hydroxyvaleric acid lactone	108-29-2
ZZ	Not specified	

## Bibliography

- [1] ISO 20029-1, *Plastics — Thermoplastic polyester/ester elastomers for moulding and extrusion materials — Part 1: Designation system and basis for specification*
- [2] ISO 20029-2, *Plastics — Thermoplastic polyester/ester elastomers for moulding and extrusion materials — Part 2: Preparation of test specimens and determination of properties.*
- [3] ISO 16396-1, *Plastics — Polyamide (PA) moulding and extrusion materials — Part 1: Designation system, marking of products and basis for specifications*

