



**INTERNATIONAL STANDARD ISO 20299-1:2006**  
**TECHNICAL CORRIGENDUM 1**

Published 2008-04-15

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

## **Film for wrapping rubber bales —**

### **Part 1: Butadiene rubber (BR) and styrene-butadiene rubber (SBR)**

TECHNICAL CORRIGENDUM 1

*Emballage des balles en caoutchouc —*

*Partie 1: Caoutchouc butadiène (BR) et caoutchouc styrène-butadiène (SBR)*

*RECTIFICATIF TECHNIQUE 1*

Technical Corrigendum 1 to ISO 20299-1:2006 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

---

*Page 1, Clause 3*

Replace item a) by the following:

- a) low-density polyethylene (polyethene) (PE-LD);

---

**ICS 83.040.01**

**Ref. No. ISO 20299-1:2006/Cor.1:2008(E)**

© ISO 2008 – All rights reserved

*Page 2, Subclause 4.1*

Replace the text of this subclause by the following:

When measured by gravimetric techniques as specified in ISO 4591, the film shall have a thickness between 0,035 mm and 0,065 mm.