
**Material used for producing wrappings
for cigarette filters, cigarettes and other
tobacco products — Determination of
acetate content**

*Matériaux utilisés pour la fabrication des enveloppes pour les filtres de
cigarette, pour les cigarettes et pour les autres produits du tabac —
Dosage de l'acétate*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 20370 was prepared by Technical Committee ISO/TC 126, *Tobacco and tobacco products*.

.....

Material used for producing wrappings for cigarette filters, cigarettes and other tobacco products — Determination of acetate content

WARNING — The use of this International Standard can involve hazardous materials, operations and equipment. This International Standard does not purport to address all the safety problems associated with its use. It is the responsibility of the user of this International Standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard specifies a method for the determination of the acetate content of material used to produce wrappings for cigarette filters, cigarettes and other tobacco products.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 187, *Paper, boards and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 287, *Paper and board — Determination of moisture content of a lot — Oven-drying method*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

acetate content

(materials for producing wrappings for cigarette filters, cigarettes and other tobacco products) anhydrous acetic acid content determined by the enzymatic method


NOTE Acetate is generally added to wrapping materials, in particular cigarette paper, as sodium acetate and potassium acetate to influence the burning rate of the cigarette and, consequently, the puff number.

4 Principle

The acetate content is determined by an enzymatic method in which acetate (acetic acid), catalyzed by the enzyme acetyl coenzyme A synthase (ACS) with adenosine 5'-triphosphate (ATP) and coenzyme A (CoA), is first converted to acetyl coenzyme A, adenosine 5'-monophosphate (AMP) and pyrophosphate in accordance with the following reaction:



Catalyzed by citrate synthase (CS), acetyl coenzyme A reacts with oxaloacetate to form citrate in accordance with the following reaction:



The oxaloacetate required for the reaction (2) is formed from malate and nicotinamide-adenine dinucleotide (NAD⁺) by catalysis using L-malate dehydrogenase (L-MDH) in accordance with the following reaction:



The determination is based on the formation of NADH, which is measured by the increase in absorbance at 340 nm. Since the determination reaction is preceded by an indicator reaction, the amount of NADH formed is not linearly proportional to the acetate content.

5 Reagents

5.1 General

All reagents used shall be of recognized analytical grade. Water used shall be in accordance with at least grade 3 of ISO 3696.

5.2 Test kit for enzymatic acetate determination

5.2.1 General

Commercially available test kits shall be used that generally contain two reagent mixtures [Roche-Biopharm 10.148.261.035, or equivalent¹].

Optionally, the determination may be performed using individual reagents. In that case, the procedure is to be found in the literature or commercial information documents.

5.2.2 Reagent mixture 1

The ready-to-use solution 1, which is buffered to a pH of 8,4 using triethanolamine buffer, contains the following:

- L-malic acid, about 4,2 mg/ml;
- magnesium chloride, about 2,1 mg/ml.

Solution 1 will be stable for one year at +4 °C.

1) Roche-Biopharm 10.148.261.035 is an example of a suitable product available commercially. This information is given for the convenience of the users of this International Standard and does not constitute an endorsement by ISO of this product.

5.2.3 Reagent mixture 2

Reagent mixture 2 shall be diluted with water in accordance with the manufacturer's instructions to produce solution 2. The ready-to-use solution 2 contains the following:

- adenosine 5'-triphosphate (ATP), about 25,0 mg/ml;
- coenzyme A (CoA), about 2,6 mg/ml;
- nicotinamide adenine dinucleotide (NAD), about 12,3 mg/ml.

Solution 2 will be stable for four weeks at +4 °C.

5.2.4 Reagent mixture 3

The ready-to-use solution 3 contains the following:

- L-malate dehydrogenase (L-MDH), about 2 750 IU²/ml;
- citrate synthase, about 675 IU/ml.

Solution 3 will be stable for one year at +4 °C.

The activity of the enzyme system shall be (100 ± 5) %.

5.2.5 Reagent mixture 4

Reagent mixture 4 shall be diluted with water in accordance with the manufacturer's instructions to produce solution 4. The ready-to-use solution 4 contains about 20 IU/ml of acetyl coenzyme A synthase (ACS).

Solution 4 will be stable for five days at +4 °C.

5.3 Sodium acetate trihydrate.

6 Apparatus

Usual laboratory apparatus and, in particular, the following items.

- 6.1 Conical flasks**, of nominal capacity 250 ml.
- 6.2 Funnel**, of diameter 80 mm.
- 6.3 Filter paper**, of diameter 125 mm [Whatman No. 40, or equivalent³].
- 6.4 Pipettes**, with graduations suitable for nominal capacities of 1 ml, 2 ml, 5 ml and 10 ml; enzyme assay pipettes might be used as well ^[2].
- 6.5 Piston-operated pipettes**, of nominal capacities 10 µl and 20 µl.
- 6.6 Double-beam spectrophotometer**, suitable for a wavelength of 340 nm.

2) IU (international unit) is the amount of enzyme (activity) that catalyses the conversion of 1 µmol of substrate per minute under standard conditions.

3) Whatman No. 40 is an example of a suitable product available commercially. This information is given for the convenience of the users of this International Standard and does not constitute an endorsement by ISO of this product.

6.7 **Glass or plastic cuvetts**, of light path 10 mm and capacity 5 ml.

6.8 **Ultrasonic bath or magnetic stirrer**.

6.9 **Analytical balance**, suitable for measuring to the nearest 0,001 g.

7 Procedure

7.1 Sample preparation

Extract approximately 1,0 g, to the nearest 0,001 g, of cut wrapping material previously conditioned as specified in ISO 187, in 100 ml of water in a 250 ml conical flask (6.1), by the aid of an ultrasonic bath or magnetic stirrer (6.8) for 30 min. Then filter the extract through a filter paper (6.3).

7.2 Determination

Perform the determination at a constant temperature of between 20 °C and 25 °C. The following pipetting procedure (see Table 1) has proved satisfactory for the blank solution (water) and the test solution (sample extract as prepared in 7.1).

The absorbance shall be determined using a double-beam spectrophotometer (6.6) at a wavelength of 340 nm with air (no cuvet in the beam path) or water as reference. The total volume, V , of the test solution in the cuvet shall be 3,23 ml.

To calibrate the method, replace the sample extract by standard solutions of sodium acetate trihydrate (5.3) having mass concentrations of 300 mg/l, 100 mg/l and 50 mg/l and proceed as described in this clause.

Table 1 — Pipetting procedure

Pipette into cuvetts	Blank cuvet ml	Test cuvet ml
Solution 1 according to 5.2.2	1,00	1,00
Solution 2 according to 5.2.3	0,20	0,20
Water	2,00	1,90
Sample extract	—	0,10
Mix, read off the absorbance of the solutions, A_0 , and then add the following.		
Solution 3 according to 5.2.4	0,01	0,01
Mix, and on completion of the reaction (after about 3 min), read off the absorbance of the solutions, A_1 . Then start the second reaction by adding the following.		
Solution 4 according to 5.2.5	0,02	0,02
Mix, and on completion of the reaction (after about 10 min to 15 min), read off the absorbances of the solutions, A_2 . If the reaction has not stopped after 15 min, read off the absorbance at 2 min intervals until the absorbance increases constantly for 2 min. If the absorbance increases at a constant rate, extrapolate it to the time when the solution was added.		

8 Calculation

In the reactions on which this determination is based, there is not a linear proportionality between the amount of NADH consumed — and, consequently, the absorbance difference, ΔA — and the acetic acid concentration (see Clause 4). Calculate the absorbance difference using the following equation:

$$\Delta A = \left[(A_2 - A_0)_{\text{sample}} - \frac{(A_1 - A_0)_{\text{sample}}^2}{(A_2 - A_0)_{\text{sample}}} \right] - \left[(A_2 - A_0)_{\text{blank}} - \frac{(A_1 - A_0)_{\text{blank}}^2}{(A_2 - A_0)_{\text{blank}}} \right] \quad (4)$$

To obtain reliable results, the absorbance difference of the sample extract should be at least 0,1. The acetic acid concentration in the cuvet shall be between 1 μg and 15 μg , and the sample shall therefore be diluted beforehand so that the acetic acid content is 0,01 g/l to 0,15 g/l. The absorbance difference should be between 0,2 and 0,4.

Calculate the acetic acid mass concentration, ρ_A , in grams per litre of the sample extract, using the following equation:

$$\rho_A = \frac{V \times M \times F}{\varepsilon \times \delta \times V_P \times 1000} \times \Delta A \quad (5)$$

where

V is the total volume of test solution in the cuvet, in millilitres (generally 3,23 ml);

M is the molar mass of the substance to be determined;

F is the dilution factor of the sample solution;

ε is the absorption coefficient of NADH at 340 nm: 6,30 l·mmol⁻¹·cm⁻¹,

δ is the light path of the cuvet, in centimetres;

V_P is the volume of sample solution used for the preparation of the test solution, in millilitres;

ΔA is the absorbance difference.

If the volumes are the same as in 7.2 and it is unnecessary to dilute the sample extract, calculate the acetate content, ρ_A , given as a concentration by mass in grams per litre of sample extract, as anhydrous acetic acid ($M = 60,05$ g/mol) using the following equation:

$$\rho_A = 2,566 \times \Delta A \quad (6)$$

Calculate the content of acetate as mass fraction, ω_A , in the wrapping material given as a percentage by mass as anhydrous acetic acid, using the following equation:

$$\omega_A = \frac{\rho_A}{\rho_P} \times 100 \% \quad (7)$$

where ρ_P is the mass concentration of the wrapping material sample, in grams per litre of sample extract.

If 1 g of wrapping material is extracted with 100 ml of water, ρ_P is equal to 10 g/l. In this case, the content of acetate, ω_A , is given by the following equation:

$$\omega_A = \rho_A \times 10 \% \quad (8)$$

Report the acetate content (mass fraction) as a percentage by mass of anhydrous acetic acid in the wrapping material.

9 Precision

Table 2 shows mean standard deviations of repeatability, s_r , and reproducibility, s_R , obtained from a collaborative study. The study, involving nine laboratories, was conducted in 2005, using three cigarette paper samples with acetate levels between 0,4 % and 1,1 %. Eight laboratories reported results obtained by this method.

Table 2 — Data analysis of collaborative study

Sample	<i>n</i> data considered	Mean value		
		m_N	s_r	s_R
Results expressed as mass fraction in % anhydrous acetic acid				
A1	8	0,52	0,025	0,031
A2	8	0,40	0,035	0,043
A3	8	1,11	0,037	0,057

10 Test report

The test report shall include the following:

- a) all information required for the complete identification of the sample (type of sample, its origin, and its designation);
- b) reference to this International Standard;
- c) date of sampling and method;
- d) details of conditioning;
- e) date of sample delivery;
- f) date of analysis;
- g) moisture content of wrapping material, determined in accordance with ISO 287;
- h) the analysis results and the units in which they are reported;
- i) any special features observed during the analysis;
- j) any working conditions that are not specified in this method or are considered as optional, and that can have affected the results.

NOTE If the wrapping material samples are taken from cigarettes, the results can be influenced by external parameters, such as additives of the tobacco blend.

Bibliography

- [1] CORESTA Recommended Method No 33, *Determination of Acetate in Cigarette Paper*, January 1993
- [2] DIN 12699, *Laboratory glassware — Graduated pipettes for enzymatic analyses, short delivery time, waiting time 15s, class AS*

ICS 65.160

Price based on 7 pages