INTERNATIONAL STANDARD

ISO 21003-5

First edition 2008-07-01

Multilayer piping systems for hot and cold water installations inside buildings —

Part 5:

Fitness for purpose of the system

Systèmes de canalisations multicouches pour installations d'eau chaude et froide à l'intérieur des bâtiments —

Partie 5: Aptitude à l'emploi du système



Reference number ISO 21003-5:2008(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below



COPYRIGHT PROTECTED DOCUMENT

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 749 09 47 E-mail copyright@iso.org Web www.iso.org

Published in Switzerland

Cont	tents	Page
Forew	ord	iv
Introd	uction	
1	Scope	1
2	Normative references	1
3	Terms and definitions	2
4	Symbols and abbreviated terms	2
5 5.1 5.2 5.3 5.4	Fitness for purpose of the joints and the piping system	3 4
5.5	Thermal cycling test	6
5.6 5.7	Pressure cycling test Leaktightness under vacuum	
Annex	A (normative) List of reference product standards	8
Biblio	graphy	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 21003-5 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 2, *Plastics pipes and fittings for water supplies*.

ISO 21003 consists of the following parts, under the general title *Multilayer piping systems for hot and cold water installations inside buildings*:

- Part 1: General
- Part 2: Pipes
- Part 3: Fittings
- Part 5: Fitness for purpose of the system
- Part 7: Guidance for the assessment of conformity [Technical Specification]

NOTE ISO 21003 does not include a Part 4: Ancillary equipment, or a Part 6: Guidance for installation.

Introduction

The system standard of which this is Part 5 specifies the requirements for a multilayer piping system.

The multilayer piping system is intended to be used for hot and cold water installations inside buildings.

In respect of potential adverse effects on the quality of water intended for human consumption caused by the products covered by ISO 21003:

- no information is provided as to whether the products may be used without restriction in any of the member states of the EU or EFTA;
- it should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of these products remain in force.

Requirements and test methods for components of the piping system are specified in ISO 21003-1, ISO 21003-2 and ISO 21003-3. ISO/TS 21003-7 gives guidance on the assessment of conformity.

This part of ISO 21003 specifies the characteristics for fitness for purpose.

For ancillary equipment, separate standards can apply.

Guidance on installation of plastics piping systems made from various materials intended to be used for hot and cold water installations is given in ENV 12108.

Other system standards which, at the date of publication of this part of ISO 21003, had been published for plastics piping systems used for the same application are listed in Annex A.

Multilayer piping systems for hot and cold water installations inside buildings —

Part 5:

Fitness for purpose of the system

1 Scope

This part of ISO 21003 specifies the characteristics for the fitness for purpose of multilayer piping systems intended to be used for hot and cold water installations inside buildings for the conveyance of water — whether or not the water is intended for human consumption (domestic systems) or for heating systems — under specified design pressures and temperatures appropriate to the class of application (see Table 1 of ISO 21003:2008).

It also specifies the test parameters for the test methods referred to in this part of ISO 21003.

ISO 21003 is a reference product standard. It is applicable to multilayer pipes, fittings, their joints, and also to joints with components made of other plastics and non-plastics materials intended to be used for hot and cold water installations. This part of ISO 21003 is intended for use only in conjunction with all the other parts of ISO 21003.

ISO 21003 covers a range of service conditions (application classes) and design pressures. It is not applicable for values of design temperature, $T_{\rm D}$, maximum design temperature, $T_{\rm max}$, and malfunction temperature, $T_{\rm mal}$, in excess of those in Table 1 of ISO 21003-1:2008.

NOTE 1 It is the responsibility of the purchaser or specifier to make the appropriate selections from these aspects, taking into account their particular requirements and any relevant national regulations and installation practices or codes.

The polymeric materials used for the stress-designed layers are the following: polybutylene (PB), polyethylene of raised temperature resistance (PE-RT), crosslinked polyethylene (PE-X), polypropylene (PP) and chlorinated poly(vinyl chloride) (PVC-C).

The PE-X used shall be fully crosslinked and shall comply with the requirements of the relevant reference product standard (ISO 15875).

NOTE 2 For the purposes of this ISO 21003, crosslinked polyethylene (PE-X) as well as adhesives are considered as thermoplastic materials.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1167-1, Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method

ISO 1167-2, Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces

---,,---,,,-----

ISO 21003-5:2008(E)

- ISO 1167-3, Thermoplastics pipes, fittings and assemblies for the conveyance of fluids Determination of the resistance to internal pressure — Part 3: Preparation of components
- ISO 1167-4, Thermoplastics pipes, fittings and assemblies for the conveyance of fluids Determination of the resistance to internal pressure — Part 4: Preparation of assemblies
- ISO 13760, Plastics pipes for the conveyance of fluids under pressure Miner's rule Calculation method for cumulative damage
- ISO 15874-5, Plastics piping systems for hot and cold water installations Polypropylene (PP) Part 5: Fitness for purpose of the system
- ISO 15875-5, Plastics piping systems for hot and cold water installations Crosslinked polyethylene (PE-X) — Part 5: Fitness for purpose of the system
- ISO 15876-5, Plastics piping systems for hot and cold water installations Polybutylene (PB) Part 5: Fitness for purpose of the system
- ISO 15877-5, Plastics piping systems for hot and cold water installations Chlorinated poly(vinyl chloride) (PVC-C) — Part 5: Fitness for purpose of the system
- ISO 17456, Plastics piping systems Multilayer pipes Determination of long-term strength
- ISO 21003-1:2008, Multilayer piping systems for hot and cold water installations inside buildings Part 1: General
- ISO 21003-2:2008, Multilayer piping systems for hot and cold water installations inside buildings Part 2: **Pipes**
- ISO 21003-3, Multilayer piping systems for hot and cold water installations inside buildings Part 3: Fittings
- ISO 22391-5, Plastics piping systems for hot and cold water installations Polyethylene of raised temperature resistance (PE-RT) — Part 5: Fitness for purpose of the system
- EN 712, Thermoplastics piping systems End-load bearing mechanical joints between pressure pipes and fittings — Test method for resistance to pull-out under constant longitudinal force
- EN 713, Plastics piping systems Mechanical joints between fittings and polyolefin pressure pipes Test method for leaktightness under internal pressure of assemblies subjected to bending
- EN 12293, Plastics piping systems Thermoplastics pipes and fittings for hot and cold water Test method for the resistance of mounted assemblies to temperature cycling
- EN 12294, Plastics piping systems Systems for hot and cold water Test method for leaktightness under vacuum
- EN 12295, Plastics piping systems Thermoplastics pipes and associated fittings for hot and cold water Test methods for resistance of joints to pressure cycling

Terms and definitions 3

For the purposes of this document, the terms and definitions given in ISO 21003-1 apply.

Symbols and abbreviated terms

For the purposes of this part of ISO 21003, the symbols and abbreviated terms given in ISO 21003-1 apply.

5 Fitness for purpose of the joints and the piping system

5.1 General

When tested in accordance with the applicable methods as specified in Table 1, using the parameters given in 5.2 to 5.7, the joints and the piping system shall have characteristics conforming to the requirements given in the applicable subclauses.

For the tests described, the fittings shall be connected to the pipe with which they are intended to be used.

Table 1 specifies the tests applicable for each different type of jointing system covered by this part of ISO 21003.

Jointing system a Test **Test parameters** Test method Solvent-**Fusion socket** Mechanical **Electrofusion** cemented Relevant parts of Internal pressure test Υ Υ Υ Shall conform to 5.2 ISO 1167 Bending test Υ Υ Shall conform to 5.3 EN 713 Pull-out test Υ Υ Υ Shall conform to 5.4 EN 712 Thermal cycling test Υ Υ Υ Shall conform to 5.5 EN 12293 Υ Pressure cycling test Υ Υ Shall conform to 5.6 EN 12295 Υ Υ Υ Shall conform to 5.7 EN 12294 Vacuum test Y denotes test applicable.

Table 1 — Joint tests

5.2 Internal pressure test

When tested in accordance with the relevant parts of ISO 1167, using the test parameters given in Table 2 for the relevant classes, the joint assembly shall not leak.

The test pressure shall be calculated using the following equation:

$$p_{\mathsf{F}} = p_{\mathsf{D}} \times \frac{p_{\mathsf{C}}}{p_{\mathsf{CD}}} \tag{1}$$

where

 $p_{\rm F}$ is the hydrostatic test pressure, in bars, to be applied to the assembly during the test period;

*p*_C is the value of the pressure, in bars, of the pipe construction corresponding to the time to failure/test temperature specified in ISO 21003-2;

 $p_{\rm CD}$ is the design pressure value, in bars, of the pipe construction, calculated in accordance with Annex E of ISO 21003-2:2008;

Not for Resale

 $p_{\rm D}$ is the design pressure of 4 bar, 6 bar, 8 bar or 10 bar, as applicable.

Table 2 — Derivation of test pressure, $p_{\rm F}$

	Application class			
	Class 1	Class 2	Class 4	Class 5
Maximum design temperature, T_{max} (°C)	80	80	70	90
Design pressure of the pipe construction, p_{CD} (MPa)	b	b	b	b
Test temperature, T _{test} (°C) ^a	95	95	80	95
Test duration, <i>t</i> (h)	1 000	1 000	1 000	1 000
Hydrostatic pressure of the pipe construction, $p_{\mathbb{C}}$ (MPa)	b	b	b	b
Test pressure, p _F (bar)				
for a design pressure, p_D , of: 4 bar	b	b	b	b
6 bar	b	b	b	b
8 bar	b	b	b	b
10 bar	b	b	b	b
Number of test pieces	3	3	3	3

NOTE 1 bar = 0.1 MPa.

If joint tests carried out in accordance with this subclause cause leaks resulting from deformation induced by differential elongation, a test pressure may be determined from the stress and creep data (relative to a design period of 50 years) for the different materials used.

Bending test 5.3

When tested in accordance with EN 713 to the pressure applicable to the 20 °C/1 h condition given in Table 3, using a bending radius equal to the minimum bend radius recommended for the pipes by the system supplier, the joint shall not leak.

The test pressure shall be calculated using the following equation:

$$p_{\mathsf{F}} = p_{\mathsf{D}} \times \frac{p_{\mathsf{C}}}{p_{\mathsf{CD}}} \tag{2}$$

where

is the hydrostatic test pressure, in bars, to be applied to the assembly during the test period;

is the value of the pressure, in bars, of the pipe construction corresponding to the time to failure/test p_{C} temperature specified in ISO 21003-2;

 p_{CD} is the design pressure value, in bars, of the pipe construction, calculated in accordance with Annex E of ISO 21003-2:2008;

is the design pressure of 4 bar, 6 bar, 8 bar or 10 bar, as applicable.

Generally, the highest test temperature is taken to be (T_{max} + 10) °C, with an upper limit of 95 °C. However, to suit existing test facilities, the highest test temperature for classes 1 and 2 is also specified as 95 °C. The hydrostatic stresses given correspond to the given test temperatures.

The values of p_{CD} , p_{C} and p_{F} result from the long-term strength data for the individual construction.

Table 3 — Test parameters for bending test

	Application class			
	Class 1	Class 2	Class 4	Class 5
Maximum design temperature, T_{max} (°C)	80	80	70	90
Design pressure of the pipe construction, p_{CD} (MPa)	а	а	а	а
Test temperature, T _{test} (°C)	20	20	20	20
Test duration, t (h)	1	1	1	1
Hydrostatic pressure of the pipe construction, $p_{\mathbb{C}}$ (MPa)	а	а	а	а
Test pressure, p _F (bar)				
for a design pressure, p_{D} , of: 4 bar	а	а	а	а
6 bar	а	а	а	а
8 bar	а	а	а	а
10 bar	а	а	а	а
Number of test pieces	3	3	3	3
NOTE 1 bar = 0,1 MPa.	•		•	
The values of p_{CD} , p_{C} and p_{F} result from the long-term strength data for the individual construction.				

5.4 Pull-out test

When tested in accordance with EN 712, using the test parameters given in Table 4, the joint assemblies shall withstand the pull-out force without being separated.

The force, *F*, shall be calculated from the following equation:

$$F = \frac{\pi}{4} \times d_{\mathsf{n}}^2 \times p_{\mathsf{D}} \tag{3}$$

where

F is the force, in N;

 $d_{\rm n}$ is the nominal outside diameter of the pipe, in mm;

 $p_{\rm D}$ is the design pressure of 4 bar, 6 bar, 8 bar or 10 bar, as applicable, expressed in MPa. In the case of the classification "all classes", the design pressure shall be 10 bar, expressed in MPa.

Table 4 — Test parameters for pull-out force

All application classes				
	Class 1	Class 2	Class 4	Class 5
	80	80	70	90
23	95	95	80	95
1	1	1	1	1
1,5 × <i>F</i>	F	F	F	F
3	3	3	3	3
	application classes — 23	application classes Class 1 — 80 23 95 1 1 1,5 × F F	application classes Class 1 Class 2 — 80 80 23 95 95 1 1 1 1,5 × F F F	application classes Class 1 Class 2 Class 4 — 80 80 70 23 95 95 80 1 1 1 1 1,5 × F F F F

The pull-out test shall be performed at 23 $^{\circ}\text{C}$ and at T_{max} for the relevant application class.

5.5 Thermal cycling test

When tested in accordance with EN 12293, using the test parameters given in Table 5, the pipes, fittings or joints, as applicable, shall withstand the test without leakage.

The test for flexible pipes shall only be used when the manufacturer declares that the pipe can be bent to the configuration shown. The bend radius shall not be smaller than the minimum declared bend radius. In all other cases, the test for rigid pipes shall be used.

For M-pipe systems, to pre-stress branch A the reference product standard and the dimensions of the inner layer shall be used.

Table 5 — Test parameters for thermal cycling

		Application class		
	Class 1	Class 2	Class 4	Class 5
Maximum design temperature, T_{max} (°C)	80	80	70	90
Highest test temperature (°C)	90	90	80	95
Lowest test temperature (°C)	20	20	20	20
Test pressure (bar) ^a	PD	p_{D}	p_{D}	₽D
Number of cycles for $D \leqslant$ 63 mm ^b	5 000	5 000	5 000	5 000
Number of cycles for D > 63 mm ^c	2 500	2 500	2 500	2 500
Number of test pieces	One set of fitti	One set of fittings with the configuration shown in EN 12293		

NOTE 1 bar = 0,1 MPa.

Pressure cycling test

When tested for leaktightness under the action of pressure cycling in accordance with EN 12295, using the test parameters given in Table 6, the pipes, fittings or joints, as applicable, shall not leak.

Table 6 — Test parameters for pressure cycling

Test temperature	23 °C		
Number of test pieces	3		
Frequency of pressure cycling	(30 ± 5) cycles per minute		
Number of cycles	10 000		
Test pressure limits for a design pressure of:	Upper limit	Lower limit	
4 bar	6,0 bar	0,5 bar	
6 bar	9,0 bar	0,5 bar	
8 bar	12,0 bar	0,5 bar	
10 bar	15,0 bar	0,5 bar	
NOTE 1 bar = 0,1 MPa.			

 $p_{\rm D}$ is the design pressure of 4 bar, 6 bar, 8 bar or 10 bar, as applicable.

b Each cycle shall comprise 15 min at the highest test temperature and 15 min at the lowest (i.e. the duration of one cycle is 30 min).

Each cycle shall comprise 30 min at the highest test temperature and 30 min at the lowest (i.e. the duration of one cycle is 60 min).

5.7 Leaktightness under vacuum

When tested for leaktightness under vacuum in accordance with EN 12294, using the test parameters given in Table 7, the change in vacuum pressure shall not be greater than 0,05 bar.

Table 7 — Test parameters for leaktightness under vacuum

Test temperature	23 °C
Number of test pieces	3
Test pressure	– 0,8 bar
Test duration	1 h
NOTE 1 bar = 0,1 MPa.	

Annex A

(normative)

List of reference product standards

Table A.1 — List of reference product standards

Material	Reference product standard
PB	ISO 15876-1, ISO 15876-2, ISO 15876-3, ISO 15876-5
PE-RT	ISO 22391-1, ISO 22391-2, ISO 22391-3, ISO 22391-5
PE-X	ISO 15875-1, ISO 15875-2, ISO 15875-3, ISO 15875-5
PP	ISO 15874-1, ISO 15874-2, ISO 15874-3, ISO 15874-5
PVC-C	ISO 15877-1, ISO 15877-2, ISO 15877-3, ISO 15877-5

Not for Resale

Bibliography

- [1] ISO/TS 21003-7, Multilayer piping systems for hot and cold water installations inside buildings Part 7: Guidance for the assessment of conformity
- [2] ENV 12108, Plastics piping systems Guidance for the installation inside buildings of pressure piping systems for hot and cold water intended for human consumption

ICS 23.040.01; 91.140.60

Price based on 9 pages