

---

---

**Nuclear fuel technology — Alpha  
spectrometry —**

Part 2:

**Determination of plutonium in uranium  
and its compounds**

*Technologie du combustible nucléaire — Spectrométrie alpha —*

*Partie 2: Détermination du plutonium dans l'uranium et ses composés*



Reference number  
ISO 21847-2:2007(E)

© ISO 2007

**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 21847-2 was prepared by Technical Committee ISO/TC 85, *Nuclear energy*, Subcommittee SC 5, *Nuclear fuel technology*.

ISO 21847 consists of the following parts, under the general title *Nuclear fuel technology — Alpha spectrometry*:

- *Part 1: Determination of neptunium in uranium and its compounds*
- *Part 2: Determination of plutonium in uranium and its compounds*
- *Part 3: Determination of uranium 232 in uranium and its compounds*

\*\*\*\*\*

# Nuclear fuel technology — Alpha spectrometry —

## Part 2: Determination of plutonium in uranium and its compounds

### 1 Scope

This part of ISO 21847 describes a method for determining trace amounts of  $^{238}\text{Pu}$  and  $^{239}\text{Pu} + ^{240}\text{Pu}$  in uranium hexafluoride, uranium oxides or uranyl nitrate.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

### 3 Principle

$\text{UF}_6$  samples are hydrolyzed, and solid samples are dissolved.

$\text{Pu(VI)}$  and  $\text{Pu(IV)}$  are reduced to  $\text{Pu(III)}$  by hydroxylamine hydrochloride. The  $\text{Pu(III)}$  is then oxidized to  $\text{Pu(IV)}$  by sodium nitrite. The  $\text{Pu(IV)}$  is extracted by thenoyltrifluoroacetone and measured by alpha spectrometry.

NOTE Impurities adversely affect the Pu reduction/oxidation cycle and can modify the extraction efficiency.

### 4 Reagents and materials

Use reagents of recognized analytical grade.

**4.1 Water**, at least quality 1 as specified in ISO 3696.

**4.2 Nitric acid**, concentrated,  $c(\text{HNO}_3) = 15,8 \text{ mol/l}$ .

**4.3 Nitric acid**,  $c(\text{HNO}_3) = 10 \text{ mol/l}$ .

**4.4 Nitric acid**, dilute,  $c(\text{HNO}_3) = 0,8 \text{ mol/l}$ .

**4.5 Thenoyltrifluoroacetone**, (TTA;  $\text{C}_8\text{H}_5\text{F}_3\text{O}_2\text{S}$ ) solution in xylene,  $c(\text{C}_8\text{H}_5\text{F}_3\text{O}_2\text{S}) = 0,5 \text{ mol/l}$ .

Prepare the solution weekly. Equilibrate the solution with dilute **nitric acid** (4.4).

**4.6 Hydroxylamine hydrochloride**,  $c(\text{ClH}_4\text{NO}) = 3 \text{ mol/l}$ .

Prepare the solution immediately before use.

**4.7 Sodium nitrite**,  $c(\text{NaNO}_2) = 5 \text{ mol/l}$ ,  $\rho(\text{NaNO}_2) = 345 \text{ g/l}$ .

Prepare the solution immediately before use.

**4.8 Standard solution of  $^{238}\text{Pu}$  or  $^{239}\text{Pu}$** , prepared from any one of a number of certified reference materials.

A  $^{238}\text{Pu}$  spike is recommended.

**4.9 Gas mixture**, with a volume fraction of 90 % argon and a volume fraction of 10 % methane.

## 5 Apparatus

**5.1 Standard laboratory equipment.**

**5.2 Frisch grid ionization chamber**, with argon-methane gas mixture, or **semiconductor detector**.

**5.3 Multichannel amplitude analyser.**

**5.4 Stainless steel disks**, approx. 60 mm diameter, or **watch glasses**.

**5.5 Epiradiator.**

## 6 Preparation of test sample

**6.1** Hydrolyze the  $\text{UF}_6$  sample. Prepare uranium nitrate solution.

**6.2** Dissolve the oxide sample in concentrated nitric acid (4.2) to obtain uranium nitrate solution.

## 7 Procedure

### 7.1 Preparation of test solution

**7.1.1** Place a test portion containing about 2 g of uranium in a beaker.

**7.1.2** If necessary, add a known quantity of  $^{238}\text{Pu}$  (4.8).

**7.1.3** Add 10 ml of concentrated nitric acid (4.2).

**7.1.4** Dry.

**7.1.5** Repeat operations 7.1.3 to 7.1.4 three times for  $\text{UF}_6$  hydrolysates.

**7.1.6** Add 1 ml of hydroxylamine hydrochloride solution (4.6).

**7.1.7** Evaporate dry, and then dissolve in 10 ml of dilute nitric acid (4.4).

**7.1.8** Add 0,2 ml of sodium nitrite solution (4.7).

**7.1.9** Bring to a boil for 2 min to eliminate the nitrous fumes, and then allow cooling for 15 min.

## 7.2 Extraction

- 7.2.1 Pour the solution into a separatory funnel; rinse the beaker three times with 1 ml of dilute nitric acid (4.4).
- 7.2.2 Add the rinsing solutions to the test solution.
- 7.2.3 Add 5 ml of TTA (4.5) and agitate mechanically for 10 min.
- 7.2.4 Allow the phases to separate.
- 7.2.5 Retain the organic phase.
- 7.2.6 Add 5 ml of TTA (4.5) to the aqueous phase, agitate mechanically for 10 min.
- 7.2.7 Allow the phases to separate.
- 7.2.8 Discard the aqueous phase and combine the two organic phases.
- 7.2.9 Add 10 ml of dilute nitric acid (4.4) to the organic phase, agitate mechanically for 2 min.
- 7.2.10 Allow the phases to separate.
- 7.2.11 Discard the aqueous phase.
- 7.2.12 Add 10 ml of dilute nitric acid (4.4) to the organic phase, agitate mechanically for 2 min.
- 7.2.13 Allow the phases to separate.
- 7.2.14 Discard the aqueous phase.

## 7.3 Stripping (optional)

- 7.3.1 Add 5 ml of nitric acid solution (4.3) to the organic phase, agitate mechanically for 5 min.
- 7.3.2 Allow the phases to separate.
- 7.3.3 Discard the organic phase.

## 7.4 Preparation of source sample

- 7.4.1 Place 0,2 ml of the organic phase (or the aqueous phase after stripping) on a stainless steel disk or a watch glass (5.4).
- 7.4.2 Dry under an epiradiator (5.5) for 15 min.

## 7.5 Measurement

- 7.5.1 Place the source in the Frisch grid ionization chamber or semiconductor detector (5.2).
- 7.5.2 Create a vacuum in the chamber, and then fill it with the gas mixture (4.9).
- 7.5.3 Set the multichannel analyser to the 4 MeV to 7 MeV energy band and record an alpha spectrum.

NOTE The counting time depends on the source activity and the detection system.

- 7.5.4 Periodically perform background counts for the same time on a stainless steel disk (5.4) without any deposit.

NOTE The source can also be used to obtain a  $\beta$  count to determine  $^{241}\text{Pu}$ .

## 8 Expression of results

Subtract the background count from the source sample count.

Calculate the massic activity,  $a_{Pu}$ , of plutonium, expressed as becquerels per gram uranium, by Equation (1):

$$a_{Pu} = \frac{A_s \times 10^3 \times V_{ph}}{t \times \eta_e \times \eta_d \times V_{tp} \times V_s \times \rho_U} \quad (1)$$

where

$A_s$  is the number of pulses during the counting time;

$t$  is the counting time, expressed in seconds;

$\eta_e$  is the extraction efficiency calculated by measuring the standard prepared from a reference solution and measured under the same conditions (7.1.2);

$\eta_d$  is the detection efficiency of the source;

$V_{tp}$  is the volume, expressed in millilitres, of the test portion of UF<sub>6</sub> hydrolyzate or uranyl nitrate;

$\rho_U$  is the mass concentration, expressed in grams per litre, of uranium in the UF<sub>6</sub> hydrolyzate or uranyl nitrate;

$V_s$  is the volume, expressed in millilitres, of the organic or aqueous phase taken for the source sample on stainless steel disk (equal to 0,2 ml);

$V_{ph}$  is the volume, expressed in millilitres, of organic phase used for the extraction or the volume of the aqueous phase after stripping.

Measure the extraction efficiency by adding a known quantity of <sup>238</sup>Pu or <sup>239</sup>Pu (7.1.2).

## 9 Precision

Reproducibility standard deviation is 0,8 Bq/g for a level of 20 Bq/g of U.

A yield equal to or higher than 90 % indicates that the method is working well (that there is no bias).

## 10 Test report

The test report shall include the following information:

- a) identification of the sample;
- b) method used by reference to this part of ISO 21847;
- c) results and the form in which they are expressed;
- d) any unusual features noted during the test;
- e) any operations not included in this part of ISO 21847, or regarded as optional.



www.iso.org/standard/68811.html

---

---

**ICS 27.120.30**

Price based on 4 pages