
**Durability of wood and wood-based
products — Use classes**

Durabilité du bois et des produits à base de bois — Classes d'emploi



Reference number
ISO 21887:2007(E)

© ISO 2007

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.



COPYRIGHT PROTECTED DOCUMENT

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 21887 was prepared by Technical Committee ISO/TC 165, *Timber structures*, Subcommittee SC 1, *Wood materials — Durability and preservation*.

Introduction

This document defines a system of use classification for wood products based on the degree of exposure to water and soil in different service conditions and the biological agents of deterioration expected in these conditions, allowing for variation among geographic regions. As of the date of publication of this International Standard, there was insufficient inter-regional trade in treated wood products to justify the development of a complete system of ISO standards for durability of wood and wood-based products. However, a unified system of use classes was anticipated to facilitate the existing level of trade and provide the foundation for a complete system of standards should this be deemed appropriate in the future. In developing this use classification system, the need for minimal conflict with existing national and regional standardization systems has been considered paramount. For more information on the application of this International Standard in national and regional standardization of the durability of wood and wood-based products, refer to Annex A.

.....

Durability of wood and wood-based products — Use classes

1 Scope

This International Standard defines five use classes that represent different service situations to which wood and wood-based products can be exposed all over the world. Subclasses are also defined for these use classes.

NOTE These subclasses might or might not be employed in national or regional standards depending on local needs.

This International Standard applies only to preservatives and processes for pre-treatment of wood and wood products and is not intended for products and processes for remediation and eradication of existing damage to timber. The annex to this International Standard provides guidance on applying use classification to specify preservative treatments, treated wood, naturally durable and modified wood but does not provide definitive specifications.

2 Definition of use classes

2.1 General

This system of use classes is derived from basic principles used in several established durability standardization systems in various parts of the world. Use class 1 represents the least aggressive service condition with the narrowest range of biological agents of deterioration and use class 5 represents the most aggressive service condition with the largest range of biological agents. In each use class, subclasses are identified based on smaller variations in service conditions or geographic variations in biological agents that justify use of different levels of preservative treatment or natural durability, or the use of different types of treatment. Where subclasses are not indicated, all biological agents listed under the use classes listed in Table 1 can be expected.

2.2 Use class 1

Use class 1 applies to situations in which the wood or wood-based product is under cover, fully protected from the weather and not exposed to wetting. There is no potential for growth of decay fungi but attack by wood-boring insects such as lyctids, anobiids and cerambycids can be expected, and in some regions certain genera of termites. Use class 1 is separated into two subclasses with different sets of biological agents based on geographic regions. Subclass 1A is appropriate for regions where wood-boring insects are recognized as an economically significant problem. Subclass 1B is appropriate for regions where, additionally, dry-wood termites are recognized as an economically significant problem.

2.3 Use class 2

Use class 2 applies to situations in which the wood or wood-based product is under cover and fully protected from the weather but where occasional, but not persistent, wetting can occur. In addition to wood-boring beetles, disfiguring fungi also occur. Use class 2 is separated into two subclasses with different sets of biological agents based on geographic regions. Subclass 2A is appropriate for regions where decay fungi are recognized as an economically significant problem. Subclass 2B is appropriate for regions where termites are also recognized as an economically significant problem.

2.4 Use class 3

Use class 3 applies to situations in which the wood or wood-based product is not under cover and not in contact with the ground. It is either continually exposed to the weather or is protected from the weather but subject to frequent wetting. Use class 3 is subdivided into two subclasses, 3.1 and 3.2, with different degrees of exposure to weathering. Subclass 3.1 represents wood products that are clad or coated and are designed to have free-draining surfaces or are otherwise protected. Subclass 3.2 represents wood products in uses fully exposed to the weather. Wood-boring beetles, disfiguring fungi and decay fungi are always expected. Termites can be expected in some geographic regions.

2.5 Use class 4

Use class 4 applies to situations in which the wood or wood-based product is in contact with the ground or fresh water and, thus, is permanently exposed to wetting. Use class 4 is subdivided into two subclasses, 4.1 and 4.2, with different soil conditions and leaching exposures. Subclass 4.1 represents relatively uncultivated, not particularly aggressive soils. Subclass 4.2 represents highly cultivated soils where organic amendment, fertilizing and irrigation for certain crops can create a much greater level of biological activity. Soils that support strand-forming wood-decay fungi can also fall into this subclass. Subclass 4.2 also covers permanent exposure to fresh water. Wood-boring beetles, disfiguring fungi, decay fungi and soft-rot fungi are always expected. Termites can be expected in some geographic regions.

2.6 Use class 5

Use class 5 applies to situations in which the wood or wood-based product is permanently or regularly submerged in salt water. For the above-water parts, wood-boring insects, disfiguring fungi, decay fungi and soft-rot fungi can be expected. In addition, for the below-water parts, marine borers are expected. Use class 5 is separated into three subclasses with different sets of biological agents based on geographic regions. Subclass 5A is appropriate for regions where teredinids and *Limnoria* are recognized as economically significant problems. Subclass 5B is appropriate for regions where teredinids, *Limnoria* and creosote-tolerant *Limnoria* are recognized as economically significant problems. Subclass 5C is appropriate for regions where teredinids, *Limnoria* (including creosote-tolerant species) and pholads are recognized as economically significant problems.

2.7 Protected

“Protected” in the context of this International Standard refers only to protection from direct weathering or any other direct water contact (for example, by design or by application and maintenance of surface coatings).

3 Application of use classes in national and regional standards

Annex A describes how this class system can be applied as existing regional and national standardization systems use classification in different ways¹⁾. Use classes might or might not be used to determine what evaluation methods should be applied to new preservative treatments or newly imported, naturally durable species for each class. Use classes might or might not be used to mark treated products to indicate suitability for different uses. Use classes might or might not imply a certain design life.

1) It is necessary to contact representatives of national or regional standardization authorities to determine how this system of use classes is being applied.

Table 1 — Use classes and subclasses, typical uses and occurrence of biological agents

Class	Service conditions		Typical uses	Biological agents		
1	Interior, dry		Framing Roof timbers	Insects	A	Wood-boring beetles
					B	As 1A plus dry-wood termites
2	Interior, damp		Framing Roof timbers	Wood boring beetles Disfiguring fungi Termites	A	As 1A plus decay fungi
					B	As 2A plus termites
3	3.1	Exterior, above-ground protected from the weather	Exterior joinery	Wood boring beetles Disfiguring fungi Decay fungi Termites		
	3.2	Exterior, above-ground unprotected from the weather	Cladding Deck boards			
4	4.1	In-ground	Fence posts Landscape timber	As 3 plus soft rot fungi		
	4.2	In-ground, severe, fresh water	Cooling tower fill			
5	Marine		Boat hulls Marine Piles Jetties	As 4 plus marine borers	A	Teridinids plus <i>Limnoria</i>
					B	As 5A plus creosote-tolerant <i>Limnoria</i>
					C	As 5B plus pholads
<p>A higher use class may be assigned if it is anticipated that service conditions can arise that result in a higher risk to the timber than that normally experienced by the typical uses listed.</p>						
<p>NOTE It might not be necessary to protect against all biological agents listed, as they might not be present or economically significant in all service conditions in all geographic regions.</p>						

Annex A (informative)

An international framework for classifying wood products' durability based on use classes

A.1 General

The World Trade Organization Agreement on Technical Barriers to Trade, the TBT Code, obliges signatory countries not to raise non-tariff barriers to trade, such as standards. The TBT Code states that the standardization body of any signatory country should ensure that standards are not prepared, adopted or applied with a view to, or with the effect of, creating unnecessary obstacles to international trade. Thus, alignment of national standards with any equivalent International Standard becomes a nation's responsibility within the TBT Code if, otherwise, there is a risk of creating barriers to trade. Exceptions can be justified if there are "fundamental climatic or geographical factors" that make their alignment inappropriate or ineffective. In the case of wood-preservation standards, such factors are likely to have a major influence on their application. However, local or geographical regional variations, for example, can be accommodated by the application of the International Standard through a guidance or framework document.

This annex describes the mechanisms by which wood preservatives and treated wood or naturally durable wood are specified for domestic and international trade within and among the major trading regions of the world, in accordance with the TBT Code.

Whilst some of the procedures developed in the different regions have features in common, distinct differences often have evolved in response to particular local geographical, climatic or end-use needs. Well established practices in different regions are often embodied in codes and standard specifications that themselves are either part of or integrated into national or regional regulations.

The value of world-wide exports for sawn timber, wood-based panels and round-wood such as poles, piles and posts is about US \$50 billion per year. While international trade in preservative treated timber represents only a fraction of this value, it is expected to increase steadily over the next decade. This necessitates the application of the TBT Code in order to minimize any potential barriers to trade arising from differing national or regional specifying practice. Removal of actual or potential barriers to trade includes addressing harmonization of the codes and standard methods used for specification. However, the scope, extent and pace of the inevitable changes this implies requires that the full range of costs, as well as benefits, be taken into account relative to the scale of the trade itself.

A.2 Biological hazards to timber

Wood preservatives are used to enhance any natural resistance of timbers or confer suitable resistance against biological wood attacking agencies that can arise as a consequence of the particular circumstances of use. Different end-use situations are characterized by different local environmental conditions, in particular the extent of exposure to moisture. These different end-use situations represent different ecological niches (habitats) for individual and groups of biological agencies. Often, there are very specific individuals or types of organisms that colonize in particular situations. This is because the combination of moisture, temperature and food material determines which biological organisms are present, depending on their particular preferences.

Whilst some organisms occur widely throughout the world, many more are very specific to particular climatic regions, soils or waters. For example, the wood-destroying termites differ from region to region around the world and often display varying degrees of aggressiveness against different wood commodities.

A further aspect of the natural world that impacts on specifying preservatives and treatments is the type of wood used. The trees from which wood is cut vary enormously in different regions, and different organisms have different abilities and preferences for attacking different timbers.

A.3 Use class

The “use class” system is a means for defining different in-service environments within which wood and wood-based products are used. In practically every major established specification system in the world, the concept of in-service use class is used, though definitions and interpretations vary. Use classes not only describe the distinct circumstances of end-use (service situations) but also reflect different classes of biological hazards likely to be encountered. On this basis, commodities can be assigned to a use class which in turn prescribes the distinct preservation requirements necessary to provide adequate resistance to the organism(s) which prevail in that situation (use class).

The use class classification systems that have been developed around the world have much in common, deriving from adoption of similar basic principles. However, issues at a local level, including those with important economic consequences, have led to the development of specific classes or subclasses.

In each of the different use class systems, class 1 (see 2.2) represents the least biologically demanding situation in terms of wetness sufficient to permit fungal decay. Consequently the lower use classes (1 and 2 and any sub-divisions; see 2.2 and 2.3) generally provide for in-service circumstances where there may be significant risks of attack by some wood-boring insects such as lyctids, anobiids, cerambycids and some genera of termites, but little or no fungal hazard.

The intermediate use classes (3 and any sub-divisions; see 2.4) provide for in-service circumstances where timber is out of ground contact, exposed to wetting, and can have varying degrees of protection or shelter. The main biological hazards are decay, some wood-boring insects and termites.

The higher use classes (4 and 5 and any subclasses; see 2.5 and 2.6) provide for service situations in contact with the ground, or with fresh or salt water. In these classes the biological hazards are diverse and may be extreme.

A.4 Design and service considerations

Subclasses can be identified based on variations in service conditions or geographic variations in biological agents that justify use of different levels of preservative treatment or the use of different types of treatment.

In principle, it is accepted internationally that assignment of a commodity or building component to a particular use class is complemented by good design use and maintenance of the construction. A higher use class may be assigned if it is anticipated that service conditions can arise that result in a higher risk to the timber than that normally experienced by the typical uses listed. Similarly, a higher use class may be assigned if there is a particularly critical aspect to the treated commodity or component’s end use when judged over the entire service life of the construction. A specifier or user may, therefore, opt for a somewhat higher level of assurance through adopting the preservation requirements related to a higher use class situation.

In addition to biological use classification and design considerations, other service factors exist related to safety (criticality of end-use; see previous paragraph), as well as economic and service life requirements. It is necessary that these factors be taken into account by specifiers or users when making a judgement on the need for preservative treatment and the level of protection. In addition, it is necessary to balance the extra costs of preservative pre-treatment or the use of timbers of sufficient natural durability against the future costs of remediation or repair of failed components. For example, some timber components can have a shorter required service life or can be relatively simple and inexpensive to replace. Under such circumstances, the costs of preservation or higher durability timber might not be justified. Conversely, where remediation or repair is expensive, or where deterioration can lead to serious structural weakening or collapse, which can compromise safety, then it is necessary to specify an appropriate level of durability, either by using naturally durable timber or through preservative treatment.

A.5 Natural durability and treatability of timber

Different timber species vary in their resistance to attack by the range of wood-destroying organisms in different parts of the world. Whilst the sapwood of most wood species is generally not resistant to biological attack, the heartwood ranges from also being not resistant to being very resistant. The usual method of classifying the natural durability of different timbers is based on the resistance of their heartwood to attack by wood-destroying fungi and, where relevant, termites, as determined by service life in ground contact. Such a system is used as the basis for recommending whether or not treatment is necessary in different service environments.

Besides inherent durability, the treatability of timbers with preservative solutions is another natural characteristic that varies greatly according to the species. Hence, when a particular timber species is considered for a particular end-use, the option to apply a given level of preservative treatment depends upon its treatability as well as its inherent durability. Alternatively, if the timber is difficult to treat, protection from an envelope treatment may be considered, depending upon the specific end-use. Whilst in qualitative terms there is widespread international acceptance of which timbers are “resistant” to treatment and those that are “easily treatable”, precise criteria used for classification purposes vary from region to region.

Variations in the natural durability and treatability of the particular timber species of local economic importance are dealt with in the local codes and standard specifications in the different geographical regions.

A.6 Selection and specification of preservative treatments

Where the durability of a given timber component is achieved by treatment with preservatives and where it is intended to market treated timber components with a specific level of durability, it is necessary that preservation be appropriate to the particular local recommendations or regulatory requirements. Indeed, varying local conditions can lead to different service life expectations and requirements for the same commodity or component in different parts of the world. Hence, this annex addresses the principle of regional and local needs.

Currently, the procedures for defining particular preservation requirements vary significantly in different geographical regions of the world. Some systems provide highly specific and prescriptive requirements in terms of wood species, preservative types, loadings and penetrations, whilst others are less prescriptive and performance based.

Protocols and processes for validating the effectiveness of preservatives vary around the world, since they are influenced by specific local requirements governed by distinctive local biological agencies. It is necessary to contact representatives of the national or regional standardization authorities to determine how the system of use classes described in this International Standard is being applied.

1

© ISO 2015

ICS 71.100.50; 79.040; 79.060.01

Price based on 6 pages